

CERTIFICATE OF ANALYSIS/QUALITY

African Mining & Commodities

Report Date: 30 September 2025

Job Number:	COTMIN0037_25RCB	Inspection Date:	25 th September 2025
Commodity:	Iron Ore	Quantity:	700.000 MT (As Advised)
Place Of Inspection:	Northern Cape	Stockpile Reference:	S.LOT 01
Sample Date Received:	30 th September 2025	Sample Date Analysed:	30 th September 2025

Methods: Analysis performed on SAMPLED/SUBMITTED SAMPLE(s). Analysis performed in accordance with Laboratory Developed Methods and/or ISO Standards.

Analytical Methods Used

Sample Preparation – Mineral Ores
Elemental Analysis Of Iron Ore by ICP
Determination Of Moisture in Minerals
Increment Sampling of Mineral Ore

Method ID

COT/01/MIN-PREP
COT/05/FE
COT/01/MIN-MOIST
COT/01/INC

In pursuance of an order given to us by our principal African Mining & Commodities to convey increment sampling and chemical analysis on what was advised to be an Iron Ore stockpile we report the following:

- Sampling (Sampling Plan: COTMIN0037_25RCB)
- Moisture Determination
- Analysis

Visual Identification Of Cargo

The material was stored in one (01) open stockpiles. The material had a visual top size estimated to be + 80mm and in a dry condition. All the material was stored in an open storage area exposed to all elements and any possible contamination, storage area floor was also loose, the material was brownish in colour (Typically Iron ore).

Sampling Procedure

Sampling was conducted using a 300mm x 200mm x 300mm aperture ISO standard scoop. Random increments were drawn at varying heights around the stockpile. Samples were decanted into labelled sample bags, which were sealed to prevent moisture loss and possible contamination. Increment samples were continually drawn in this manner and one (01) lot sample was created. The results below are reported.

Job Number: COTMIN0037_25RCB

CHEMICAL ANALYSIS

Elements	Results	Units
Aluminium, as Al_2O_3	1.85	%
Calcium, as CaO	0.05	%
Iron, as Fe	62.50	%
Magnesium, as MgO	0.05	%
Manganese, as Mn	1.23	%
Phosphorus, as P	0.045	%
Silica, as SiO_2	5.53	%
Titanium, as TiO_2	0.096	%
Moisture	0.29	%

SIZING ANALYSIS

Sizing	Results	Units
100 - 30 mm	83.76	%
+25 mm	13.11	%
Pan	3.13	%
Total	100	%



Sabelo Mkhabela
Technical Signatory



Signed & dated in South Africa on this day, 30th of September 2025 for & on behalf of Cotecna South Africa.

Results in this report relate to items tested. The sample(s), to which the findings recorded herein (the "Findings") relate, was (were) drawn and / or provided by the Client or a third party acting on Client's directions. The Findings constitute no warranty of the sample's representativity of all the goods and strictly relate to the sample(s). Cotecna South Africa accepts no responsibility and/ or liability for the consequences of any action taken or not taken on the basis of this certificate/report. This certificate may not be reproduced in part or full without written permission from the Quality Manager of the laboratory. A copy of this test report is available from this laboratory upon request. Analysis marked "*" in this report are subcontracted to another laboratory. Cotecna General Terms & Conditions are available at <https://www.cotecna.com/en/terms-and-conditions> and apply to all services provided by companies of the Cotecna group.