

BUREAU OF INDIAN STANDARDS

DRAFT FOR COMMENTS ONLY

(Not to be reproduced without permission of BIS or used as an Indian Standard)

भारतीय मानक मसौदा
ईस्ट इंडिया टैन किए हुए किप्स और खाल — विशिष्टि
(IS 1639 का पहला पुनरीक्षण)

Draft Indian Standard
East India Tanned Kips and Skins — Specification
(First Revision of IS 1639)
(ICS 59.140.20)

Leather, Tanning Materials and Allied Products Sectional
Committee, CHD 17

Last Date for Comments: As per the covering letter

Foreword

(Formal clause will be added later)

East India tanning industry has been, for over a century, a valuable foreign earner to the Indian Government fetching as much as Rs 250 million annually. For the smooth working of such a valuable export trade, the maintenance of integrity through standards is essential. The fact that this trade has existed for over a century suggests that some sort of quality control grading, etc, within the trade are practiced. In fact, a system, of assessment and arbitration is prevalent, but the methods followed under the system are based on age-long, master-to-the-pupil experience. However, this very useful knowledge gained through experience by the sorters has not been resolved and expressed in scientific terms in the form of a standard specification wherein the chemical characteristics of the material are clearly stipulated. The requirements of the material as laid down in this standard were adopted by the Leather Export Promotion Council under the scheme of Voluntary Quality Control in the E.I Tanning Industry, since the requirements were met with the general approval of the exporters in India and the importers abroad

This standard was first published in 1960. In this revision the following changes have been incorporated:

- a) Method of test for water soluble matter has been updated; and
- b) Relevant clauses and reference clause have been added, and necessary editorial corrections have been made. Aligned with latest style and format of the Indian Standards.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1 SCOPE

1.1 This standard specifies chemical requirements of East India tanned leathers for pure tannage and includes all leathers under the category of prime tannages, semi-prime tannages and single tannages.

1.2 This standard excludes all other East India tanned leathers pertaining to mixed tannages and market quality East India tanned leathers.

2 REFERENCES

The standards listed in Annex A contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of these standards.

3 TERMINOLOGY

3.1 For the purpose of this specification, the definitions given in IS 1640 shall apply.

4 SAMPLING AND PREPARATIONS OF SAMPLES

4.1 Scale and Position of Sampling

For the purpose of this specification, the scale and position of sampling shall be in accordance with IS 5868 (Part 2).

4.2 Preparing Sample for Chemical Analysis

The procedure in preparing the sample for analysis shall be as specified in IS 5868 (Part 2).

5 REQUIREMENTS

The material shall comply with the requirements prescribed in Table 1.

6 TESTS

Test shall be conducted as prescribed in IS 582. References to the relevant clauses of IS 582 are given in col 4 of table 1.

Table 1 Chemical Requirements for East India Tanned Kips and Skins

(Clauses 5 and 6)

Sl No.	Characteristic	Requirement	Method of Test ref to IS 582
i)	Moisture content	all put together 39 percent by mass, <i>Max</i>	LC : 2
ii)	Solvent extractable substance		Part 14
iii)	Water-soluble matter		Part 2
iv)	Insoluble ash		Part 3
v)	Hide substance, percent by mass, <i>Min</i>	62	Part 12

7 PACKING AND MARKING

7.1 Packing

The East India tanned kips and skins shall be packed as agreed between the purchaser and the supplier.

7.2 Marking

The packages shall be marked with the name of the manufacturer, number of pieces of East India tanned kips and skins; recognized trade-mark, if any; and month and year of manufacture.

7.2.1 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.

ANNEX A

(Clause 2)

LIST OF REFERRED INDIAN STANDARD

<i>IS/ISO No</i>	<i>Title</i>
IS 582 : 1970	Method of chemical testing of leather (<i>first revision</i>)
IS 582	Methods of chemical testing of leather
Part 2: 2024/ ISO 4098 : 2018	Determination of Water-Soluble Matter, Water-Soluble Inorganic Matter and Water-Soluble Organic Matter (<i>first revision</i>)
Part 3: 2017 ISO 4047 : 1977	Determination of sulphated total ash and sulphated water - Insoluble ash (<i>second revision</i>)
Part 12 : 2022	Determination of nitrogen content and hide substance Titrimetric method
Part 14 : 2022	Determination of matter soluble in dichloromethane and free fatty acid content
IS 1640 : 2007	Glossary of terms relating to hides, skins and leather (<i>first revision</i>)
IS 5868 (Part 2) : 2025	Leather - Methods of sampling Part 2 Position and Preparation of Specimens for Testing for Chemical, Physical, Mechanical and Fastness Tests (<i>second revision</i>)