

BUREAU OF INDIAN STANDARDS

DRAFT FOR COMMENTS ONLY

(Not to be reproduced without the permission of BIS or used as an amendment to Indian Standard)

DRAFT AMENDEMENT NO. 1 TO IS 15298 (Part 4) : 2024 PERSONAL PROTECTIVE EQUIPMENT PART 4 OCCUPATIONAL FOOTWEAR (ISO 20347 : 2021, MOD) <i>(Third Revision)</i> ICS 13.340.50	
Footwear Sectional Committee, CHD 19	Last Date for Comments : As per the covering letter

(Foreword, Para 10) — Insert the following new para

‘In this standard, certain modifications due to particular needs of Indian footwear industry have been made. These technical modifications have been mentioned in National Annex C at the end of National Annex B.’

(Page 51, clause B-2.2) — Insert the following National Annex C at the end:

‘NATIONAL ANNEX C’

[Page 8, clause 5.1, Table 2, row 3 (see also National Annex A)] — Insert the following at the end:

2 nd column	3 rd column	4 th column	5 th column	6 th column	7 th column
Volatility	5.3.8	X	X	X	X

(Page 9, clause 5.1, Table 2, row 8) — Insert the following at the end:

1 st column	2 nd column	3 rd column	4 th column	5 th column	6 th column	7 th column
Fasteners	-	5.9	o	o	o	o

[Page 12, clause 5.3.7, (see also National Annex A)] — Insert the following new clause after 5.3.7.

5.3.8 Volatility

‘Three test pieces of thickness (2.0 ± 0.1) mm are taken from upper as well as the sole. When these are tested in accordance with IS 12240 (Part 4), the mean loss in mass shall not exceed 2 percent for either the test pieces taken from upper or the test pieces taken from sole.’

(Page 18, clause 5.8.7) – Insert the following new clause after 5.8.7.

5.9 Fasteners

The fasteners in the footwear shall conform to requirements as prescribed in Table 18.

Table 18 Requirements for Fasteners

S. No.	Characteristics	Requirements for Occupational footwear	Test Method
i)	^a Breaking strength, N	Min 350	Annex K of IS 15844(Part 1)
ii)	^a Aglet strength, N	Min 120	Annex L of IS 15844(Part 1)
iii)	^a Abrasion resistance, Cycles	No breakage before 7,500 cycles	Method 1 and Method 3 of IS 8085 (Part 17)/ ISO 22774
iv)	^b Corrosion resistance	Not worse than slight uniform change	IS 17098
v)	^c Strength of eyelet attachment, N	Min 250	Annex B of IS 17043 (Part 1)
vi)	^d Attachment strength of strap assembly, N		Annex D of IS 15844 (Part 1)
	a) More than 20 mm strap width	Min 200	
	b) 10 mm to 20mm strap width	Min 150	
	c) Less than 10 mm strap width	Min 100	
^a applicable for the “lace”, ^b applicable for “all metal part” of the fasteners and trims, ^c applicable for “eyelet”, ^d applicable for “strap with Buckle, d-Ring, hooks and Velcro”			

5.9.1. Zipper

‘In fasteners, if zipper is used in the footwear shall conform to requirement as prescribed in Table 19.

Table 19 Requirements for Zipper

S. No.	Characteristics	Requirements for Occupational footwear	Test Method
1	Fatigue resistance, cycles	Min 1000 cycles	ISO 10751
2	Security of puller attachment strength, N, <i>Min</i>	Min 250	ISO 10734
3	Lateral strength, N, <i>Min</i>	Min 400	ISO 10764’