

Karman Power and Labour PyRoll Plugin

Christoph Renzing

September 11, 2026

The PyRoll plugin `pyroll-karman-power-and-labour` calculates the roll-force and roll-torque as well as the mean neutral plane location for a roll-pass. Since von-Karman originally developed the strip or slap theory for flat rolling, the grooved pass is not considered directly. The solution is therefore derived for an equivalent flat pass, which makes the plugin's accuracy heavily depended on the equivalent flat pass plugins.

The plugin provides three solvers, covering the full range from thick slabs to metal foils, and selects between them automatically for each roll pass:

- a rigid-roll solver based directly on von-Kármán's differential equation (section 1), valid whenever elastic effects are negligible;
- an elastic-plastic layer model (section 2), used for medium and thick passes, that adds elastic entry/exit zones, a mixed Coulomb/stiction friction law, through-thickness resolution into multiple layers, and full thermal coupling;
- a full elastic-contour foil-rolling model (section 3), used once elastic roll flattening becomes so severe that a circular roll-gap assumption is no longer valid.

section 4 explains the criteria used to select between the three, and section 5 lists the hooks the plugin defines.

1 Rigid-roll model (von-Kármán)

The current model is based on the classic elementary theory of plasticity, which is a well known approach of modelling the stress distributions in flat rolling. The elementary theory of plasticity for flat rolling is also known as strip or slap theory, because the roll gap is divided in rolling direction in infinitesimal narrow strips, as shown in Figure 1, on which the force balance is built. In thickness direction the strip's height is equal the local height of the roll gap. The deformation of each strip is always plane and parallelepipedic. The strip's material properties are constant in thickness direction and may vary in rolling




Figure 1: Stripe element of elementary theory of plasticity

direction. Therefore, the vertical stress is constant in thickness direction and no shear deformation can be considered.

The roll surface is described as a circular arc, since elastic roll deformation is neglected in this model (see section 2 and section 3 for the elastic-plastic and elastic-contour models, which lift this restriction). So the roll gap height can be described by Equation 1. The rolls are here considered to be rigid. Also, the rolls are considered to be symmetric, meaning of equal radius R_W and rotational frequency n_W .

$$h(x) = s + 2 * \left(R_W - \sqrt{R_W^2 - x^2} \right) \quad (1)$$

The model needs additional approaches for the yield stress, and the friction between rolls and workpiece. The shear stress resulting from friction between the material and the roll surface is model by Coulomb's friction law. Since normally this model is used for cold rolling with lubricates, the friction coefficient μ has to be sufficiently high. The force balance at the stripe element leads to the well known Karmán differential equation [1, 2] as shown in Equation 4, which is an ordinary differential equation for the horizontal stress σ_x in x and can be solved easily by numerical methods. A suitable yield criterion gives the connection between σ_x and σ_y . In this approach the yield criterion according to von-Mises was chosen [3, 4].

$$0 = \sigma_x, \frac{dh}{dx} + h \frac{d\sigma_x}{dx} + 2\tau_R - 2p_N \tan(\alpha) \quad (2)$$

$$p_N = -\sigma_y - \tau_R \tan(\alpha) \quad (3)$$

$$\tau = \mu p_N \quad (4)$$

This rigid-roll solution never resolves elastic zones (the whole contact is assumed plastic from the first point of contact) and does not couple to temperature; it is implemented in

`karman_solver.py` as `KarmanSolver`.

2 Elastic-plastic layer model for medium and thick passes

For medium and thick passes, the rigid-roll assumption of section 1 misses three effects that become significant as the relative pass thickness grows: an elastic entry/compression zone and elastic recovery zone at exit (rather than the whole contact being plastic immediately), a friction law that can saturate into sticking rather than remaining Coulomb throughout, and, once the strip is thick enough relative to the contact length, meaningfully different flow stress between the surface (which alone feels roll-contact friction) and the core through the pass. `layer_solver.py` implements `LayerRollingSolver`, a layer-count-parametrized model following Weiner [5] (based on his *RollingHomogeneousElasticPlastic* and *RollingLayerModelElasticPlastic* implementations), which addresses all three:

- the strip is discretized into N through-thickness layers (the single-layer case, $N = 1$, is the "medium" regime; $N > 1$ resolves the "thick slab" regime);
- each layer starts elastic and yields once its own local Mises/Tresca criterion is met, giving genuine elastic entry and exit zones per layer instead of a single sharp elastic/plastic split;
- friction at the roll interface, and between adjacent layers, follows a mixed Coulomb/sticking law after Bay and Wanheim [6], transitioning smoothly from Coulomb sliding to a sticking-limited shear stress as normal pressure grows;
- deformation heat, friction heat, conduction between neighbouring layers (and to the rolls), and convective transport are solved simultaneously with the stress equations, so each layer's temperature - and hence its flow stress - evolves individually through the pass.

Roll flattening is deliberately out of scope here, as it is for `KarmanSolver` and `FoilRollingSolver`'s own base radius: all three solvers simply read `Roll.working_radius` once rather than deriving a flattened radius themselves. A separate plugin providing a Hitchcock [7] (or other) flattened radius via that hook is therefore picked up transparently by every solver in this plugin, with no special-casing needed; the classical linear Hitchcock relation implemented in `condition.py` (`hitchcock_radius_ratio`) exists solely to *classify* a pass for dispatch (section 4), and is never fed back into a calculation.

Because each pass only sees the incoming profile's own scalar strain and temperature (`pyroll-core` has no native concept of a through-thickness state carried from one pass to the next), all layers start uniform; the elastic entry zone therefore has no mechanism to break symmetry between layers (matching the reference implementation, which defines but never uses a redundant-shear correction after Ekelund [8]). Layers still diverge from the first plastification onward, since only the outermost layers feel roll-contact friction directly while inner layers feel the weaker inner-friction law, and the resulting temperature and flow-stress differences compound through the rest of the pass.

3 Full elastic-contour foil-rolling model

Once elastic roll flattening becomes severe enough, even a scalar (Hitchcock) roll-flattening correction to `Roll.working_radius` is no longer accurate, because the flattened roll-gap shape stops being well approximated by a single effective radius. `foil_solver.py` implements `FoilRollingSolver`, following Mauk and Overhagen [9], which instead computes the true, generally non-circular, deformed roll-gap shape directly: the normal-pressure distribution along the contact is superposed with elastic half-space (Boussinesq/Johnson [10]) influence coefficients to obtain the roll surface's own elastic deflection, iterated to convergence with the strip's own elastic-plastic stress solution (elastic entry, plastic slip, an optional sticking zone, plastic slip, elastic exit).

4 Selecting between the three models

`roll_pass.py` wires the three solvers together behind a single hook, `karman_solution`, so that `roll_force`, `Roll.roll_torque`, `Roll.neutral_point` and the profile velocity hooks work unchanged regardless of which solver actually ran:

1. if the roll or profile elastic properties (`elastic_modulus`, `poissons_ratio`) are not set, the pass falls back to the rigid-roll model of section 1 unconditionally, since none of the elastic effects can be evaluated;
2. otherwise, the Hitchcock flattened-to-nominal radius ratio r'/r is evaluated (Mauk and Overhagen [9] give $r'/r \geq 2$ as the point where a circular roll-gap assumption is no longer trustworthy); if exceeded, the foil-rolling model of section 3 is used;
3. otherwise, the classical contact-length-to-mean-thickness ratio L_d/H_m decides between the layer model's thick-slab (multiple layers) and medium (single layer) configurations, as described in section 2.

All three limits are themselves hooks (Table 1) and can be overridden per pass, including forcing a particular model unconditionally.

5 Usage instructions

The plugin can be loaded under the name `pyroll_karman_power_and_labour`.

An implementation of the `roll_force` hook on `RollPass` is provided. Furthermore, an implementation of the `roll_torque` and `neutral_point` hooks on `RollPass.Roll` is provided.

Additionally, hooks on `RollPass` are defined, which are used in the calculation, as listed in Table 1. The hooks `back_tension`, `front_tension` and `coulomb_friction_coefficient` have to be set and adjusted individually; the elastic-plastic models additionally need `elastic_modulus` and `poissons_ratio` set on both `RollPass.Roll` and `RollPass.InProfile` to be selected at all (see section 4), and the layer model's thermal coupling needs `specific_heat_capacity`, `thermal_conductivity` and `density` set on both.

Table 1: Hooks specified by this plugin.

Hook name	Meaning
<code>coulomb_friction_coefficient</code>	Coulomb's friction coefficient μ
<code>back_tension</code>	Back tension of the roll pass $\sigma_{x,0}$
<code>front_tension</code>	Front tension of the roll pass $\sigma_{x,1}$
<code>karman_solution</code>	Solver object (of one of the three models) with solution values as attributes
<code>foil_rolling_condition</code>	Whether the foil-rolling model (section 3) is used
<code>foil_rolling_hitchcock_limit</code>	Hitchcock ratio r'/r above which the foil model is used (default 2.0)
<code>thick_slab_condition</code>	Whether the multi-layer, thick-slab configuration is used
<code>layer_model_ld_hm_limit</code>	L_d/H_m ratio below which the multi-layer configuration is used (default 1.0)
<code>layer_model_layer_count</code>	Number of through-thickness layers on the thick-slab path (default 5)
<code>friction_stiction_coefficient</code>	Sticking friction coefficient feeding the Bay/Wanheim conversion (default 0.8)
<code>roll_heat_transfer_coefficient</code>	Heat transfer coefficient at the roll/material interface (default 6000 W/(m ² K))

References

- [1] Th. von Kármán. “Beitrag zur Theorie des Walzvorganges”. de. In: *Zeitschrift für angewandte Mathematik und Mechanik* (1925), pp. 139–141.
- [2] J. M. Alexander. “On theory of rolling”. In: *Proc. R. Soc. Lond.* 326 (1972), pp. 535–563.
- [3] Richard von Mises. “Mechanik der festen Körper im plastisch-deformablen Zustand”. de. In: *Nachrichten von der Gesellschaft der Wissenschaften zu Göttingen* (1913).
- [4] Richard von Mises. “Mechanik der plastischen Formänderung von Kristallen”. de. In: *Zeitschrift für angewandte Mathematik und Mechanik* (1928).
- [5] Max Weiner. “Modellierung des Walzens dünner Bänder und Folien unter Berücksichtigung elastisch-plastischer Werkstoffeigenschaften”. de. PhD thesis. Technische Universität Bergakademie Freiberg, Institut für Metallformung, 2021.
- [6] Niels Bay and Tarras Wanheim. “Real area of contact and friction stresses at high pressure sliding contact”. In: *Wear* 38 (1976), pp. 201–209.
- [7] John Hall Hitchcock. “Roll neck bearings”. In: *ASME Research Publication* (1935).
- [8] Sven Ekelund. “The analysis of factors influencing rolling pressure and power consumption in hot rolling”. In: *Steel* 93 (1933).

- [9] Paul Josef Mauk and Christian Overhagen. *Prozessmodell zum Kaltwalzen von Metallfolien mit keramischen Arbeitswalzen auf Mehrwalzengerüsten*. de. Tech. rep. Anlage zum Verwendungsnachweis, Förderkennzeichen KF2095013SU0. Universität Duisburg-Essen, Institut für Metall- und Umformtechnik, 2013.
- [10] Kenneth Langstreth Johnson. “Contact Mechanics”. In: (1985).