From: Bernardo Bordini
To: Nicolas Bourcey; Angelo Bonasia
Subject: Re: Vamas 11T#112 et #113 + cycle
Date: 13 April 2015 15:02:13

Hello Nicolat,

Sorry for the late answer, I was on vacation last week

Here is the heat treatment
48 hrs at 210 °C, 48 hrs at 400 °C, 50 hrs at 640 °C

Best Regards,
Bernardo

Bernardo Bordini
TE-MSC-SCD

CERN (European Organization for Nuclear Research)
CH-1211 Geneva 23, Switzerland
Phone: +41 22 767 3049
Fax: +41 22 767 6300
http://www.cern.ch

From: Nicolas Bourcey <Nicolas.Bourcey@cern.ch>
Date: Wednesday, April 8, 2015 6:43 AM
To: Angelo Bonasia <Angelo.Bonasia@cern.ch>
Cc: Bernardo Bordini <bernardo.bordini@cern.ch>
Subject: Vamas 11T#112 et #113 + cycle

Salut Angelo,

Peux-tu me préparer les vamas et échantillons RRR pour les bobines suivantes :

11T#112 : câble H15OC0181A

11T#113 : câble H15OC0181B

Bernardo, peux-tu stp confirmer le cycle de réaction pour ces 2 bobines ?

Je voudrais lancer la réaction de la 112 en semaine 17.

Merci d'avance et bonne journée,
Nicolas

Nicolas BOURCEY
TE-MSC-MDT
Magnet Design & Technology Section
CH-1211 Geneve 23
Tel: +41 76 487 3532

Fax: +41 22 766 8997