

Report of Analysis

LSI 6846 - 58999

To: IXM S.A.
Rue de Lausanne 15
CH-1201 Geneva Switzerland

Your ref.: BCC10072S

Att.: Ray Li

Material*: 224.995 DMT ARANZAZU COPPER CONCENTRATES

Vessel*: mv "APL ESPLANADE"

ORIGINAL

Date: 25-01-2022

Page: 1 of 1

We have analysed the samples in the received bags of the above mentioned material and report as below:

LOT	Weight DMT*	Q Cu %	Q Ag g/t	Au g/t
1	404.907	21.22	204	11.3
2	401.427	21.31	204	10.7
3	408.911	21.27	205	11.4
4	404.646	21.28	207	11.4
5	405.104	21.28	203	12.0

Composite	As =	1.88	%
Composite	Cd =	0.009	%
Composite	Zn+Pb =	1.19	%
Composite	Bi =	0.19	%
Composite	Sb =	0.12	%
Composite	Hg =	1	ppm **
Composite	F =	349	ppm
Composite	Al2O3+MgO =	1.77	%

* Provided by client

Analysis relates to the material in the dry state (@ 105°C)

** on sample as received

Cu : W0700 - Volumetric - In House Method

Ag : W0703 - AAS - In House Method

Au : W0701 - Fire Assay Gravimetric - In House Method


Q : Analysis carried out according to RvA NEN-EN-ISO/IEC 17025 Accreditation. The measurement uncertainty of the accredited analyses is available on request.

Sealed : CCICGX - Company Sealing Tape

and : Intertek - Company Stamp

and : C.C.I.C. Guangxi Co., Ltd. - Company Stamp

Sampled by : Intertek



: intact

: intact

: intact

Raymond Abell
Laboratory Manager