

# CONTENTS

I	SUPERCONDUCTIVITY	1
I.1	BCS Theory . . . . .	2
I.1.1	BCS theory as a mean field-theory (Hubbard model) . .	2
I.1.2	Multi-band BCS theory on the Hubbard model . . . . .	3
I.1.3	BdG Hamiltonian in band basis . . . . .	4
I.1.4	Grand potential . . . . .	7
I.2	Transport in superconductors: superfluid weight . . . . .	7
I.3	Ginzburg-Landau theory of superconductivity, phase transitions and broken symmetry . . . . .	7
I.3.1	Order parameter concept . . . . .	8
I.3.2	Landau theory . . . . .	8
I.3.3	Ginzburg-Landau theory I: Ising order . . . . .	10
I.3.4	Ginzburg-Landau theory II: complex order and superflow	10
I.4	Coherence length and penetration depth in strongly correlated superconductors . . . . .	12
II	DYNAMICAL MEAN-FIELD THEORY	13
II.1	Green's Function Formalism . . . . .	13
II.2	Perturbation theory, Dyson equation . . . . .	15
II.3	Nambu-Gorkov GF . . . . .	15
II.4	DMFT . . . . .	15
III	QUANTUM METRIC	17
III.1	Quantum Metric and superfluid weight . . . . .	17
IV	NONINTERACTING EG-X MODEL AND STRUCTURE	19
IV.1	Lattice Structure of Graphene . . . . .	19
IV.2	EG-X Model . . . . .	22
IV.2.1	Review: Hubbard model on the honeycomb lattice . . . .	23
IV.2.2	Band structure of the non-interacting EG-X model . . . .	23

V	EG-X MODEL WITH INTERACTIONS	27
V.1	BdG . . . . .	27
V.1.1	BdG Hamiltonian . . . . .	27
V.1.2	Derivative of the normal state Hamiltonian . . . . .	29
V.1.3	BdG Hamiltonian in band basis . . . . .	29
V.2	Grand potential . . . . .	32
	BIBLIOGRAPHY	33
	LIST OF SYMBOLS	37

# TODO LIST

Unconventional SC, what is the same, what is different, what makes it difficult to grasp . . . . .	1
Open questions in unconventional SC, what is this citation? . . . . .	1
Connection to my topic: flat bands, strong correlations . . . . .	2
Why supercurrent? . . . . .	2
BCS hamiltonian, pairing . . . . .	2
Mean-field . . . . .	2
Phonon interaction . . . . .	2
Mean field level can already explain a lot . . . . .	2
Some relevance of the repulsive Hubbard model . . . . .	3
Motivation for taking a negative $U$ . . . . .	3
Phase diagram . . . . .	3
BCS mean field theory on the Hubbard model . . . . .	3
Derivation for superfluid weight in this case? . . . . .	3
Do general multi-band BCS theory . . . . .	3
length scale/correlation length . . . . .	10
energy density of bosonic field? -> for comparison! . . . . .	11
Compare with Ising order, especially dependence on $T$ . . . . .	11
Compare with Ising order. Is that derived or postulated? . . . . .	11
Here: particle-current operator, especially for coherent state, connection with phase twist . . . . .	12
Finish up the discussion of Niklas paper . . . . .	12
Show GFs can be related to observables . . . . .	14

How to resolve ambiguity at borders of integral . . . . .	14
single-particle Matsubara GF . . . . .	15
equations of motion for Matsubara GF . . . . .	15
Short introduction to diagrams . . . . .	15
Self energy . . . . .	15
Dyson equation . . . . .	15
More general introduction into NG GFs, how they look like, what they describe etc. . . . .	15
Sources for these? . . . . .	15
How to get quasiparticle weight? . . . . .	15
See what is specific to this paper, see that I can derive that myself . . . .	17
Dont get it here . . . . .	17
Write up notes about quantum metric and superfluid weight . . . . .	17
Spin-orbit coupling, drop second spin index? . . . . .	22
Write review for Hubbard model on the honeycomb lattice . . . . .	23

# I SUPERCONDUCTIVITY

At the end of the 19th and the beginning of the 20th century, cooling technology made great progress. Liquifying gases, were able to reach temperatures as low as 4 K (the boiling point of Helium). Using that, SC was discovered in mercury in 1911 by Heike Onnes [1]. Superconductivity describes the phenomenon of the electrical resistance of a material suddenly dropping to zero below a critical temperature  $T_C$ . Discovery of Meissner effect, perfect expulsion of external magnetic fields in 1933 [2]. This started almost half a century of intensive theoretical research, which culminated in John Bardeen, Leon Cooper and J. Robert Schrieffer developing the microscopic theory now known as BCS theory [3]. 1986 and 1987: discovery of superconductivity with very high  $T_C$  found in cuprates [4, 5]. Cuprate superconductors are made up of layers of copper oxide and charge reservoirs in between. The specific charge reservoir layers determine the properties of the SC and varying them lead to a rich zoo of materials with high  $T_C$  [6].

Most current technical applications of superconductors rely on the fact that superconducting wires can carry much higher currents than ordinary wires and thus produce much larger magnetic fields. The largest commercial application to date is in magnetic resonance imaging, a medical technique using strong magnetic fields and field gradients [7]. Technical applications in research are much wider, ranging from strong superconducting magnets in the LHC [8] and other particle accelerators over detectors of single photons in astrophysics [9] to extremely sensitive measurement devices for magnetic fields [10, 11].

Theoretical description of HT-SC using BCS-theory based on an attractive interaction mediated by phonons could not explain high  $T_C$  superconductivity. For this reason called 'unconventional superconductors'. Some key experimental facts are established in high  $T_C$  SC: there is Cooper pairing, ordered normal state is very important for SC, phenomenon of 'Pseudogap' is defining [12].

Today, still many unanswered questions in unconventional SC [13].

Unconventional SC,  
what is the same,  
what is different,  
what makes it difficult to grasp

Open questions in  
unconventional SC,  
what is this citation?

Connection to my  
topic: flat bands,  
strong correlations

One interesting development in unconventional superconductivity is in twisted multilayer systems, first realized as twisted bilayer Graphene [caoUnconventionalSuperconduct

This chapter: introduction to the mean-field BCS theory in section I.1, supercurrent in section I.2, GL-theory in section I.3 and description of a method to treat certain aspects of strongly-correlated superconductivity from a microscopic standpoint away from the mean-field level in section I.4.

## I.1 BCS THEORY

Following [14, ch. 14].

Theoretical description of SC: 1957 by John Bardeen, his postdoc Leon Cooper and the graduate in the group, J. Robert Schrieffer [3]. Description is based on the fact, that the Fermi sea is unstable towards development of bound pairs under arbitrarily small attraction [15]. These bound electrons show bosonic behaviour and

Why supercurrent?

This model Hamiltonian

BCS hamiltonian,  
pairing

It can be connected to

Mean-field

The final element in this description was the origin of the attractive interaction between electrons, which Bardeen, Cooper and Schrieffer identified as a retarded electron-phonon interaction [3]. This so-called BCS-theory of superconductivity is very successful in explaining experimental results in many compounds, Surprisingly, it

Phonon interaction

Mean field level can  
already explain a lot

BCS-theory gave a microscopic explanation to a phenomenological description of superconductivity pioneered by Fritz London in 1937 [16]. This descriptions is based on a one-particle wave function  $\phi(x)$

Later, this one-particle wavefunction was identified as the order parameter in the developing GL-theory of phase transitions [17]. GL-theory is discussed in more detail in section I.3. This explains the Meissner effect and in turn the supercurrent.

### I.1.1 BCS THEORY AS A MEAN FIELD-THEORY (HUBBARD MODEL)

Hubbard model is the simplest model for interactions

[18]

[19]

Some relevance of the repulsive Hubbard model

## I.1.2 MULTI-BAND BCS THEORY ON THE HUBBARD MODEL

Motivation for taking a negative U

Define sublattice index

$$\alpha = 1, 2, 3 \quad (\text{I.1})$$

Phase diagram

with  $1 \cong \text{Gr}_1, 2 \cong \text{Gr}_2, 3 \cong \text{X}$ . Then we can write the non-interacting term as

$$H_0 = - \sum_{\langle i,j \rangle, \alpha, \beta, \sigma} [\mathbf{t}]_{i\alpha, j\beta} c_{i\alpha}^\dagger c_{j\beta} \quad (\text{I.2})$$

BCS mean field theory on the Hubbard model

with the matrix

$$\mathbf{t} = \begin{pmatrix} 0 & t_{\text{Gr}} & 0 \\ t_{\text{Gr}} & 0 & -V\delta_{ij} \\ 0 & -V\delta_{ij} & t_{\text{X}} \end{pmatrix} \quad (\text{I.3})$$

Derivation for superfluid weight in this case?

Add chemical potential:

$$-\mu \sum_{i\alpha\sigma} n_{i\alpha\sigma} \quad (\text{I.4})$$

Do general multi-band BCS theory

Also write the interaction part with  $\alpha$  (with changed signs compared to Niklas, to keep in line with papers about the attractive Hubbard model):

$$H_{\text{int}} = - \sum_{i\alpha} U_\alpha c_{i\alpha\uparrow}^\dagger c_{i\alpha\downarrow}^\dagger c_{i\alpha\downarrow} c_{i\alpha\uparrow} \quad (\text{I.5})$$

Fourier transformation:

$$H_{\text{int}} = - \frac{1}{N^2} \sum_{\alpha, \mathbf{k}_1, 2, 3, 4} U_\alpha e^{i(\mathbf{k}_1 + \mathbf{k}_4 - \mathbf{k}_1 - \mathbf{k}_3)r_{i\alpha}} c_{\mathbf{k}_1\alpha\uparrow}^\dagger c_{\mathbf{k}_3\alpha\downarrow}^\dagger c_{\mathbf{k}_2\alpha\downarrow} c_{\mathbf{k}_4\alpha\uparrow} \quad (\text{I.6})$$

Impose zero-momentum pairing:  $\mathbf{k}_1 + \mathbf{k}_3 = 0$  and  $\mathbf{k}_2 + \mathbf{k}_4 = 0$ :

$$H_{\text{int}} = - \sum_{\alpha, \mathbf{k}, \mathbf{k}'} U_\alpha c_{\mathbf{k}\alpha\uparrow}^\dagger c_{-\mathbf{k}\alpha\downarrow}^\dagger c_{-\mathbf{k}'\alpha\downarrow} c_{\mathbf{k}'\alpha\uparrow} \quad (\text{I.7})$$

Mean-field approximation:

$$H_{\text{int}} \approx \sum_{\alpha, \mathbf{k}} (\Delta_\alpha c_{\mathbf{k}\alpha\uparrow}^\dagger c_{-\mathbf{k}\alpha\downarrow}^\dagger + \Delta_\alpha^* c_{-\mathbf{k}\alpha\downarrow} c_{\mathbf{k}\alpha\uparrow}) \quad (\text{I.8})$$

with

$$\Delta_\alpha = -U_\alpha \sum_{\mathbf{k}'} \langle c_{-\mathbf{k}'\alpha\downarrow} c_{\mathbf{k}'\alpha\uparrow} \rangle \quad (\text{I.9})$$

$$\Delta_\alpha^* = -U_\alpha \sum_{\mathbf{k}'} \langle c_{\mathbf{k}'\alpha\uparrow}^\dagger c_{-\mathbf{k}'\alpha\downarrow}^\dagger \rangle \quad (\text{I.10})$$

This gives the BCS mean field Hamiltonian:

$$H_{BCS} = \sum_{\mathbf{k}\alpha\beta\sigma} [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} c_{\mathbf{k}\alpha\sigma}^\dagger c_{\mathbf{k}\beta\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{\mathbf{k}\alpha\sigma} + \sum_{\alpha,\mathbf{k}} (\Delta_\alpha c_{\mathbf{k}\alpha\uparrow}^\dagger c_{-\mathbf{k}\alpha\downarrow}^\dagger + \Delta_\alpha^* c_{-\mathbf{k}\alpha\downarrow} c_{\mathbf{k}\alpha\uparrow}) \quad (\text{I.11})$$

with Nambu spinor

$$\Psi_{\mathbf{k}} = \begin{pmatrix} c_{1,\mathbf{k}\uparrow} \\ c_{2,\mathbf{k}\uparrow} \\ c_{3,\mathbf{k}\uparrow} \\ c_{1,-\mathbf{k}\downarrow}^\dagger \\ c_{2,-\mathbf{k}\downarrow}^\dagger \\ c_{3,-\mathbf{k}\downarrow}^\dagger \end{pmatrix} \quad (\text{I.12})$$

we have:

$$H_{MF} = \sum_{\mathbf{k}} \Psi_{\mathbf{k}}^\dagger \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}} \quad (\text{I.13})$$

with

$$\mathcal{H}(\mathbf{k}) = \begin{pmatrix} H_{0,\uparrow}(\mathbf{k}) - \mu & \Delta \\ \Delta^\dagger & -H_{0,\downarrow}^*(-\mathbf{k}) + \mu \end{pmatrix} \quad (\text{I.14})$$

with  $H_{0,\sigma}$  being the F.T. of the kinetic term and  $\Delta = \text{diag}(\Delta_1, \Delta_2, \Delta_3)$ .

### I.1.3 BdG HAMILTONIAN IN BAND BASIS

Use transformation

$$c_{\mathbf{k}\alpha\sigma}^\dagger = \sum_n [\mathbf{G}]_{\alpha n}^* d_{n\mathbf{k}\sigma}^\dagger \quad (\text{I.15})$$

where the columns are made up of the eigenvectors of  $\mathbf{H}_{0,\sigma}$  for a given  $\mathbf{k}$ :

$$\mathbf{G} = (\mathbf{G}_1 \quad \mathbf{G}_2 \quad \mathbf{G}_3) \quad (\text{I.16})$$



with that:

$$\mathbf{G}_\sigma^\dagger(\mathbf{k})\mathbf{H}_{0,\sigma}(\mathbf{k})\mathbf{G}_\sigma(\mathbf{k}) = \begin{pmatrix} \epsilon_1 & 0 & 0 \\ 0 & \epsilon_2 & 0 \\ 0 & 0 & \epsilon_3 \end{pmatrix} \quad (\text{I.17})$$

So the kinetic part of the BdG Hamiltonian becomes:

$$\sum_{\mathbf{k}\alpha\beta\sigma} [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} \sum_n [\mathbf{G}(\mathbf{k})]_{\alpha n}^* d_{n\mathbf{k}\sigma}^\dagger \sum_m [\mathbf{G}(\mathbf{k})]_{\beta m} d_{m\mathbf{k}\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{I.18})$$

$$= \sum_{m\mathbf{k}\sigma} d_{n\mathbf{k}\sigma}^\dagger d_{m\mathbf{k}\sigma} \sum_{\alpha\beta} [\mathbf{G}(\mathbf{k})]_{\alpha n}^* [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} [\mathbf{G}(\mathbf{k})]_{\beta m} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{I.19})$$

$$= \sum_{m\mathbf{k}\sigma} d_{n\mathbf{k}\sigma}^\dagger d_{m\mathbf{k}\sigma} \epsilon_n \delta_{nm} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{I.20})$$

$$= \sum_{n\mathbf{k}\sigma} \epsilon_n d_{n\mathbf{k}\sigma}^\dagger d_{n\mathbf{k}\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{I.21})$$

$$=: \sum_{n\mathbf{k}\sigma} \tilde{\zeta}_{\mathbf{k}} d_{n\mathbf{k}\sigma}^\dagger d_{n\mathbf{k}\sigma} \quad (\text{I.22})$$

with  $\tilde{\zeta}_{\mathbf{k}} := \epsilon_{\mathbf{k}} - \mu$ . The pairing terms become:

$$\sum_{\mathbf{k}\alpha} \Delta_\alpha c_{\mathbf{k}\alpha\uparrow}^\dagger c_{-\mathbf{k}\alpha\downarrow}^\dagger = \sum_{\mathbf{k}\alpha} \Delta_\alpha \sum_n [\mathbf{G}_\uparrow(\mathbf{k})]_{\alpha n}^* d_{n\mathbf{k}\uparrow}^\dagger \sum_m [\mathbf{G}_\downarrow(-\mathbf{k})]_{\beta m}^* d_{m-\mathbf{k}\downarrow}^\dagger \quad (\text{I.23})$$

$$= \quad (\text{I.24})$$

So that:

$$\mathcal{H}(\mathbf{k}) = \begin{pmatrix} \epsilon_{\mathbf{k}} - \mu & G^\dagger \Delta G \\ G^\dagger \Delta^\dagger G & -\epsilon_{\mathbf{k}} + \mu \end{pmatrix} \quad (\text{I.25})$$

with

$$\epsilon_{\mathbf{k}} = \begin{pmatrix} \epsilon_1(\mathbf{k}) & 0 & 0 \\ 0 & \epsilon_2(\mathbf{k}) & 0 \\ 0 & 0 & \epsilon_3(\mathbf{k}) \end{pmatrix} \quad (\text{I.26})$$

Concrete example for transformation of gaps from orbital to band basis at

$\mathbf{K} = \frac{4\pi}{3a} \begin{pmatrix} 1 \\ 0 \end{pmatrix}$ . There, the non-interacting part becomes simply:

$$\mathcal{H}_0 = \begin{pmatrix} 0 & 0 & V \\ 0 & 0 & 0 \\ V & 0 & 3t_X \end{pmatrix} \quad (\text{I.27})$$

The eigenvalue problem can be solved e.g. via sympy:

$$G = \begin{pmatrix} \frac{-3t_X - \sqrt{4V^2 + 9t_X^2}}{\sqrt{4V^2 + (3t_X + \sqrt{4V^2 + 9t_X^2})^2}} & 0 & \frac{-3t_X + \sqrt{4V^2 + 9t_X^2}}{\sqrt{4V^2 + (3t_X - \sqrt{4V^2 + 9t_X^2})^2}} \\ 0 & 1 & 0 \\ \frac{2V}{\sqrt{4V^2 + (3t_X + \sqrt{4V^2 + 9t_X^2})^2}} & 0 & \frac{2V}{\sqrt{4V^2 + (3t_X - \sqrt{4V^2 + 9t_X^2})^2}} \end{pmatrix} \quad (\text{I.28})$$

So for  $V \rightarrow 0$ :

$$G = \begin{pmatrix} -1 & 0 & 0 \\ 0 & 1 & 0 \\ 0 & 0 & 1 \end{pmatrix} \quad (\text{I.29})$$

but for  $V > 0$ , there are off-diagonal elements, e.g.  $V = 0.1$ :

$$G = \begin{pmatrix} -0.7578 & 0 & 0.6526 \\ 0 & 1 & 0 \\ 0.6526 & 0 & 0.7578 \end{pmatrix} \quad (\text{I.30})$$

So the transformation of the gap from orbital to band space reads:

$$G^\dagger \Delta G = \begin{pmatrix} \frac{3\Delta_1 t_X - 3\Delta_3 t_X + (\Delta_1 + \Delta_3)\sqrt{4V^2 + 9t_X^2}}{2\sqrt{4V^2 + 9t_X^2}} & 0 & \frac{V(-\Delta_1 + \Delta_3)}{\sqrt{4V^2 + 9t_X^2}} \\ 0 & \Delta_2 & 0 \\ \frac{V(-\Delta_1 + \Delta_3)}{\sqrt{4V^2 + 9t_X^2}} & 0 & \frac{-3\Delta_1 t_X + 3\Delta_3 t_X + (\Delta_1 + \Delta_3)\sqrt{4V^2 + 9t_X^2}}{2\sqrt{4V^2 + 9t_X^2}} \end{pmatrix} \quad (\text{I.31})$$

So in particular there is no interband pairing for  $V \rightarrow 0$ :

$$G^\dagger \Delta G = \begin{pmatrix} \Delta_1 & 0 & 0 \\ 0 & \Delta_2 & 0 \\ 0 & 0 & \Delta_3 \end{pmatrix} \quad (\text{I.32})$$

But for  $V > 0$ , there is interband pairing (e.g.  $V = 0.1$ ):

$$G^\dagger \Delta G = \begin{pmatrix} 0.5742\Delta_1 + 0.4258\Delta_3 & 0 & -0.4945\Delta_1 + 0.4945\Delta_3 \\ 0 & \Delta_2 & 0 \\ -0.4945\Delta_1 + 0.4945\Delta_3 & 0 & 0.4258\Delta_1 + 0.5742\Delta_3 \end{pmatrix} \quad (\text{I.33})$$

### I.1.4 GRAND POTENTIAL

See [20], especially supplementary material, notes 1 and 3.

Mean-Field Hamiltonian (with the last two terms due to exchange of anticommuting fermion operators and the term quadratic in the expectation value from the mean-field decoupling respectively):

$$H_{MF} = \sum_{\mathbf{k}} \Psi_{\mathbf{k}}^{\dagger} \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}} + \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\dagger}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} \quad (\text{I.34})$$

The second term is the trace of the non-interacting Hamiltonian.

Thermodynamic grand potential (which at zero temperature is equivalent to the mean-field energy):

$$\Omega(T, \Delta) = -\frac{1}{\beta} \ln Z_{\Omega} = -\frac{1}{\beta} \ln \text{Tr}(e^{-\beta H_{MF}}) \quad (\text{I.35})$$

$$= \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\dagger}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} - \frac{1}{\beta} \ln \text{Tr}(e^{-\beta \Psi_{\mathbf{k}}^{\dagger} \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}}}) \quad (\text{I.36})$$

Zero temperature limit:

$$\Omega(\Delta) = \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\dagger}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} - \frac{1}{2} \sum_{\mathbf{k}} \text{Tr}(|\mathcal{H}_{\mathbf{k}}|) \quad (\text{I.37})$$

where a function of a matrix  $H$  (such as taking the absolute value of the BdG Hamiltonian  $\mathcal{H}_{\mathbf{k}}$ ) is defined for the diagonal matrix of eigenvalues  $D$  and the unitary matrix  $U$  that diagonalizes  $H$ :

$$f(H) = U f(D) U^{\dagger} \quad (\text{I.38})$$

The route to finding the value of the order parameter for a fixed interaction  $U$  is minimizing the grand potential with respect to  $\Delta$ .

## I.2 TRANSPORT IN SUPERCONDUCTORS: SUPERFLUID WEIGHT

### I.3 GINZBURG-LANDAU THEORY OF SUPERCONDUCTIVITY, PHASE TRANSITIONS AND BROKEN SYMMETRY

Following [14, ch. 11].

### I.3.1 ORDER PARAMETER CONCEPT

Landau theory: phase transitions (e.g. iron becomes magnetic, water freezes, superfluidity/superconductivity) are associated with the development of an order parameter when the temperature drops below the transition temperature  $T_C$ .

$$|\psi| = \begin{cases} 0, & T > T_C \\ |\psi_0| > 0, & T < T_C \end{cases} \quad (\text{I.39})$$

Landau theory does not need microscopic expression for order parameter, it provides coarse-grained description of the properties of matter. The order parameter description is good at length scales above  $\xi_0$ , the coherence length (e.g. size of Cooper pairs for SC).

### I.3.2 LANDAU THEORY

Basic idea of Landau theory: write free energy as function  $F[\psi]$  of the order parameter. Region of small  $\psi$ , expand free energy of many-body system as simple polynomial:

$$f_L = \frac{1}{V}F[\psi] = \frac{r}{2}\psi^2 + \frac{u}{4}\psi^4 \quad (\text{I.40})$$


Provided  $r$  and  $u$  are greater than 0: minimum of  $f_L[\psi]$  lies at  $\psi = 0$ . Landau theory assumes: at phase transition temperature  $r$  changes sign, so:

$$r = a(T - T_C) \quad (\text{I.41})$$

Minimum of free energy occurs for:

$$\psi = \begin{cases} 0 \\ \pm \sqrt{\frac{a(T_C - T)}{u}} \end{cases} \quad (\text{I.42})$$

Two minima for free energy function for  $T < T_C$ . With this, we can extract  $T_C$  from the knowledge of the dependence of  $|\psi|^2$  on  $T$  via a linear fit. This is only valid for an area near  $T_C$  (where Landau theory holds), but can be used to get  $T_C$  from microscopic theories.



**Figure I.1:** Mexican hat potential

Going from a one to a  $n$ -component order parameters, OP acquires directions and magnitude. Particularly important example: complex or two component order parameter in superfluids and superconductors:

$$\psi = \psi_1 + i\psi_2 = |\psi|e^{i\phi} \quad (\text{I.43})$$

The Landau free energy takes the form:

$$f[\psi] = r(\psi^* \psi) + \frac{u}{2}(\psi^* \psi)^2 \quad (\text{I.44})$$

As before:

$$r = a(T - T_C) \quad (\text{I.45})$$

Figure I.1 shows the Landau free energy as function of  $\psi$ .

Rotational symmetry, because free energy is independent of the global phase of the OP:

$$f[\psi] = f[e^{ia}\psi] \quad (\text{I.46})$$

In this 'Mexican hat' potential: order parameter can be rotated continuously from one broken-symmetry state to another. If we want the phase to be rigid, we need to introduce an There is a topological argument for the fact that the phase is rigid. This leads to Ginzburg-Landau theory. Will see later: well-defined phase is associated with persistent currents or superflow.

## I.3.3 GINZBURG-LANDAU THEORY I: ISING ORDER

Landau theory: energy cost of a uniform order parameter, more general theory needs to account for inhomogeneous order parameters, in which the amplitude varies or direction of order parameter is twisted  $\rightarrow$  GL theory. First: one-component, 'Ising' order parameter. GL introduces additional energy  $\delta f \propto |\Delta\psi|^2$ ,  $f_{GL}[\psi, \Delta\psi] = \frac{s}{2}|\Delta\psi|^2 + f_L[\psi(s)]$ , or in full:

$$f_{GL}[\psi, \Delta\psi, h] = \frac{s}{2}(\Delta\psi)^2 + \frac{r}{2}\psi^2 + \frac{u}{4}\psi^4 \quad (\text{I.47})$$

GL theory is only valid near critical point, where OP is small enough to permit leading-order expansion. Length scale introduced by the gradient term: correlation length

$$d \quad (\text{I.48})$$

length scale/correlation length

## I.3.4 GINZBURG-LANDAU THEORY II: COMPLEX ORDER AND SUPERFLOW

Now: GL theory of complex or two-component order parameters, so superfluids and superconductors. Heart of discussion: emergence of a 'macroscopic wave-function', where the microscopic field operators  $\hat{\psi}(x)$  acquire an expectation value:

$$\langle \hat{\psi}(x) \rangle = \psi(x) = |\psi(x)|e^{i\theta(x)} \quad (\text{I.49})$$

Reminder: Field operators are the real space representations of creation/annihilation operators. They can be thought of the superposition of all ways of creating a particle at position  $x$  via the basis coefficients.

Magnitude determines density of particles in the superfluid:

$$|\psi(x)|^2 = n_s(x) \quad (\text{I.50})$$

Density operator is

$$\hat{\rho} = \hat{\psi}(x)\hat{\psi}^\dagger(x) \quad (\text{I.51})$$

so expectation value of that is the formula above.

Twist/gradient of phase determines superfluid velocity:

$$\mathbf{v}_s(x) = \frac{\hbar}{m}\Delta\phi(x) \quad (\text{I.52})$$

We will derive this later in the chapter. Counterintuitive from quantum mechanics: GL suggested that  $\Phi(x)$  is a macroscopic manifestation of a macroscopic number of particles condensed into precisely the same quantum state. Emergent phenomenon, collective properties of matter not a-priori self-evident from microscopic physics.

GL free energy density for superfluid (with one added term in comparison to Landau energy):

$$f_{GL}[\psi, \Delta\psi] = \frac{\hbar^2}{2m} |\Delta\psi|^2 + r|\psi|^2 + \frac{u}{2} |\psi|^4 \quad (I.53)$$

Interpreted as energy density of a condensate of bosons in which the field operator behaves as a complex order parameter. Gives interpretation of gradient term as kinetic energy:

$$s|\Delta\psi|^2 = \frac{\hbar^2}{2m} \langle \Delta\hat{\psi}^\dagger \Delta\hat{\psi} \rangle \Rightarrow s = \frac{\hbar^2}{2m} \quad (I.54)$$

energy density of bosonic field? -> for comparison!

As in Ising order: correlation length/GL-coherence length governs characteristic range of amplitude fluctuations of the order parameter:

$$\xi = \sqrt{\frac{s}{|r|}} = \sqrt{\frac{\hbar^2}{2m|r|}} = \xi_0 (1 - \frac{T}{T_C})^{-\frac{1}{2}} \quad (I.55)$$

where  $\xi_0 = \xi(T=0) = \sqrt{\frac{\hbar^2}{2maT_C}}$  is the coherence length. Beyond this length: only phase fluctuations survive. Freeze out fluctuations in amplitude (no  $x$ -dependence in amplitude)  $\psi(x) = \sqrt{n_s} e^{i\phi(x)}$ , then  $\Delta\psi = i\Delta\phi\psi$  and  $|\Delta\psi|^2 = n_s(\Delta\phi)^2$ , dependency of kinetic energy on the phase twist is (bringing it into the form  $\frac{m}{2}v^2$ ):

$$\frac{\hbar^2 n_s}{2m} (\Delta\phi)^2 = \frac{mn_s}{2} (\frac{\hbar}{m} \Delta\phi)^2 \quad (I.56)$$

Compare with Ising order, especially dependence on  $T$

Compare with Ising order. Is that derived or postulated?

So twist of phase results in increase in kinetic energy, associated with a superfluid velocity:

$$\mathbf{v}_s = \frac{\hbar}{m} \Delta\phi \quad (I.57)$$

For interpretation of superfluid states: coherent states. These are eigenstates of the field operator

$$\hat{\psi}(x) |\psi\rangle = \psi(x) |\psi\rangle \quad (I.58)$$

and don't have a definite particle number. Importantly, this small uncertainty in particle number enables a high degree of precision in phase (which is the property of a condensate).

Phase rigidity and superflow: in GL theory, energy is sensitive to a twist of the phase. Substitute  $\psi = |\psi|e^{i\phi}$  into GL free energy, gradient term is:

$$\Delta\psi = (\Delta|\psi| + i\Delta\phi|\psi|)e^{i\phi} \quad (\text{I.59})$$

So:

$$f_{GL} = \frac{\hbar}{2m}|\psi|^2(\Delta\phi)^2 + \left[ \frac{\hbar}{2m}(\Delta|\psi|)^2 + r|\psi|^2 + \frac{u}{2}|\psi|^4 \right] \quad (\text{I.60})$$

The second term resembles GL functional for an Ising order parameter, describes energy cost of variations in the magnitude of the order parameter.

Here: particle-current operator, especially for coherent state, connection with phase twist

#### I.4 COHERENCE LENGTH AND PENETRATION DEPTH IN STRONGLY CORRELATED SUPERCONDUCTORS

Is that a good fit here?

From [21].

In most materials: Cooper pairs do not carry finite center-of-mass momentum. In presence of e.g. external fields or magnetism: SC states with FMP might arise.

Theory/procedure in the paper: enforce FMP states via constraints on pair-center-of-mass momentum  $\mathbf{q}$ , access characteristic length scales  $\xi_0, \lambda_L$  through analysis of the momentum and temperature-dependent OP. Constrain for FF-type pairing:

$$\psi_{\mathbf{q}}(\mathbf{r}) = |\psi_{\mathbf{q}}|e^{i\mathbf{q}\cdot\mathbf{r}} \quad (\text{I.61})$$

Finish up the discussion of Niklas paper



## II DYNAMICAL MEAN-FIELD THEORY

### II.1 GREEN'S FUNCTION FORMALISM

Following [22]

Green's functions: method to encode influence of many-body effects on propagation of particles in a system.

Have different kinds of Green's functions, for example the retarded Green's function:

$$G^R(\mathbf{r}\sigma t, \mathbf{r}'\sigma' t') = -i\Theta(t - t') \langle \{c_{\mathbf{r}\sigma}(t), c_{\mathbf{r}'\sigma'}^\dagger(t')\} \rangle \quad (\text{II.1})$$

They give the amplitude of a particle inserted at point  $\mathbf{r}'$  at time  $t'$  to propagate to position  $\mathbf{r}$  at time  $t$ . For time-independent Hamiltonians and systems in equilibrium, the GFs only depend on time differences:

$$G^R(\mathbf{r}\sigma t, \mathbf{r}'\sigma' t') = G^R(\mathbf{r}\sigma, \mathbf{r}'\sigma', t - t') \quad (\text{II.2})$$

So we can take  $t' = 0$  and consider  $t$  as the only free variable:

$$G^R(\mathbf{r}\sigma, \mathbf{r}'\sigma', t) = -i\Theta(t) \langle \{c_{\mathbf{r}\sigma}(t), c_{\mathbf{r}'\sigma'}^\dagger(0)\} \rangle \quad (\text{II.3})$$

In a translation invariant system: can use  $\mathbf{k}$  as a natural basis set:

$$G^R(\mathbf{k}, \sigma, \sigma' t) = -i\Theta(t) \langle \{c_{\mathbf{k}\sigma}(t), c_{\mathbf{k}\sigma'}^\dagger(0)\} \rangle \quad (\text{II.4})$$

Define Fourier-transform:

$$G^R(\mathbf{k}, \sigma, \sigma', \omega) = \int_{-\infty}^{\infty} dt G^R(\mathbf{k}, \sigma, \sigma' t) \quad (\text{II.5})$$

Can define the spectral function from this:

$$A(\mathbf{k}\sigma, \omega) = -2\Im G^R(\mathbf{k}\sigma, \omega) \quad (\text{II.6})$$

Looking at the diagonal elements of  $G^R$  here. The spectral function can be thought of as the energy resolution of a particle with energy  $\omega$ . This mean, for non-interacting systems, the spectral function is a delta-function around the single-particle energies:

$$A_0(\mathbf{k}\sigma, \omega) = 2\pi\delta(\omega - \epsilon_{\mathbf{k}\sigma}) \quad (\text{II.7})$$

Show GFs can be related to observables

For interacting systems this is not true, but  $A$  can still be peaked.

Mathematical technique to calculate retarded GFs involves defining GFs on imaginary times  $\tau$ :

$$t \rightarrow -i\tau \quad (\text{II.8})$$

where  $\tau$  is real and has the dimension time. This enables the simultaneous expansion of exponential  $e^{-\beta H}$  coming from the thermodynamic average and  $e^{-iHt}$  coming from the time evolution of operators.

Define imaginary time/Matsubara GF  $C_{AB}(\tau, 0)$ :

$$C_{AB}(\tau, 0) = -\langle T_\tau(A(\tau)B(0)) \rangle \quad (\text{II.9})$$

with time-ordering operator in imaginary time:

$$T_\tau(A(\tau)B(\tau')) = \Theta(\tau - \tau')A(\tau)B(\tau') \pm \Theta(\tau' - \tau)B(\tau')A(\tau) \quad (\text{II.10})$$

so that operators with later 'times' go to the left.

Can prove from properties of Matsubara GF, that they are only defined for

$$-\beta < \tau < \beta \quad (\text{II.11})$$

Due to this, the Fourier transform of the Matsubara GF is defined on discrete values:

$$C_{AB}(i\omega_n) = \int_0^\beta d\tau \quad (\text{II.12})$$

with fermionic/bosonic Matsubara frequencies

$$\omega_n = \begin{cases} \frac{2n\pi}{\beta} & \text{for bosons} \\ \frac{(2n+1)\pi}{\beta} & \text{for fermions} \end{cases} \quad (\text{II.13})$$

How to resolve ambiguity at borders of integral

It turns out that Matsubara GFs and retarded GFs can be generated from a common function  $C_{AB}(z)$  that is defined on the entire complex plane except for the real axis. So we can get the retarded GF  $C_{AB}^R(\omega)$  by analytic continuation:

$$C_{AB}^R(\omega) = C_{AB}(i\omega_n \rightarrow \omega + i\eta) \quad (\text{II.14})$$

So in particular the extrapolation of the Matsubara GF to zero is proportional to the density of states at the chemical potential. Gapped: density is zero (Matsubara GF goes to 0), metal: density is finite (Matsubara GF goes to finite value) [22, p. 8.3.4].

## II.2 PERTURBATION THEORY, DYSON EQUATION

Dyson equation:

$$G_{\sigma}(\mathbf{k}, i\omega_n) = \frac{G_{\sigma}^0(\mathbf{k}, i\omega_n)}{1 - G_{\sigma}^0(\mathbf{k}, i\omega_n) \Sigma_{\sigma}(\mathbf{k}, i\omega_n)} = \frac{1}{i\omega_n - \tilde{\xi}_{\mathbf{k} - \Sigma_{\sigma}(\mathbf{k}, i\omega_n)}} \quad (\text{II.15})$$

## II.3 NAMBU-GORKOV GF

Introduction following [14, ch. 14.7]

Order parameter can be chosen as the anomalous GF:

$$\Psi = F^{\text{loc}}(\tau = 0^-) \quad (\text{II.16})$$

or the superconducting gap

$$\Delta = Z \Sigma^{\text{AN}} \quad (\text{II.17})$$

that can be calculated from the anomalous self-energy  $\Sigma^{\text{AN}}$  and quasiparticle weight  $Z$

## II.4 DMFT

Following [23].

single-particle Matsubara GF

equations of motion for Matsubara GF

Short introduction to diagrams

Self energy

Dyson equation

More general introduction into NG GFs, how they look like, what they describe etc.

Sources for these?

How to get quasiparticle weight?

Most general non-interacting electronic Hamiltonian in second quantization:

$$H_0 = \sum_{i,j,\sigma} \quad (\text{II.18})$$

with lattice coordinates  $i, j$  and spin  $\sigma$ .

One particle Green's function (many-body object, coming from the Hubbard model):

$$G(\mathbf{k}, i\omega_n) = \frac{1}{i\omega_n + \mu - \epsilon_{\mathbf{k}} - \Sigma(\mathbf{k}, i\omega_n)} \quad (\text{II.19})$$

with the self energy  $\Sigma(i\omega_n)$  coming from the solution of the effect on-site problem:

The Dyson equation

$$G(\mathbf{k}, i\omega_n) = (G_0(\mathbf{k}, i\omega_n) - \Sigma(\mathbf{k}, i\omega_n))^{-1} \quad (\text{II.20})$$

relates the non-interacting Greens function  $G_0(\mathbf{k}, i\omega_n)$  and the fully-interacting Greens function  $G(\mathbf{k}, i\omega_n)$  (inversion of a matrix!).

### III QUANTUM METRIC

First formulated in [24]

Following Cheng - a pedagogical Introduction

Parameter dependent Hamiltonian  $\{H(\lambda)\}$ , smooth dependence on parameter  $\lambda = (\lambda_1, \lambda_2, \dots) \in \mathcal{M}$  (base manifold)

Hamiltonian acts on parametrized Hilbert space  $\mathcal{H}(\lambda)$

Eigenenergies  $E_n(\lambda)$ , eigenstates  $|\phi_n(\lambda)\rangle$

System state  $|\psi(\lambda)\rangle$  is linear combination of  $|\phi_n(\lambda)\rangle$  at every point in  $\mathcal{M}$

Infinitesimal variation of the parameter  $d\lambda$  :

$$ds^2 = \|\psi(\lambda+d\lambda) - \psi(\lambda)\|^2 = \langle \delta\psi | \delta\psi \rangle = \langle \partial_\mu \psi | \partial_\nu \psi \rangle d\lambda^\mu d\lambda^\nu = (\gamma_{\mu\nu} + i\sigma_{\mu\nu}) d\lambda^\mu d\lambda^\nu \quad (\text{III.1})$$

Last part is splitting up into real and imaginary part

See what is specific to this paper, see that I can derive that myself

Dont get it here

#### III.1 QUANTUM METRIC AND SUPERFLUID WEIGHT

Write up notes about quantum metric and superfluid weight



## IV NONINTERACTING EG-X MODEL AND STRUCTURE

### IV.1 LATTICE STRUCTURE OF GRAPHENE

Structure of honeycomb lattice following [25].

Monolayer graphene forms a hexagonal lattice.

Primitive lattice vectors of the hexagonal lattice:

$$\mathbf{a}_1 = \frac{a}{2} \begin{pmatrix} 1 \\ \sqrt{3} \end{pmatrix} \quad (\text{IV.1})$$

$$\mathbf{a}_2 = \frac{a}{2} \begin{pmatrix} 1 \\ -\sqrt{3} \end{pmatrix} \quad (\text{IV.2})$$

with lattice constant  $a \approx 2.46 \text{ \AA}$  (distance between unit cells). Have

$$a = \sqrt{3}a_0 \quad (\text{IV.3})$$


with the nearest-neighbour distance  $a_0$ .

Vectors to the nearest-neighbor  $B_i$  ( $i = 1, 2, 3$ ) atoms from atom  $A$ :

$$\delta_{AB,1} = \begin{pmatrix} 0 \\ \frac{a}{\sqrt{3}} \end{pmatrix}, \delta_{AB,2} = \begin{pmatrix} \frac{a}{2} \\ -\frac{a}{2\sqrt{3}} \end{pmatrix}, \delta_{AB,3} = \begin{pmatrix} -\frac{a}{2} \\ -\frac{a}{2\sqrt{3}} \end{pmatrix} \quad (\text{IV.4})$$

Vectors to the nearest-neighbor  $A_i$  ( $i = 1, 2, 3$ ) atoms from atom  $B$ :

$$\delta_{BA,1} = \begin{pmatrix} 0 \\ -\frac{a}{\sqrt{3}} \end{pmatrix}, \delta_{BA,2} = \begin{pmatrix} \frac{a}{2} \\ \frac{a}{2\sqrt{3}} \end{pmatrix}, \delta_{BA,3} = \begin{pmatrix} -\frac{a}{2} \\ \frac{a}{2\sqrt{3}} \end{pmatrix} \quad (\text{IV.5})$$



**Figure IV.1:** Graphene lattice structure

The vectors between the Graphene A atom and the six neighbours on the same sub lattice can be found by rotating  $\mathbf{a}_1$  six times by  $1/6 * 2\pi = \pi/3$ :

$$\delta_{AA,1} = \mathbf{a}_1 = \frac{a}{2} \begin{pmatrix} 1 \\ \sqrt{3} \end{pmatrix} = a \begin{pmatrix} \frac{1}{2} \\ \frac{\sqrt{3}}{2} \end{pmatrix} = a \begin{pmatrix} \sin(\frac{\pi}{6}) \\ \cos(\frac{\pi}{6}) \end{pmatrix} \quad (\text{IV.6})$$

$$\delta_{AA,2} = a \begin{pmatrix} \sin(\frac{3\pi}{6}) \\ \cos(\frac{3\pi}{6}) \end{pmatrix} = a \begin{pmatrix} 1 \\ 0 \end{pmatrix} \quad (\text{IV.7})$$


$$\delta_{AA,3} = a \begin{pmatrix} \sin(\frac{5\pi}{6}) \\ \cos(\frac{5\pi}{6}) \end{pmatrix} = a \begin{pmatrix} \frac{1}{2} \\ -\frac{\sqrt{3}}{2} \end{pmatrix} \quad (\text{IV.8})$$

$$\delta_{AA,4} = a \begin{pmatrix} \sin(\frac{7\pi}{6}) \\ \cos(\frac{7\pi}{6}) \end{pmatrix} = a \begin{pmatrix} -\frac{1}{2} \\ -\frac{\sqrt{3}}{2} \end{pmatrix} \quad (\text{IV.9})$$

$$\delta_{AA,5} = a \begin{pmatrix} \sin(\frac{9\pi}{6}) \\ \cos(\frac{9\pi}{6}) \end{pmatrix} = a \begin{pmatrix} -1 \\ 0 \end{pmatrix} \quad (\text{IV.10})$$

$$\delta_{AA,6} = a \begin{pmatrix} \sin(\frac{11\pi}{6}) \\ \cos(\frac{11\pi}{6}) \end{pmatrix} = a \begin{pmatrix} -\frac{1}{2} \\ \frac{\sqrt{3}}{2} \end{pmatrix} \quad (\text{IV.11})$$





**Figure IV.2:** *Graphene Brillouin Zone*

The primitive reciprocal lattice vectors  $\mathbf{b}_1, \mathbf{b}_2$  fulfill

$$\mathbf{a}_1 \cdot \mathbf{b}_1 = \mathbf{a}_2 \cdot \mathbf{b}_2 = 2\pi \quad (\text{IV.12})$$

$$\mathbf{a}_1 \cdot \mathbf{b}_2 = \mathbf{a}_2 \cdot \mathbf{b}_1 = 0, \quad (\text{IV.13})$$

so we have:

$$\mathbf{b}_1 = \frac{2\pi}{a} \begin{pmatrix} 1 \\ \frac{1}{\sqrt{3}} \end{pmatrix} \quad (\text{IV.14})$$

$$\mathbf{b}_2 = \frac{2\pi}{a} \begin{pmatrix} 1 \\ -\frac{1}{\sqrt{3}} \end{pmatrix} \quad (\text{IV.15})$$

Points of high symmetry in the Brillouin zone are:


$$\Gamma = \begin{pmatrix} 0 \\ 0 \end{pmatrix} \quad (\text{IV.16})$$

$$\text{M} = \frac{\pi}{a} \begin{pmatrix} 1 \\ \frac{1}{\sqrt{3}} \end{pmatrix} \quad (\text{IV.17})$$

$$\text{K} = \frac{4\pi}{3a} \begin{pmatrix} 1 \\ 0 \end{pmatrix} \quad (\text{IV.18})$$

## IV.2 EG-X MODEL

Graphene lattice and a site X. Real-life motivation: layer of graphene on top



**Figure IV.3:** *EG-X model*

of a substrate of another material (which provides the additional X atoms). There is no spin-orbit coupling considered in the model (but when according to Niklas: when mapping to substrates Sn or Pb, it could be necessary (but does not the qualitative result?)).

Spin-orbit coupling,  
drop second spin  
index?

Without interaction :

$$H_0 = -t_X \sum_{\langle ij \rangle, \sigma \sigma'} d_{i, \sigma}^\dagger d_{j, \sigma'} + \text{h.c.} - t_{\text{Gr}} \sum_{\langle ij \rangle, \sigma \sigma'} \left( c_{i, \sigma}^{(A), \dagger} c_{j, \sigma'}^{(B)} + c_{j, \sigma'}^{(B), \dagger} c_{i, \sigma}^{(A)} + \text{h.c.} \right) \quad (\text{IV.19})$$

$$+ V \sum_{i, \sigma \sigma'} \left( d_{i, \sigma}^\dagger c_{i, \sigma'}^{(A)} + c_{i, \sigma}^{(A), \dagger} d_{i, \sigma'} \right) \quad (\text{IV.20})$$

with:

- $d$  operators on the X atom
- $c^{(\epsilon)}$  operators on the graphene site ( $\epsilon = A, B$ )
- $t_X$  NN hopping for X
- $t_{\text{Gr}}$  NN hopping of Gr
- $V$  hybridization between X and Graphene B sites

We can also introduce an onsite Hubbard interaction:

$$H_{\text{int}} = U_X \sum_i d_{i, \uparrow}^\dagger d_{i, \downarrow}^\dagger d_{i, \downarrow} d_{i, \uparrow} + U_{\text{Gr}} \sum_{i, \epsilon=A, B} c_{i, \uparrow}^{(\epsilon), \dagger} c_{i, \downarrow}^{(\epsilon), \dagger} c_{i, \downarrow}^{(\epsilon)} c_{i, \uparrow}^{(\epsilon)} \quad (\text{IV.21})$$

#### IV.2.1 REVIEW: HUBBARD MODEL ON THE HONEYCOMB LATTICE

Write review for Hubbard model on the honeycomb lattice

#### IV.2.2 BAND STRUCTURE OF THE NON-INTERACTING EG-X MODEL

To treat eq. IV.20, we first write out the sums over nearest neighbours  $\langle i, j \rangle$  explicitly, writing  $\delta_X, \delta_\epsilon$  ( $\epsilon = A, B$ ) for the connections to the nearest neighbours of the X atoms and Graphene A, B sites. Doing the calculation for the example of the X atoms:

$$-t_X \sum_{\langle ij \rangle, \sigma \sigma'} (d_{i, \sigma}^\dagger d_{j, \sigma'} + d_{j, \sigma}^\dagger d_{i, \sigma'}) \quad (\text{IV.22})$$

$$= -\frac{t_X}{2} \sum_{i, \sigma, \sigma'} \sum_{\delta_X} d_{i, \sigma}^\dagger d_{i+\delta_X, \sigma'} - \frac{t_X}{2} \sum_{j, \sigma, \sigma'} \sum_{\delta_X} d_{j, \sigma}^\dagger d_{j+\delta_X, \sigma'} \quad (\text{IV.23})$$

$$= -t_X \sum_{i, \sigma, \sigma'} \sum_{\delta_X} d_{i, \sigma}^\dagger d_{i+\delta_X, \sigma'} \quad (\text{IV.24})$$

(The factor  $1/2$  is to account for double counting when going to the sum over all lattice sites  $i$ )

Now we can input the discrete Fourier transform (for both graphene and X operators) into eq. IV.24

$$c_i = \frac{1}{\sqrt{N}} \sum_{\mathbf{k}} e^{i\mathbf{k}\mathbf{r}_i} c_{\mathbf{k}} \quad (\text{IV.25})$$

$$c_i^\dagger = \frac{1}{\sqrt{N}} \sum_{\mathbf{k}} e^{-i\mathbf{k}\mathbf{r}_i} c_{\mathbf{k}}^\dagger \quad (\text{IV.26})$$

with the completeness relation:

$$\sum_i e^{i\mathbf{k}\mathbf{r}_i} e^{-i\mathbf{k}'\mathbf{r}_i} = N\delta_{\mathbf{k},\mathbf{k}'} . \quad (\text{IV.27})$$

We get:

$$-t_X \frac{1}{N} \sum_{i,\sigma,\sigma'} \sum_{\delta_X} d_{i,\sigma}^\dagger d_{i+\delta_X,\sigma'} = -t_X \frac{1}{N} \sum_{i,\sigma,\sigma'} \sum_{\delta_X} \sum_{\mathbf{k},\mathbf{k}'} e^{-i\mathbf{k}\mathbf{r}_i} d_{\mathbf{k},\sigma}^\dagger e^{i\mathbf{k}'\mathbf{r}_i} e^{i\mathbf{k}'\delta_X} d_{\mathbf{k}',\sigma'} \quad (\text{IV.28})$$

$$= -t_X \frac{1}{N} \sum_{\mathbf{k},\mathbf{k}',\sigma,\sigma'} \sum_{\delta_X} d_{\mathbf{k},\sigma}^\dagger e^{i\mathbf{k}'\delta_X} d_{\mathbf{k}',\sigma'} \sum_i e^{-i\mathbf{k}\mathbf{r}_i} e^{i\mathbf{k}'\mathbf{r}_i} \quad (\text{IV.29})$$

$$= -t_X \frac{1}{N} \sum_{\mathbf{k},\mathbf{k}',\sigma,\sigma'} \sum_{\delta_X} d_{\mathbf{k},\sigma}^\dagger e^{i\mathbf{k}'\delta_X} d_{\mathbf{k}',\sigma'} N\delta_{\mathbf{k},\mathbf{k}'} \quad (\text{IV.30})$$

$$= -t_X \sum_{\mathbf{k},\sigma,\sigma'} d_{\mathbf{k},\sigma}^\dagger d_{\mathbf{k},\sigma'} \sum_{\delta_X} e^{i\mathbf{k}\delta_X} \quad (\text{IV.31})$$

The nearest neighbours for X atoms are the vectors  $\delta_{AA,i}$  from section IV.1. With that, we can calculate:

$$f_X(\mathbf{k}) = -t_X \sum_{\delta_X} e^{i\mathbf{k}\delta_X} \quad (\text{IV.32})$$

$$= -t_X \left( e^{ia(\frac{k_x}{2} + \frac{\sqrt{3}k_y}{2})} + e^{iak_x} + e^{ia(\frac{k_x}{2} - \frac{\sqrt{3}k_y}{2})} \right) \quad (\text{IV.33})$$

$$+ e^{ia(-\frac{k_x}{2} - \frac{\sqrt{3}k_y}{2})} + e^{-iak_x} + e^{ia(-\frac{k_x}{2} + \frac{\sqrt{3}k_y}{2})} \right) \quad (\text{IV.34})$$

$$= -t_X \left( 2 \cos(ak_x) + 2e^{ia\frac{\sqrt{3}k_y}{2}} \cos(\frac{a}{2}k_x) + 2e^{-ia\frac{\sqrt{3}k_y}{2}} \cos(\frac{a}{2}k_x) \right) \quad (\text{IV.35})$$

$$= -2t_X \left( \cos(ak_x) + 2 \cos(\frac{a}{2}k_x) \cos(\sqrt{3}\frac{a}{2}k_y) \right) \quad (\text{IV.36})$$

We can do the same for the hopping between Graphene sites, for example :

$$-t_{Gr} \sum_{\langle ij \rangle, \sigma \sigma'} c_{i,\sigma}^{(A)\dagger} c_{j,\sigma'}^{(B)} = -t_{Gr} \sum_{i,\sigma \sigma'} \sum_{\delta_{AB}} c_{i,\sigma}^{(A)\dagger} c_{i+\delta_{AB},\sigma'}^{(B)} \quad (\text{IV.37})$$

$$= -t_{Gr} \sum_{\mathbf{k}, \sigma, \sigma'} c_{\mathbf{k},\sigma}^{(A)\dagger} c_{\mathbf{k},\sigma'}^{(B)} \sum_{\delta_{AB}} e^{i\mathbf{k}\delta_{AB}} \quad (\text{IV.38})$$

We note

$$\sum_{\delta_{AB}} e^{i\mathbf{k}\delta_{AB}} = \left( \sum_{\delta_{BA}} e^{i\mathbf{k}\delta_{BA}} \right)^* = \sum_{\delta_{BA}} e^{-i\mathbf{k}\delta_{BA}} \quad (\text{IV.39})$$


and calculate

$$f_{Gr} = -t_{Gr} \sum_{\delta_{AB}} e^{i\mathbf{k}\delta_{AB}} \quad (\text{IV.40})$$

$$= -t_{Gr} \left( e^{i\frac{a}{\sqrt{3}}k_y} + e^{i\frac{a}{2\sqrt{3}}(\sqrt{3}k_x - k_y)} + e^{i\frac{a}{2\sqrt{3}}(-\sqrt{3}k_x - k_y)} \right) \quad (\text{IV.41})$$

$$= -t_{Gr} \left( e^{i\frac{a}{\sqrt{3}}k_y} + e^{-i\frac{a}{2\sqrt{3}}k_y} \left( e^{i\frac{a}{2}k_x} + e^{-i\frac{a}{2}k_x} \right) \right) \quad (\text{IV.42})$$

$$= -t_{Gr} \left( e^{i\frac{a}{\sqrt{3}}k_y} + 2e^{-i\frac{a}{2\sqrt{3}}k_y} \cos(\frac{a}{2}k_x) \right) \quad (\text{IV.43})$$



**Figure IV.4:** Bands of the non-interacting EG-X model. All the bands are spin-degenerate.

All together, we get:

$$H_0 = \sum_{\mathbf{k}, \sigma, \sigma'} \begin{pmatrix} c_{\mathbf{k}, \sigma}^{A, \dagger} & c_{\mathbf{k}, \sigma}^{B, \dagger} & d_{\mathbf{k}, \sigma}^{\dagger} \end{pmatrix} \begin{pmatrix} 0 & f_{Gr} & V \\ f_{Gr}^* & 0 & 0 \\ V & 0 & f_X \end{pmatrix} \begin{pmatrix} c_{\mathbf{k}, \sigma}^A \\ c_{\mathbf{k}, \sigma}^B \\ d_{\mathbf{k}, \sigma} \end{pmatrix} \quad (\text{IV.44})$$

The band structure for the non-interacting EG-X model is easily obtained by diagonalising the matrix in eq. IV.44. This was done in fig. IV.4.

Values used for calculation:

- $a_0 = 1$
- $t_{Gr} = 1$
- $t_X = 0.01$

$V$  is the control parameter. (According to Niklas), a range from  $V = 0.1$  to  $V = 2$  can be mapped onto materials in experiment.

# V EG-X MODEL WITH INTERACTIONS

## V.1 BdG

### V.1.1 BdG HAMILTONIAN

Define sublattice index

$$\alpha = 1, 2, 3 \quad (\text{V.1})$$

with  $1 \cong \text{Gr}_1, 2 \cong \text{Gr}_2, 3 \cong \text{X}$ . Then we can write the non-interacting term as

$$H_0 = - \sum_{\langle i,j \rangle, \alpha, \beta, \sigma} [\mathbf{t}]_{i\alpha, j\beta} c_{i\alpha}^\dagger c_{j\beta} \quad (\text{V.2})$$

with the matrix

$$\mathbf{t} = \begin{pmatrix} 0 & t_{\text{Gr}} & 0 \\ t_{\text{Gr}} & 0 & -V\delta_{ij} \\ 0 & -V\delta_{ij} & t_{\text{X}} \end{pmatrix} \quad (\text{V.3})$$

Add chemical potential:

$$-\mu \sum_{i\alpha\sigma} n_{i\alpha\sigma} \quad (\text{V.4})$$

Also write the interaction part with  $\alpha$  (with changed signs compared to Niklas, to keep in line with papers about the attractive Hubbard model):

$$H_{int} = - \sum_{i\alpha} U_\alpha c_{i\alpha\uparrow}^\dagger c_{i\alpha\downarrow}^\dagger c_{i\alpha\downarrow} c_{i\alpha\uparrow} \quad (\text{V.5})$$

Fourier transformation:

$$H_{int} = -\frac{1}{N^2} \sum_{\alpha, \mathbf{k}_1, 2, 3, 4} U_\alpha e^{i(\mathbf{k}_1 + \mathbf{k}_4 - \mathbf{k}_1 - \mathbf{k}_3)r_{i\alpha}} c_{\mathbf{k}_1\alpha\uparrow}^\dagger c_{\mathbf{k}_3\alpha\downarrow}^\dagger c_{\mathbf{k}_2\alpha\downarrow} c_{\mathbf{k}_4\alpha\uparrow} \quad (\text{V.6})$$

Impose zero-momentum pairing:  $\mathbf{k}_1 + \mathbf{k}_3 = 0$  and  $\mathbf{k}_2 + \mathbf{k}_4 = 0$ :

$$H_{int} = - \sum_{\alpha, \mathbf{k}, \mathbf{k}'} U_{\alpha} c_{\mathbf{k}\alpha\uparrow}^{\dagger} c_{-\mathbf{k}\alpha\downarrow}^{\dagger} c_{-\mathbf{k}'\alpha\downarrow} c_{\mathbf{k}'\alpha\uparrow} \quad (\text{V.7})$$

Mean-field approximation:

$$H_{int} \approx \sum_{\alpha, \mathbf{k}} (\Delta_{\alpha} c_{\mathbf{k}\alpha\uparrow}^{\dagger} c_{-\mathbf{k}\alpha\downarrow}^{\dagger} + \Delta_{\alpha}^{*} c_{-\mathbf{k}\alpha\downarrow} c_{\mathbf{k}\alpha\uparrow}) \quad (\text{V.8})$$

with

$$\Delta_{\alpha} = -U_{\alpha} \sum_{\mathbf{k}'} \langle c_{-\mathbf{k}'\alpha\downarrow} c_{\mathbf{k}'\alpha\uparrow} \rangle \quad (\text{V.9})$$

$$\Delta_{\alpha}^{*} = -U_{\alpha} \sum_{\mathbf{k}'} \langle c_{\mathbf{k}'\alpha\uparrow}^{\dagger} c_{-\mathbf{k}'\alpha\downarrow}^{\dagger} \rangle \quad (\text{V.10})$$

This gives the BCS mean field Hamiltonian:

$$H_{BCS} = \sum_{\mathbf{k}\alpha\beta\sigma} [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} c_{\mathbf{k}\alpha\sigma}^{\dagger} c_{\mathbf{k}\beta\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{\mathbf{k}\alpha\sigma} + \sum_{\alpha, \mathbf{k}} (\Delta_{\alpha} c_{\mathbf{k}\alpha\uparrow}^{\dagger} c_{-\mathbf{k}\alpha\downarrow}^{\dagger} + \Delta_{\alpha}^{*} c_{-\mathbf{k}\alpha\downarrow} c_{\mathbf{k}\alpha\uparrow}) \quad (\text{V.11})$$

with Nambu spinor

$$\Psi_{\mathbf{k}} = \begin{pmatrix} c_{1,\mathbf{k}\uparrow} \\ c_{2,\mathbf{k}\uparrow} \\ c_{3,\mathbf{k}\uparrow} \\ c_{1,-\mathbf{k}\downarrow}^{\dagger} \\ c_{2,-\mathbf{k}\downarrow}^{\dagger} \\ c_{3,-\mathbf{k}\downarrow}^{\dagger} \end{pmatrix} \quad (\text{V.12})$$

we have:

$$H_{MF} = \sum_{\mathbf{k}} \Psi_{\mathbf{k}}^{\dagger} \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}} \quad (\text{V.13})$$

with

$$\mathcal{H}(\mathbf{k}) = \begin{pmatrix} H_{0,\uparrow}(\mathbf{k}) - \mu & \Delta \\ \Delta^{\dagger} & -H_{0,\downarrow}^{*}(-\mathbf{k}) + \mu \end{pmatrix} \quad (\text{V.14})$$

with  $H_{0,\sigma}$  being the F.T. of the kinetic term and  $\Delta = \text{diag}(\Delta_1, \Delta_2, \Delta_3)$ .



### V.1.2 DERIVATIVE OF THE NORMAL STATE HAMILTONIAN

For calculation of quantum metric: need derivative of the BdG and normal state Hamiltonian w.r.t.  $k_x$  and  $k_y$ .

$$H_0 = \begin{pmatrix} 0 & f_{\text{Gr}}(\mathbf{k}) & V \\ f_{\text{Gr}}^*(\mathbf{k}) & 0 & 0 \\ V & 0 & f_{\text{X}}(\mathbf{k}) \end{pmatrix} \quad (\text{V.15})$$

So need derivatives of  $f_{\text{Gr}}$  and  $f_{\text{X}}$ :

$$\partial_{k_x} f_{\text{Gr}}(\mathbf{k}) = -t_{\text{Gr}} 2e^{-i\frac{a}{2\sqrt{3}k_y}} \left( -\frac{a}{2} \sin\left(\frac{a}{2}k_x\right) \right) = t_{\text{Gr}} e^{-i\frac{a}{2\sqrt{3}k_y}} \sin\left(\frac{a}{2}k_x\right) \quad (\text{V.16})$$

$$\partial_{k_y} f_{\text{Gr}}(\mathbf{k}) = -t_{\text{Gr}} \left( i\frac{a}{\sqrt{3}} e^{i\frac{a}{\sqrt{3}k_y}} - 2i\frac{a}{2\sqrt{3}} e^{-i\frac{a}{2\sqrt{3}k_y}} \cos\left(\frac{a}{2}k_x\right) \right) \quad (\text{V.17})$$

$$= -t_{\text{Gr}} i\frac{a}{\sqrt{3}} \left( e^{i\frac{a}{\sqrt{3}k_y}} - e^{-i\frac{a}{2\sqrt{3}k_y}} \cos\left(\frac{a}{2}k_x\right) \right) \quad (\text{V.18})$$

$$\partial_{k_x} f_{\text{X}}(\mathbf{k}) = -2t_{\text{X}}(-a \sin(ak_x) - 2\frac{a}{2} \sin\left(\frac{a}{2}\right) \cos(\sqrt{3}\frac{a}{2}k_y)) \quad (\text{V.19})$$

$$= 2at_{\text{X}}(\sin(ak_x) + \sin\left(\frac{a}{2}\right) \cos(\sqrt{3}\frac{a}{2}k_y)) \quad (\text{V.20})$$

$$\partial_{k_y} f_{\text{X}}(\mathbf{k}) = -2t_{\text{X}}(-\sqrt{3}\frac{a}{2} \sin(\sqrt{3}\frac{a}{2}k_y)) = \sqrt{3}t_{\text{X}}a \sin(\sqrt{3}\frac{a}{2}k_y) \quad (\text{V.21})$$

### V.1.3 BdG HAMILTONIAN IN BAND BASIS

Use transformation

$$c_{\mathbf{k}\alpha\sigma}^\dagger = \sum_n [\mathbf{G}]_{\alpha n}^* d_{n\mathbf{k}\sigma}^\dagger \quad (\text{V.22})$$

where the columns are made up of the eigenvectors of  $\mathbf{H}_{0,\sigma}$  for a given  $\mathbf{k}$ :

$$\mathbf{G} = (\mathbf{G}_1 \quad \mathbf{G}_2 \quad \mathbf{G}_3) \quad (\text{V.23})$$

with that:

$$\mathbf{G}_\sigma^\dagger(\mathbf{k}) \mathbf{H}_{0,\sigma}(\mathbf{k}) \mathbf{G}_\sigma(\mathbf{k}) = \begin{pmatrix} \epsilon_1 & 0 & 0 \\ 0 & \epsilon_2 & 0 \\ 0 & 0 & \epsilon_3 \end{pmatrix} \quad (\text{V.24})$$

So the kinetic part of the BdG Hamiltonian becomes:

$$\sum_{\mathbf{k}\alpha\beta\sigma} [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} \sum_n [\mathbf{G}(\mathbf{k})]_{\alpha n}^* d_{n\mathbf{k}\sigma}^\dagger \sum_m [\mathbf{G}(\mathbf{k})]_{\beta m} d_{m\mathbf{k}\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{V.25})$$

$$= \sum_{mn\mathbf{k}\sigma} d_{n\mathbf{k}\sigma}^\dagger d_{m\mathbf{k}\sigma} \sum_{\alpha\beta} [\mathbf{G}(\mathbf{k})]_{\alpha n}^* [H_{0,\sigma}(\mathbf{k})]_{\alpha\beta} [\mathbf{G}(\mathbf{k})]_{\beta m} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{V.26})$$

$$= \sum_{mn\mathbf{k}\sigma} d_{n\mathbf{k}\sigma}^\dagger d_{m\mathbf{k}\sigma} \epsilon_n \delta_{nm} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{V.27})$$

$$= \sum_{n\mathbf{k}\sigma} \epsilon_n d_{n\mathbf{k}\sigma}^\dagger d_{n\mathbf{k}\sigma} - \mu \sum_{\mathbf{k}\alpha\sigma} n_{n\mathbf{k}\sigma} \quad (\text{V.28})$$

$$=: \sum_{n\mathbf{k}\sigma} \tilde{\zeta}_{\mathbf{k}} d_{n\mathbf{k}\sigma}^\dagger d_{n\mathbf{k}\sigma} \quad (\text{V.29})$$

with  $\tilde{\zeta}_{\mathbf{k}} := \epsilon_{\mathbf{k}} - \mu$ . The pairing terms become:

$$\sum_{\mathbf{k}\alpha} \Delta_\alpha c_{\mathbf{k}\alpha\uparrow}^\dagger c_{-\mathbf{k}\alpha\downarrow}^\dagger = \sum_{\mathbf{k}\alpha} \Delta_\alpha \sum_n [\mathbf{G}_\uparrow(\mathbf{k})]_{\alpha n}^* d_{n\mathbf{k}\uparrow}^\dagger \sum_m [\mathbf{G}_\downarrow(-\mathbf{k})]_{\beta m}^* d_{m-\mathbf{k}\downarrow}^\dagger \quad (\text{V.30})$$

$$= \quad (\text{V.31})$$

So that:

$$\mathcal{H}(\mathbf{k}) = \begin{pmatrix} \epsilon_{\mathbf{k}} - \mu & G^\dagger \Delta G \\ G^\dagger \Delta^\dagger G & -\epsilon_{\mathbf{k}} + \mu \end{pmatrix} \quad (\text{V.32})$$

with

$$\epsilon_{\mathbf{k}} = \begin{pmatrix} \epsilon_1(\mathbf{k}) & 0 & 0 \\ 0 & \epsilon_2(\mathbf{k}) & 0 \\ 0 & 0 & \epsilon_3(\mathbf{k}) \end{pmatrix} \quad (\text{V.33})$$

Concrete example for transformation of gaps from orbital to band basis at  $\mathbf{K} = \frac{4\pi}{3a} \begin{pmatrix} 1 \\ 0 \end{pmatrix}$ . There, the non-interacting part becomes simply:

$$\mathcal{H}_0 = \begin{pmatrix} 0 & 0 & V \\ 0 & 0 & 0 \\ V & 0 & 3t_X \end{pmatrix} \quad (\text{V.34})$$

The eigenvalue problem can be solved e.g. via sympy:

$$G = \begin{pmatrix} \frac{-3t_X - \sqrt{4V^2 + 9t_X^2}}{\sqrt{4V^2 + (3t_X + \sqrt{4V^2 + 9t_X^2})^2}} & 0 & \frac{-3t_X + \sqrt{4V^2 + 9t_X^2}}{\sqrt{4V^2 + (3t_X - \sqrt{4V^2 + 9t_X^2})^2}} \\ 0 & 1 & 0 \\ \frac{2V}{\sqrt{4V^2 + (3t_X + \sqrt{4V^2 + 9t_X^2})^2}} & 0 & \frac{2V}{\sqrt{4V^2 + (3t_X - \sqrt{4V^2 + 9t_X^2})^2}} \end{pmatrix} \quad (\text{V.35})$$

So for  $V \rightarrow 0$ :

$$G = \begin{pmatrix} -1 & 0 & 0 \\ 0 & 1 & 0 \\ 0 & 0 & 1 \end{pmatrix} \quad (\text{V.36})$$

but for  $V > 0$ , there are off-diagonal elements, e.g.  $V = 0.1$ :

$$G = \begin{pmatrix} -0.7578 & 0 & 0.6526 \\ 0 & 1 & 0 \\ 0.6526 & 0 & 0.7578 \end{pmatrix} \quad (\text{V.37})$$

So the transformation of the gap from orbital to band space reads:

$$G^\dagger \Delta G = \begin{pmatrix} \frac{3\Delta_1 t_X - 3\Delta_3 t_X + (\Delta_1 + \Delta_3) \sqrt{4V^2 + 9t_X^2}}{2\sqrt{4V^2 + 9t_X^2}} & 0 & \frac{V(-\Delta_1 + \Delta_3)}{\sqrt{4V^2 + 9t_X^2}} \\ 0 & \Delta_2 & 0 \\ \frac{V(-\Delta_1 + \Delta_3)}{\sqrt{4V^2 + 9t_X^2}} & 0 & \frac{-3\Delta_1 t_X + 3\Delta_3 t_X + (\Delta_1 + \Delta_3) \sqrt{4V^2 + 9t_X^2}}{2\sqrt{4V^2 + 9t_X^2}} \end{pmatrix} \quad (\text{V.38})$$

So in particular there is no interband pairing for  $V \rightarrow 0$ :

$$G^\dagger \Delta G = \begin{pmatrix} \Delta_1 & 0 & 0 \\ 0 & \Delta_2 & 0 \\ 0 & 0 & \Delta_3 \end{pmatrix} \quad (\text{V.39})$$

But for  $V > 0$ , there is interband pairing (e.g.  $V = 0.1$ ):

$$G^\dagger \Delta G = \begin{pmatrix} 0.5742\Delta_1 + 0.4258\Delta_3 & 0 & -0.4945\Delta_1 + 0.4945\Delta_3 \\ 0 & \Delta_2 & 0 \\ -0.4945\Delta_1 + 0.4945\Delta_3 & 0 & 0.4258\Delta_1 + 0.5742\Delta_3 \end{pmatrix} \quad (\text{V.40})$$

## V.2 GRAND POTENTIAL

See [20], especially supplementary material, notes 1 and 3.

Mean-Field Hamiltonian (with the last two terms due to exchange of anticommuting fermion operators and the term quadratic in the expectation value from the mean-field decoupling respectively):

$$H_{MF} = \sum_{\mathbf{k}} \Psi_{\mathbf{k}}^{\dagger} \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}} + \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\downarrow}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} \quad (\text{V.41})$$

The second term is the trace of the non-interacting Hamiltonian.

Thermodynamic grand potential (which at zero temperature is equivalent to the mean-field energy):

$$\Omega(T, \Delta) = -\frac{1}{\beta} \ln Z_{\Omega} = -\frac{1}{\beta} \ln \text{Tr}(e^{-\beta H_{MF}}) \quad (\text{V.42})$$

$$= \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\downarrow}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} - \frac{1}{\beta} \ln \text{Tr}(e^{-\beta \Psi_{\mathbf{k}}^{\dagger} \mathcal{H}(\mathbf{k}) \Psi_{\mathbf{k}}}) \quad (\text{V.43})$$

Zero temperature limit:

$$\Omega(\Delta) = \sum_{\mathbf{k}} \text{Tr}(H_{\mathbf{k}}^{\downarrow}) + \sum_{\mathbf{k}\alpha} \frac{|\Delta_{\alpha}|^2}{U} - \frac{1}{2} \sum_{\mathbf{k}} \text{Tr}([|\mathcal{H}_{\mathbf{k}}|]) \quad (\text{V.44})$$

where a function of a matrix  $H$  (such as taking the absolute value of the BdG Hamiltonian  $\mathcal{H}_{\mathbf{k}}$ ) is defined for the diagonal matrix of eigenvalues  $D$  and the unitary matrix  $U$  that diagonalizes  $H$ :

$$f(H) = U f(D) U^{\dagger} \quad (\text{V.45})$$

The route to finding the value of the order parameter for a fixed interaction  $U$  is minimizing the grand potential with respect to  $\Delta$ .

## BIBLIOGRAPHY

- [1] H. K. Onnes. "Further Experiments with Liquid Helium. G. On the Electrical Resistance of Pure Metals, Etc. VI. On the Sudden Change in the Rate at Which the Resistance of Mercury Disappears." In: *Through Measurement to Knowledge: The Selected Papers of Heike Kamerlingh Onnes 1853–1926*. Ed. by K. Gavroglu and Y. Goudaroulis. Dordrecht: Springer Netherlands, 1991, pp. 267–272. ISBN: 978-94-009-2079-8. DOI: 10.1007/978-94-009-2079-8\_17 (cit. on p. 1).
- [2] W. Meissner and R. Ochsenfeld. "Ein neuer Effekt bei Eintritt der Supraleitfähigkeit". In: *Naturwissenschaften* 21.44 (Nov. 1933), pp. 787–788. ISSN: 1432-1904. DOI: 10.1007/BF01504252 (cit. on p. 1).
- [3] J. Bardeen, L. N. Cooper, and J. R. Schrieffer. "Theory of Superconductivity". In: *Physical Review* 108.5 (Dec. 1957), pp. 1175–1204. DOI: 10.1103/PhysRev.108.1175 (cit. on pp. 1, 2).
- [4] J. G. Bednorz and K. A. Müller. "Possible High T<sub>c</sub> Superconductivity in the Ba-La-Cu-O System". In: *Zeitschrift für Physik B Condensed Matter* 64.2 (June 1986), pp. 189–193. ISSN: 1431-584X. DOI: 10.1007/BF01303701 (cit. on p. 1).
- [5] S.-i. Uchida et al. "High T<sub>c</sub> Superconductivity of La-Ba-Cu Oxides". In: *Japanese Journal of Applied Physics* 26.1A (Jan. 1987), p. L1. ISSN: 1347-4065. DOI: 10.1143/JJAP.26.L1 (cit. on p. 1).
- [6] D. Rybicki et al. "Perspective on the Phase Diagram of Cuprate High-Temperature Superconductors". In: *Nature Communications* 7.1 (May 2016), p. 11413. ISSN: 2041-1723. DOI: 10.1038/ncomms11413 (cit. on p. 1).
- [7] P. A. Rinck. *Magnetic Resonance in Medicine - A Critical Introduction*. ISBN: 978-628-01-2260-1 (cit. on p. 1).

- [8] A. Tollestrup and E. Todesco. “The Development of Superconducting Magnets for Use in Particle Accelerators: From the Tevatron to the LHC”. In: *Reviews of Accelerator Science and Technology* 1.01 (2008), pp. 185–210 (cit. on p. 1).
- [9] K. Irwin and G. Hilton. “Transition-Edge Sensors”. In: *Cryogenic Particle Detection*. Ed. by C. Enss. Berlin, Heidelberg: Springer, 2005, pp. 63–150. ISBN: 978-3-540-31478-3. DOI: 10.1007/10933596\_3 (cit. on p. 1).
- [10] D. Koelle et al. “High-Transition-Temperature Superconducting Quantum Interference Devices”. In: *Reviews of Modern Physics* 71.3 (Apr. 1999), pp. 631–686. DOI: 10.1103/RevModPhys.71.631 (cit. on p. 1).
- [11] M. I. Faley et al. “High-Tc SQUID Biomagnetometers”. In: *Superconductor Science and Technology* 30.8 (July 2017), p. 083001. ISSN: 0953-2048. DOI: 10.1088/1361-6668/aa73ad (cit. on p. 1).
- [12] Y. Yanase et al. “Theory of Superconductivity in Strongly Correlated Electron Systems”. In: *Physics Reports* 387.1 (Nov. 2003), pp. 1–149. ISSN: 0370-1573. DOI: 10.1016/j.physrep.2003.07.002 (cit. on p. 1).
- [13] X. Zhou et al. “High-Temperature Superconductivity”. In: *Nature Reviews Physics* 3.7 (July 2021), pp. 462–465. ISSN: 2522-5820. DOI: 10.1038/s42254-021-00324-3 (cit. on p. 1).
- [14] P. Coleman. *Introduction to Many-Body Physics*. Cambridge University Press, Nov. 2015. ISBN: 978-0-521-86488-6. DOI: 10.1017/CBO9781139020916 (cit. on pp. 2, 7, 15).
- [15] L. N. Cooper. “Bound Electron Pairs in a Degenerate Fermi Gas”. In: *Physical Review* 104.4 (Nov. 1956), pp. 1189–1190. DOI: 10.1103/PhysRev.104.1189 (cit. on p. 2).
- [16] F. London. “A New Conception of Supraconductivity”. In: *Nature* 140.3549 (Nov. 1937), pp. 793–796. ISSN: 1476-4687. DOI: 10.1038/140793a0 (cit. on p. 2).
- [17] L. D. Landau. “On The Theory of Superconductivity”. In: *Collected Papers of L.D. Landau*. Ed. by D. Ter Haar. Pergamon, Jan. 1965, pp. 546–568. ISBN: 978-0-08-010586-4. DOI: 10.1016/B978-0-08-010586-4.50078-X (cit. on p. 2).

- 
- [18] M. Qin et al. “The Hubbard Model: A Computational Perspective”. In: *Annual Review of Condensed Matter Physics* 13. Volume 13, 2022 (Mar. 2022), pp. 275–302. ISSN: 1947-5454, 1947-5462. DOI: 10.1146/annurev-conmatphys-090921-033948 (cit. on p. 3).
  - [19] R. Micnas, J. Ranninger, and S. Robaszkiewicz. “Superconductivity in Narrow-Band Systems with Local Nonretarded Attractive Interactions”. In: *Reviews of Modern Physics* 62.1 (Jan. 1990), pp. 113–171. DOI: 10.1103/RevModPhys.62.113 (cit. on p. 3).
  - [20] S. Peotta and P. Törmä. “Superfluidity in Topologically Nontrivial Flat Bands”. In: *Nature Communications* 6.1 (Nov. 2015), p. 8944. ISSN: 2041-1723. DOI: 10.1038/ncomms9944 (cit. on pp. 7, 32).
  - [21] N. Witt et al. *Bypassing the Lattice BCS-BEC Crossover in Strongly Correlated Superconductors: Resilient Coherence from Multiorbital Physics*. July 2024. DOI: 10.48550/arXiv.2310.09063 (cit. on p. 12).
  - [22] H. Bruus and K. Flensberg. *Many-Body Quantum Theory in Condensed Matter Physics: An Introduction*. Oxford Graduate Texts. Oxford, New York: Oxford University Press, Nov. 2004. ISBN: 978-0-19-856633-5 (cit. on pp. 13, 15).
  - [23] A. Georges et al. “Dynamical Mean-Field Theory of Strongly Correlated Fermion Systems and the Limit of Infinite Dimensions”. In: *Reviews of Modern Physics* 68.1 (Jan. 1996), pp. 13–125. DOI: 10.1103/RevModPhys.68.13 (cit. on p. 15).
  - [24] J. P. Provost and G. Vallee. “Riemannian Structure on Manifolds of Quantum States”. In: *Communications in Mathematical Physics* 76.3 (Sept. 1980), pp. 289–301. ISSN: 1432-0916. DOI: 10.1007/BF02193559 (cit. on p. 17).
  - [25] G. Yang et al. “Structure of Graphene and Its Disorders: A Review”. In: *Science and Technology of Advanced Materials* 19.1 (Aug. 2018), pp. 613–648. ISSN: 1468-6996. DOI: 10.1080/14686996.2018.1494493 (cit. on p. 19).





# LIST OF SYMBOLS

Symbol	Meaning	Definition
$\tau$	general imaginary time variable	14
$\mathcal{C}_{AB}(\tau,0)$	Correlation function in imaginary time	14