

Date: October 28, 2025



Issuing Office:
Jl. Arteri Tol Cibitung No. 1, Cibitung Bekasi 17520, Indonesia
Phone/Facs: +62 21 88321176/88321166
Email: cs.cbt@sucofindo.co.id

REPORT OF ANALYSIS

The following sample (s) was submitted and identified by the client as :

CLIENT	: PELAYARAN NASIONAL INDONESIA, PT Jl. Gajah Mada No. 14, RT. 6 / RW. 2, Petojo Utara, Kec. Gambir, Kota Jakarta Pusat, DKI Jakarta 10130
TYPE OF SAMPLE	: HSD B40
DATE RECEIVED	: October 20, 2025 From Sucofindo Hulu Migas dan Produk Migas
DATE OF ANALYSIS	: October 20, 2025 to October 27, 2025
TESTED FOR	: Full Analysis
DESCRIPTION OF SAMPLE	: Form : Liquid Volume : 1 L Packing : Unsealed Plastic Bottle 1 (One) sample
SAMPLE IDENTIFICATION	: KM UMSINI - Surabaya, 13 Oktober 2025, Tanki 2S (Kanan)
YOUR REFERENCE	: HMP.IWO.25.000028.M

The Attachment available is an integral part of this certificate.

This test result (s) related to the sample (s) submitted only and the report / certificate cannot be reproduced in any way, except in full context and with the prior approval in writing from Sucofindo Laboratory.

This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id

SBU Laboratory

Restu Fatmawati

CBT380110000813102025M

Date: October 28, 2025



Issuing Office:
Jl. Arteri Tol Cibitung No. 1, Cibitung Bekasi 17520, Indonesia
Phone/Facs: +62 21 88321176/88321166
Email: cs.cbt@sucofindo.co.id

REPORT OF ANALYSIS

Parameters	Units	Results	Specifications B40 CN 48*)		Methods
			Min	Max	
- Calculated Cetane Index	-	52.1	48	-	ASTM D4737-21
- Density at 15 °C	kg/m ³	853.3	815	880	ASTM D4052-22
- Kinematic Viscosity at 40 °C	mm ² /s	3.147	2.0	5.0	ASTM D445-23
- Sulfur Content	% wt	0.036	-	0.2	ASTM D4294-21
- <u>Distillation</u> Temperature at 90 % vol	°C	340.0	-	370	ASTM D86-23
- Flash Point PMcc	°C	69.0	52	-	ASTM D93-20
- Pour Point	°C	0	-	18	ASTM D97-17b (2022)
- Carbon Residue	% wt	0.02	-	0.1	ASTM D4530-15 (2020)
- Water Content	mg/kg	678	-	380	ASTM D6304-20
- FAME Content	% vol	35.69	40		ASTM D7371-14
- Copper Strip Corrosion	Class	1a	-	Class 1	ASTM D130-19
- Ash Content	% wt	0.003	-	0.01	ASTM D482-19
- Sediment Content	% wt	0	-	0.01	ASTM D473-22
- Strong Acid Number	mg KOH/g	0	0		ASTM D974-22
- Total Acid Number	mg KOH/g	0.87	-	0.6	ASTM D664-18e2
- Visual Appearance	-	Clear & Bright	Clear & Bright		Visual
- Color ASTM	No. ASTM	L 3.5	-	3	ASTM D1500-12 (2017)
- Oxidation Stability at 140 °C	Minutes	Greater than 60	45	-	ASTM D7545-14 (2019)
- Lubricity (HFRR Wear Scar Diameter at 60 °C)	µm	17799	-	460	ASTM D6079-22
- Particle Count:					
> 4 µm	Count/mL	420099	-	-	ISO 11500:2008
> 6 µm	Count/mL	126966	-	-	ISO 11500:2008
> 14 µm	Count/mL	2166	-	-	ISO 11500:2008
- ISO Code	-	26/24/18	-	-	ISO 4406

*) SK. Dirjen Migas No. 384.K/MG.06/DJM/2024