



Thermal fragmentation: $\hat{\ell} = 0.04$ | $\Lambda = 50.0$ | $\eta = 0.001$
Run: $\theta_{\max} = 4.00$ | $N_{QS} = 40$ | $N_{Dyn} = 120$ | $N_{Mesh} = 200$ | $T_0 = 1.0$


Mean stress vs thermal strain




QS: fragmentation generations



Dynamic: fragmentation generations



Energy evolution



Inf-norm gaps (max |QS - Dyn|): $\Delta P_{el} = 1.938e - 07$ | $\Delta P_f = 2.379e - 07$ | $\Delta S = 4.285e - 07$ | $\Delta Total = 2.478e - 09$