



Thermal fragmentation: $\hat{\ell} = 0.08$ | $\Lambda = 50.0$ | $\eta = 0.05$
Run: $\theta_{\max} = 4.00$ | $N_{QS} = 20$ | $N_{Dyn} = 60$ | $N_{Mesh} = 200$ | $T_0 = 1.0$


Mean stress vs thermal strain




QS: fragmentation generations



Dynamic: fragmentation generations



Energy evolution



Inf-norm gaps (max |QS - Dyn|): $\Delta P_{el} = 6.346e - 05$ | $\Delta P_f = 7.157e - 05$ | $\Delta S = 1.346e - 04$ | $\Delta \text{Total} = 2.013e - 06$