



Thermal fragmentation: $\hat{\ell} = 0.02$ | $\Lambda = 20.0$ | $\eta = 0.1$
Run: $\theta_{\max} = 4.00$ | $N_{QS} = 20$ | $N_{Dyn} = 60$ | $N_{Mesh} = 200$ | $T_0 = 1.0$


Mean stress vs thermal strain




QS: fragmentation generations



Dynamic: fragmentation generations



Energy evolution



Inf-norm gaps (max |QS - Dyn|): $\Delta P_{el} = 9.356e - 02$ | $\Delta P_f = 9.107e - 02$ | $\Delta S = 6.593e - 02$ | $\Delta \text{Total} = 3.218e - 02$