


Aprosoft LFE-Labor

Project I-G
 Material 50 hydrogel
 Sample 1
 Atmosphere vacuum

Temp in °C 24
 Measnr 1113
 Thickness in 0.4000
 I-G_1__50 hydrogel_1_766.lf



Details

Duration in s 9.0153
 Max. in V 1.28
 Min. in V 0.5
 Halftime in ms 1327.482
 Min.type Baseline
 Remark

Pulse in ms

Length 0.0500
 Type Tri
 Trapez time1 0.005
 Trapez time2 0.045

Condition

Operator Nathan
 Filter 0
 Iris 1
 Amp. 100

Adiabatic results in cm²/s

Ave. 0.0221
 40 0.0217
 50% 0.0167
 60% 0.0138

Finite Pulse in cm²/s

Dusza 0.0167
 Azumi 0.0167
 Clark 0.0167
 Combined
 Dusza 0.018

Heatloss in cm²/s

Dusza 0.018
 Cowan 0.0143
 Degiovanni 0.0167
 Taylor 0
 Cowan 10 0.0167