


Aprosoft LFE-Labor

Project I-G
Material 50 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 0.4000
I-G_1__50 hydrogel_1_773.If



Details

Duration in s 9.0153
Max. in V 2.24
Min. in V 0.5
Halftime in ms 951.997
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 200

Adiabatic results in cm²/s

Ave. 0.0284
40 0.0299
50% 0.0233
60% 0.02

Finite Pulse in cm²/s

Dusza 0.0233
Azumi 0.0233
Clark 0.0233
Combined
Dusza 0.0208

Heatloss in cm²/s

Dusza 0.0208
Cowan 0.0208
Degiovanni 0
Taylor 0
Cowan 10 0.0233