


Aprosoft LFE-Labor

Project	I-G	Temp in °C	24
Material	50 hydrogel	Measnr	1113
Sample	1	Thickness in	0.4000
Atmosphere	vacuum	I-G_1__50 hydrogel_1_775.lf	



Details

Duration in s	14.0238
Max. in V	2.52
Min. in V	0.5
Halftime in ms	2894.802
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	200

Adiabatic results in cm²/s

Ave.	0.00829
40	0.00867
50%	0.00767
60%	0.00695

Finite Pulse in cm²/s

Dusza	0.00767
Azumi	0.00767
Clark	0.00767
Combined	
Dusza	0.00823

Heatloss in cm²/s

Dusza	0.00394
Cowan	0.00767
Degiovanni	0.00767
Taylor	0
Cowan 10	0.00767