


Aprosoft LFE-Labor

Project	I-G	Temp in °C	23
Material	hydrogel 50	Measnr	1719
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_750.lf	



Details

Duration in s	185.652
Max. in V	6.39
Min. in V	0.5
Halftime in ms	89061.644
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	50

Adiabatic results in cm²/s

Ave.	0.00287
40	0.00277
50%	0.00263
60%	0.00258

Finite Pulse in cm²/s

Dusza	0.00263
Azumi	0.00263
Clark	0.00263
Combined	
Dusza	0.00263

Heatloss in cm²/s

Dusza	0.00374
Cowan	0.00263
Degiovanni	0.0023
Taylor	0.00263
Cowan 10	0.00263