


Aprosoft LFE-Labor

Project	I-G	Temp in °C	24
Material	hydrogel 50	Measnr	1113
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_753.If	



Details

Duration in s	20.034
Max. in V	1.51
Min. in V	0.5
Halftime in ms	2222.0582
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	100

Adiabatic results in cm2/s

Ave.	0.152
40	0.161
50%	0.106
60%	0.0798

Finite Pulse in cm2/s

Dusza	0.106
Azumi	0.106
Clark	0.106
Combined	
Dusza	0.126

Heatloss in cm2/s

Dusza	0.126
Cowan	0.0837
Degiovanni	0
Taylor	0
Cowan 10	0.106