


Project	I-G	Temp in °C	24
Material	hydrogel 50	Measnr	1113
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_754.If	



Details

Duration in s	60.102
Max. in V	4.27
Min. in V	0.46
Halftime in ms	22711.735
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	100

Adiabatic results in cm²/s

Ave.	0.0192
40	0.0135
50%	0.0103
60%	0.00912

Finite Pulse in cm²/s

Dusza	0.0103
Azumi	0.0103
Clark	0.0103
Combined	
Dusza	0.0111

Heatloss in cm²/s

Dusza	0.0111
Cowan	0.0103
Degiovanni	0.00981
Taylor	0
Cowan 10	0.0103