


Aprosoft LFE-Labor

Project I-G
Material hydrogel 50
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 1.3000
I-G_1__hydrogel 50_1_755.If



Details

Duration in s 5.0085
Max. in V 0.86
Min. in V 0.5
Halftime in ms 188.728
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.646
40 1.0665
50% 1.243
60% 0.207

Finite Pulse in cm²/s

Dusza 1.243
Azumi 1.243
Clark 1.243
Combined
Dusza 1.606

Heatloss in cm²/s

Dusza 1.606
Cowan 0.734
Degiovanni 0
Taylor 0
Cowan 10 1.0872