


Aprosoft LFE-Labor

Project	I-G	Temp in °C	24
Material	hydrogel 50	Measnr	1113
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_756.lf	



Details

Duration in s 15.0255
 Max. in V 1.063
 Min. in V 0.5
 Halftime in ms 2328.765
 Min.type Baseline
 Remark

Pulse in ms

Length 0.0500
 Type Tri
 Trapez time1 0.005
 Trapez time2 0.045

Condition

Operator Nathan
 Filter 0
 Iris 1
 Amp. 100

Adiabatic results in cm²/s

Ave. 0.147
 40 0.168
 50% 0.101
 60% 0.0726

Finite Pulse in cm²/s

Dusza 0.101
 Azumi 0.101
 Clark 0.101
 Combined
 Dusza 0.11

Heatloss in cm²/s

Dusza 0.11
 Cowan 0.0866
 Degiovanni 0.0935
 Taylor 0
 Cowan 10 0.101