


Aprosoft LFE-Labor

Project I-G
Material 100 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 0.3140
I-G_1__100 hydrogel_1_760.If



Details

Duration in s 15.0255
Max. in V 1.063
Min. in V 0.51
Halftime in ms 996.913
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.0179
40 0.0165
50% 0.0137
60% 0.0114

Finite Pulse in cm²/s

Dusza 0.0137
Azumi 0.0137
Clark 0.0137
Combined
Dusza 0.0126

Heatloss in cm²/s

Dusza 0.0126
Cowan 0.0132
Degiovanni 0
Taylor 0
Cowan 10 0.0131