


Aprosoft LFE-Labor

Project I-G
Material 100 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 0.3140
I-G_1__100 hydrogel_1_762.If



Details

Duration in s 15.0255
Max. in V 1.14
Min. in V 0.51
Halftime in ms 907.283
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.017
40 0.0192
50% 0.0151
60% 0.0125

Finite Pulse in cm²/s

Dusza 0.0151
Azumi 0.0151
Clark 0.0151
Combined
Dusza 0.0165

Heatloss in cm²/s

Dusza 0.0165
Cowan 0.0133
Degiovanni 0
Taylor 0
Cowan 10 0.0145