


Aprosoft LFE-Labor

Project	I-G	Temp in °C	24
Material	hydrogel 50	Measnr	1113
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_758.lf	



Details

Duration in s	20.034
Max. in V	1.72
Min. in V	0.49
Halftime in ms	5159.513
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	100

Adiabatic results in cm²/s

Ave.	0.0773
40	0.0664
50%	0.0455
60%	0.032

Finite Pulse in cm²/s

Dusza	0.0455
Azumi	0.0455
Clark	0.0455
Combined	
Dusza	0.0533

Heatloss in cm²/s

Dusza	0.0533
Cowan	0.0455
Degiovanni	0.0408
Taylor	0
Cowan 10	0.0455