


Aprosoft LFE-Labor

Project	I-G	Temp in °C	24
Material	hydrogel 50	Measnr	1719
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_759.If	



Details

Duration in s	185.652
Max. in V	2.77
Min. in V	0.5
Halftime in ms	95782.237
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	20

Adiabatic results in cm2/s

Ave.	0.00267
40	0.00253
50%	0.00245
60%	0.00244

Finite Pulse in cm2/s

Dusza	0.00245
Azumi	0.00245
Clark	0.00245
Combined	
Dusza	0.00241

Heatloss in cm2/s

Dusza	0.00365
Cowan	0.00245
Degiovanni	0.00204
Taylor	0.0024
Cowan 10	0.00245