


Aprosoft LFE-Labor

Project	I-G	Temp in °C	25
Material	25 hydrogel	Measnr	1113
Sample	1	Thickness in	0.4000
Atmosphere	vacuum	I-G_1__25 hydrogel_1_780.lf	



Details

Duration in s	10.017
Max. in V	1.69
Min. in V	0.51
Halftime in ms	1872.0374
Min.type	Baseline
Remark	

Pulse in ms

Length	0.0500
Type	Tri
Trapez time1	0.005
Trapez time2	0.045

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	200

Adiabatic results in cm²/s

Ave.	0.0176
40	0.0159
50%	0.0119
60%	0.01

Finite Pulse in cm²/s

Dusza	0.0119
Azumi	0.0119
Clark	0.0119
Combined	
Dusza	0.0115

Heatloss in cm²/s

Dusza	0.0115
Cowan	0.0115
Degiovanni	0
Taylor	0
Cowan 10	0.0119