


Aprosoft LFE-Labor

Project I-G
Material 25 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 25
Measnr 1113
Thickness in 0.4000
I-G_1__25 hydrogel_1_781.lf



Details

Duration in s 13.0221
Max. in V 2.058
Min. in V 0.5
Halftime in ms 2383.329
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 200

Adiabatic results in cm²/s

Ave. 0.0152
40 0.0131
50% 0.00932
60% 0.00763

Finite Pulse in cm²/s

Dusza 0.00932
Azumi 0.00932
Clark 0.00932
Combined
Dusza 0.0102

Heatloss in cm²/s

Dusza 0.0102
Cowan 0.00864
Degiovanni 0.00932
Taylor 0
Cowan 10 0.00932