


Aprosoft LFE-Labor

Project I-G
Material 50 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 0.4000
I-G_1__50 hydrogel_1_768.If



Details

Duration in s 15.0255
Max. in V 0.93
Min. in V 0.51
Halftime in ms 864.436
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.0301
40 0.0288
50% 0.0257
60% 0.0235

Finite Pulse in cm²/s

Dusza 0.0257
Azumi 0.0257
Clark 0.0257
Combined
Dusza 0.0265

Heatloss in cm²/s

Dusza 0.0193
Cowan 0.0252
Degiovanni 0
Taylor 0
Cowan 10 0.0219