


Aprosoft LFE-Labor

Project I-G
Material 50 hydrogel
Sample 1
Atmosphere vacuum

Temp in °C 24
Measnr 1113
Thickness in 0.4000
I-G_1__50 hydrogel_1_770.lf



Details

Duration in s 9.0153
Max. in V 1.2
Min. in V 0.5
Halftime in ms 1057.499
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.0284
40 0.0266
50% 0.021
60% 0.0177

Finite Pulse in cm²/s

Dusza 0.021
Azumi 0.021
Clark 0.021
Combined
Dusza 0.0223

Heatloss in cm²/s

Dusza 0.0223
Cowan 0.0179
Degiovanni 0.021
Taylor 0
Cowan 10 0.021