


Aprosoft LFE-Labor

Project I-G
 Material 50 hydrogel
 Sample 1
 Atmosphere vacuum

Temp in °C 24
 Measnr 1113
 Thickness in 0.4000
 I-G_1__50 hydrogel_1_774.If



Details

Duration in s 9.0153
 Max. in V 2.074
 Min. in V 0.5
 Halftime in ms 2117.676
 Min.type Baseline
 Remark

Pulse in ms

Length 0.0500
 Type Tri
 Trapez time1 0.005
 Trapez time2 0.045

Condition

Operator Nathan
 Filter 0
 Iris 1
 Amp. 200

Adiabatic results in cm²/s

Ave. 0.0112
 40 0.0117
 50% 0.0105
 60% 0.00965

Finite Pulse in cm²/s

Dusza 0.0105
 Azumi 0.0105
 Clark 0.0105
 Combined
 Dusza 0.0109

Heatloss in cm²/s

Dusza 0.00928
 Cowan 0.0105
 Degiovanni 0.0105
 Taylor 0.00477
 Cowan 10 0.0105