


Aprosoft LFE-Labor

Project	I-G	Temp in °C	23
Material	hydrogel 50	Measnr	1113
Sample	1	Thickness in	1.3000
Atmosphere	vacuum	I-G_1__hydrogel 50_1_743.If	



Details

Duration in s	2.0034
Max. in V	1.16
Min. in V	0.51
Halftime in ms	732.543
Min.type	Baseline
Remark	

Pulse in ms

Length	0.400
Type	Tri
Trapez time1	0.040
Trapez time2	0.360

Condition

Operator	Nathan
Filter	0
Iris	1
Amp.	200

Adiabatic results in cm²/s

Ave.	0.475
40	0.358
50%	0.32
60%	0.298

Finite Pulse in cm²/s

Dusza	0.32
Azumi	0.32
Clark	0.32
Combined	
Dusza	0.337

Heatloss in cm²/s

Dusza	0.337
Cowan	0.32
Degiovanni	0.317
Taylor	0
Cowan 10	0.32