


Aprosoft LFE-Labor

Project I-G
Material hydrogel 50
Sample 1
Atmosphere vacuum

Temp in °C 23
Measnr 1113
Thickness in 1.3000
I-G_1__hydrogel 50_1_748.lf



Details

Duration in s 30.051
Max. in V 2.18
Min. in V 0.5
Halftime in ms 6598.302
Min.type Baseline
Remark

Pulse in ms

Length 0.0500
Type Tri
Trapez time1 0.005
Trapez time2 0.045

Condition

Operator Nathan
Filter 0
Iris 1
Amp. 100

Adiabatic results in cm²/s

Ave. 0.0457
40 0.0472
50% 0.0355
60% 0.025

Finite Pulse in cm²/s

Dusza 0.0355
Azumi 0.0355
Clark 0.0355
Combined
Dusza 0.0421

Heatloss in cm²/s

Dusza 0.0421
Cowan 0.0355
Degiovanni 0.0326
Taylor 0
Cowan 10 0.0355