

RECYCLED PET ACOUSTIC PANEL

rPET Panel

The recycled PET felt panel you machine like MDF.

rPET Panel is a rigid acoustic felt board made from 100 % recycled PET bottles. It absorbs sound across its whole surface, weighs a fraction of a wood-based board and is worked with standard workshop tools: saw, mill and drill it, then paint or UV-print it.

Used for wall and ceiling panels, room dividers and acoustic furniture. Two thicknesses, two formats, a Standard and a fire-retardant (FR) version. Made in Poland.

PANEL FORMATS · TO SCALE



2 800 × 1 220 mm
3.42 m²



2 440 × 1 220 mm
2.98 m²

9 · 12

mm thickness

1.8 · 2.4

kg/m² surface weight

100 %

recycled PET

10

stock colours, any colour to order

TECHNICAL DATA

Dimensions and weight

Per thickness	9 mm	12 mm
Surface weight	1.8 kg/m²	2.4 kg/m²
Panel 2 800 × 1 220 mm	≈ 6.1 kg	≈ 8.2 kg
Panel 2 440 × 1 220 mm	≈ 5.4 kg	≈ 7.1 kg
Density (both)	≈ 200 kg/m³	

General	
Material	100 % recycled PET felt
Formats	2 800 × 1 220 mm (3.42 m²) 2 440 × 1 220 mm (2.98 m²)
Versions	Standard · FR (fire-retardant)
Colours	10 stock colours + custom
Made in	Poland (Częstochowa)

≈ Calculated from the nominal surface weight and the panel area.

ACOUSTICS

Sound absorption

PET felt is a porous absorber: sound enters the open fibre structure and is turned into heat. How much a panel absorbs depends on its thickness and, above all, on how it is mounted. Fixed straight to the wall it treats mainly mid and high frequencies; with an air cavity or mineral wool behind it, absorption rises sharply and reaches lower frequencies.

Mounting · 12 mm panel	αw	NRC	Absorption class
Directly on the wall	0.25 (MH)	0.40	D
50 mm air cavity	0.60 (MH)	0.75	C
50 mm cavity + 50 mm stone wool	1.00	0.95	A
100 mm air cavity	0.80 (H)	0.80	B
100 mm cavity + 100 mm stone wool	0.95	0.95	A

Measured to EN ISO 354 on 12 mm PET felt of identical specification (2.4 kg/m²); αw and class to EN ISO 11654, NRC to ASTM C423. 9 mm panel: not yet measured.

FIRE SAFETY

Reaction to fire

Reaction to fire to EN 13501-1 depends on the colour: white, grey and black reach B-s1,d0, all other colours B-s2,d0, in both the Standard and the FR version. Classification reports on request.

**White, grey,
black**

Class to EN 13501-1

B-s1,d0

Other colours

Class to EN 13501-1

B-s2,d0

PROCESSING

Works like a wood-based board

Cutting A knife, circular saw, panel saw or an angle grinder with a metal-cutting blade.	CNC milling Shapes, cut-outs and grooves; V-cuts let you fold corners and 3D forms.	Drilling and fixing Drills and takes screws without splitting.
Painting Takes water-based and solvent-based paints.	UV printing Custom graphics, printed in-house by Re-Sound.	Care Vacuum with a soft brush; treat stains locally.

COLOURS

Ten colours from stock, any colour to order



01	02	03	04	05	06	07	08	09	10
Light grey	Off-white	Sand	Dusty rose	Deep red	Olive green	Forest green	Slate blue	Silver grey	Charcoal

Made to order

Stock colours 01–10 are always available, from one panel. Any other colour is made to order: send us a RAL or NCS reference or a physical sample. Minimum quantities for made-to-order colours on request.

Colour and batch

Made from recycled fibres, so slight shade differences between batches are normal. Order the panels for one surface together and mount them the same way round. The swatches are photographs: ask for physical samples before you specify.

ORDERING

Minimum order and lead time

Order		Supply	
Minimum order	1 panel	Lead time	≈ 3–4 working weeks
Versions	Standard · FR	Delivery	EXW Częstochowa, Poland
Prices	On request		

End of life

100 % PET, one material, recyclable at end of life. Re-Sound takes panels back free of charge in Belgium, the Netherlands, France, Germany and Luxembourg.

Samples and quotes

info@re-sound.be · +32 3 284 68 18
Showroom: Gentseweg 309 A3, 9120
Beveren-Waas, Belgium

Data reflects our current knowledge and may change without notice. Values marked ≈ are calculated.