

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	vg96371	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	02 Hour 16 Min 14 Sec
Total Counter :	189092	Total Running Time :	1751 Hour 33 Min
Station :	Station 1		

Setting Value

Feeder :	Auto ;	122	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	26.14	kN	No		
HEP :	25.0 %	25.13	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	20.51	kN	Yes 15	Times	
Ref :		20.11	kN			
LCP :	2.0 %	19.70	kN	Yes 15	Times	
LEP :	25.0 %	15.08	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	14.07	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	None					

Pressure Data

Mean Pre Pressure :	3.27	kN	Min :	2.48	kN	Punch NO.;	33
SD :	11.40	%	Max :	4.41	kN	Punch NO.;	1
Mean Main Pressure :	20.35	kN	Min :	17.77	kN	Punch NO.;	33
SD :	6.10	%	Max :	24.50	kN	Punch NO.;	1
Filling Depth :	Increase ;	153	Times	Decrease ;	158	Times	

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	18	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.40	mm	Main Thickness ;	0.60	mm
Filling Depth :	6.82	mm	Current Cam :	Cam B	
Main Air pressure :	0.817	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	9	Min			
Lower Punch Remain Time (S2):	20	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.30	kN		
	Max ;	0.40	kN	Max Punch ;	49
Lower Punch :	Average ;	0.10	kN		
	Max ;	0.14	kN	Max Punch ;	28
Ejection Force :	Average ;	0.02	kN		
	Max ;	0.03	kN	Max Punch ;	3

Tablet Data (N/A)

Total Counter :	189092	Tablets			
A.W.C Counter :	186666	Tablets			
HEP :	285 (0.2%)	Tablets	LEP :	130 (0.1%)	Tablets
GOOD :	186251 (99.8%)	Tablets			

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	vg96371	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	02 Hour 16 Min 14 Sec
Total Counter :	189092	Total Running Time :	1751 Hour 33 Min
Station :	Station 2		

Setting Value

Feeder :	Auto ;	124	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	27.02	kN	No		
HEP :	25.0 %	25.99	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	21.20	kN	Yes 15	Times	
Ref :		20.79	kN			
LCP :	2.0 %	20.37	kN	Yes 15	Times	
LEP :	25.0 %	15.59	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	14.55	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	N					

Pressure Data

Mean Pre Pressure :	2.89	kN	Min :	2.37	kN	Punch NO.;	51
SD :	10.80	%	Max :	3.61	kN	Punch NO.;	45
Mean Main Pressure :	20.92	kN	Min :	19.03	kN	Punch NO.;	41
SD :	4.40	%	Max :	23.14	kN	Punch NO.;	45
Filling Depth :	Increase ; 127	Times	Decrease ;	135	Times		

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	19	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.40	mm	Main Thickness ;	0.60	mm
Filling Depth :	6.84	mm	Current Cam :	Cam B	
Main Air pressure :	0.817	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	9	Min			
Lower Punch Remain Time (S2):	20	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.30	kN		
	Max ;	0.40	kN	Max Punch ;	49
Lower Punch :	Average ;	0.10	kN		
	Max ;	0.14	kN	Max Punch ;	32
Ejection Force :	Average ;	0.03	kN		
	Max ;	0.03	kN	Max Punch ;	27

Tablet Data (N/A)

Total Counter :	189092	Tablets			
A.W.C Counter :	186666	Tablets			
HEP :	285 (0.2%)	Tablets	LEP :	130 (0.1%)	Tablets
GOOD :	186251 (99.8%)	Tablets			