

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	pb97604	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	10 Hour 24 Min 17 Sec
Total Counter :	959892	Total Running Time :	1759 Hour 41 Min
Station :	Station 1		

Setting Value

Feeder :	Auto ;	120	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	27.62	kN	No		
HEP :	25.0 %	26.56	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	21.67	kN	Yes 15	Times	
Ref :		21.25	kN			
LCP :	2.0 %	20.82	kN	Yes 15	Times	
LEP :	25.0 %	15.94	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	14.87	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	None					

Pressure Data

Mean Pre Pressure :	3.18	kN	Min :	2.51	kN	Punch NO.;	48
SD :	9.40	%	Max :	3.80	kN	Punch NO.;	36
Mean Main Pressure :	20.49	kN	Min :	18.06	kN	Punch NO.;	48
SD :	4.80	%	Max :	22.53	kN	Punch NO.;	27
Filling Depth :	Increase ; 636	Times	Decrease ;	647	Times		

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	0	Tablets/hour
Feeder : Status ;	Auto		Speed ;	18	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.42	mm	Main Thickness ;	0.62	mm
Filling Depth :	6.51	mm	Current Cam :	Cam B	
Main Air pressure :	0.815	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	4	Min			
Lower Punch Remain Time (S2):	15	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.08	kN		
	Max ;	0.14	kN	Max Punch ;	1
Lower Punch :	Average ;	0.24	kN		
	Max ;	0.90	kN	Max Punch ;	1
Ejection Force :	Average ;	0.03	kN		
	Max ;	0.05	kN	Max Punch ;	29

Tablet Data (N/A)

Total Counter :	959892	Tablets			
A.W.C Counter :	956899	Tablets			
HEP :	563 (0.1%)	Tablets	LEP :	221 (0.0%)	Tablets
GOOD :	956115 (99.9%)	Tablets			

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	pb97604	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	10 Hour 24 Min 17 Sec
Total Counter :	959892	Total Running Time :	1759 Hour 41 Min
Station :	Station 2		

Setting Value

Feeder :	Auto ;	124	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	29.32	kN	No		
HEP :	25.0 %	28.20	kN	Yes	10	Rotations 15 Tablets
HCP :	2.0 %	23.01	kN	Yes	15	Times
Ref :		22.56	kN			
LCP :	2.0 %	22.11	kN	Yes	15	Times
LEP :	25.0 %	16.92	kN	Yes	10	Rotations 15 Tablets
LSP :	30.0 %	15.79	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2	Rotations		Calculation Pass :	2	Rotations
Empty Punch No. :	N					

Pressure Data

Mean Pre Pressure :	3.27	kN	Min :	2.36	kN	Punch NO.;	33
SD :	11.60	%	Max :	4.08	kN	Punch NO.;	23
Mean Main Pressure :	22.57	kN	Min :	19.78	kN	Punch NO.;	33
SD :	5.40	%	Max :	25.24	kN	Punch NO.;	23
Filling Depth :	Increase ;	297	Times	Decrease ;	316	Times	

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	0	Tablets/hour
Feeder : Status ;	Auto		Speed ;	19	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.42	mm	Main Thickness ;	0.62	mm
Filling Depth :	6.79	mm	Current Cam :	Cam B	
Main Air pressure :	0.815	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	4	Min			
Lower Punch Remain Time (S2):	15	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.08	kN		
	Max ;	0.16	kN	Max Punch ;	1
Lower Punch :	Average ;	0.24	kN		
	Max ;	0.90	kN	Max Punch ;	1
Ejection Force :	Average ;	0.03	kN		
	Max ;	0.05	kN	Max Punch ;	29

Tablet Data (N/A)

Total Counter :	959892	Tablets			
A.W.C Counter :	956952	Tablets			
HEP :	563 (0.1%)	Tablets	LEP :	221 (0.0%)	Tablets
GOOD :	956168 (99.9%)	Tablets			