

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	pb97604	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	14 Hour 05 Min 55 Sec
Total Counter :	1309998	Total Running Time :	1763 Hour 23 Min
Station :	Station 1		

Setting Value

Feeder :	Auto ;	136	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	28.71	kN	No		
HEP :	25.0 %	27.60	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	22.52	kN	Yes 15	Times	
Ref :		22.08	kN			
LCP :	2.0 %	21.64	kN	Yes 15	Times	
LEP :	25.0 %	16.56	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	15.46	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	None					

Pressure Data

Mean Pre Pressure :	4.05	kN	Min :	3.40	kN	Punch NO.;	14
SD :	9.20	%	Max :	4.89	kN	Punch NO.;	20
Mean Main Pressure :	23.33	kN	Min :	21.16	kN	Punch NO.;	14
SD :	4.80	%	Max :	26.01	kN	Punch NO.;	20
Filling Depth :	Increase ;	1039	Times	Decrease ;	1049	Times	

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	20	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.42	mm	Main Thickness ;	0.62	mm
Filling Depth :	6.65	mm	Current Cam :	Cam B	
Main Air pressure :	0.801	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	22	Min			
Lower Punch Remain Time (S2):	33	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.09	kN		
	Max ;	0.14	kN	Max Punch ;	14
Lower Punch :	Average ;	0.23	kN		
	Max ;	0.29	kN	Max Punch ;	36
Ejection Force :	Average ;	0.04	kN		
	Max ;	0.06	kN	Max Punch ;	42

Tablet Data (N/A)

Total Counter :	1309998	Tablets			
A.W.C Counter :	1307017	Tablets			
HEP :	625 (0.0%)	Tablets	LEP :	226 (0.0%)	Tablets
GOOD :	1306166 (99.9%)	Tablets			

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	pb97604	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	14 Hour 05 Min 55 Sec
Total Counter :	1309998	Total Running Time :	1763 Hour 23 Min
Station :	Station 2		

Setting Value

Feeder :	Auto ;	124	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	29.32	kN	No		
HEP :	25.0 %	28.20	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	23.01	kN	Yes 15	Times	
Ref :		22.56	kN			
LCP :	2.0 %	22.11	kN	Yes 15	Times	
LEP :	25.0 %	16.92	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	15.79	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	N					

Pressure Data

Mean Pre Pressure :	SD :	3.37	kN	Min :	2.55	kN	Punch NO.;	10
		10.80	%	Max :	4.19	kN	Punch NO.;	28
Mean Main Pressure :		22.99	kN	Min :	19.99	kN	Punch NO.;	10
	SD :	5.00	%	Max :	25.44	kN	Punch NO.;	28
Filling Depth :	Increase ;	455	Times	Decrease ;	463	Times		

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	19	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.42	mm	Main Thickness ;	0.62	mm
Filling Depth :	7.12	mm	Current Cam :	Cam B	
Main Air pressure :	0.801	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	22	Min			
Lower Punch Remain Time (S2):	33	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.08	kN		
	Max ;	0.15	kN	Max Punch ;	1
Lower Punch :	Average ;	0.23	kN		
	Max ;	0.29	kN	Max Punch ;	36
Ejection Force :	Average ;	0.04	kN		
	Max ;	0.06	kN	Max Punch ;	42

Tablet Data (N/A)

Total Counter :	1309998	Tablets			
A.W.C Counter :	1307017	Tablets			
HEP :	625 (0.0%)	Tablets	LEP :	226 (0.0%)	Tablets
GOOD :	1306166 (99.9%)	Tablets			