

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	sj97904	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	05 Hour 39 Min 17 Sec
Total Counter :	509780	Total Running Time :	1754 Hour 56 Min
Station :	Station 1		

Setting Value

Feeder :	Auto ;	124	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	26.52	kN	No		
HEP :	25.0 %	25.50	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	20.81	kN	Yes 15	Times	
Ref :		20.40	kN			
LCP :	2.0 %	19.99	kN	Yes 15	Times	
LEP :	25.0 %	15.30	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	14.28	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	None					

Pressure Data

Mean Pre Pressure :	3.31	kN	Min :	2.51	kN	Punch NO.;	33
SD :	13.20	%	Max :	4.31	kN	Punch NO.;	2
Mean Main Pressure :	20.83	kN	Min :	18.22	kN	Punch NO.;	39
SD :	6.40	%	Max :	23.44	kN	Punch NO.;	2
Filling Depth :	Increase ;	165	Times	Decrease ;	169	Times	

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	19	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.40	mm	Main Thickness ;	0.60	mm
Filling Depth :	6.59	mm	Current Cam :	Cam B	
Main Air pressure :	0.814	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	46	Min			
Lower Punch Remain Time (S2):	17	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.12	kN		
	Max ;	0.17	kN	Max Punch ;	11
Lower Punch :	Average ;	0.15	kN		
	Max ;	0.19	kN	Max Punch ;	2
Ejection Force :	Average ;	0.03	kN		
	Max ;	0.05	kN	Max Punch ;	3

Tablet Data (N/A)

Total Counter :	509780	Tablets			
A.W.C Counter :	506899	Tablets			
HEP :	404 (0.1%)	Tablets	LEP :	190 (0.0%)	Tablets
GOOD :	506305 (99.9%)	Tablets			

PRODUCTION REPORT

Product Information

Machine Name :	VANTIX P720D	Product Name :	Amio 200mg STAI3A00
User ID :	sj97904	Batch NO. :	AIM2500420
Print Interval :	50000 Tablets	Running Time :	05 Hour 39 Min 17 Sec
Total Counter :	509780	Total Running Time :	1754 Hour 56 Min
Station :	Station 2		

Setting Value

Feeder :	Auto ;	124	%	Manual ;	20	RPM
Filling Cam :		Cam B		Cam Range :	Min :	2.50 mm
		4.5-10mm			Max :	8.00 mm
Target Quantity :		1500000	Tablets			
Air Pressure Low Limit :		0.600	MPa			
Oil Lubrication :						
Upper Punch Interval Time(S1) ;		60	Min	Supply Time ;	1.0	Sec
Lower Punch Interval Time(S2) ;		40	Min	Supply Time ;	1.0	Sec
Powder Supply Time :		5.0	Sec			
Initial Reject Time :		2	Tablets			
Upper Punch Tightness High Limit :		1.00	kN			
Lower Punch Tightness High Limit :		4.00	kN			
Ejecting Force High Limit :		4.00	kN			
				Stop Condition ;		
HSP :	30.0 %	28.29	kN	No		
HEP :	25.0 %	27.21	kN	Yes 10	Rotations 15	Tablets
HCP :	2.0 %	22.20	kN	Yes 15	Times	
Ref :		21.76	kN			
LCP :	2.0 %	21.33	kN	Yes 15	Times	
LEP :	25.0 %	16.32	kN	Yes 10	Rotations 15	Tablets
LSP :	30.0 %	15.23	kN	No		
SD limit :	35.0 %			Yes		
Pre HSP		30.00	kN	Yes		
Mean Calculation range :	2 Rotations			Calculation Pass :	2	Rotations
Empty Punch No. :	N					

Pressure Data

Mean Pre Pressure :	SD :	2.97	kN	Min :	2.31	kN	Punch NO.;	43
		9.00	%	Max :	3.56	kN	Punch NO.;	32
Mean Main Pressure :		21.52	kN	Min :	19.62	kN	Punch NO.;	43
	SD :	3.90	%	Max :	23.36	kN	Punch NO.;	37
Filling Depth :	Increase ;	85	Times	Decrease ;	90	Times		

PRODUCTION REPORT

Operation Value

Disk Speed :	15	RPM	Capacity :	95400	Tablets/hour
Feeder : Status ;	Auto		Speed ;	19	RPM
Pre Upper Punch Position ;	2.20	mm			
Pre Lower Punch Position ;	3.40	mm	Pre Thickness ;	1.20	mm
Main Upper Punch Position ;	2.80	mm			
Main Lower Punch Position ;	3.40	mm	Main Thickness ;	0.60	mm
Filling Depth :	6.94	mm	Current Cam :	Cam B	
Main Air pressure :	0.814	MPa		4.5-10mm	
Oil Lubrication status :					
Upper Punch Remain Time (S1):	46	Min			
Lower Punch Remain Time (S2):	17	Min			
Lower Head Remain Time (S3):	0	Min			
Powder Status :	Disable		Dust Collector :	Off	
Initial Reject :	Off		Buzzer :	Off	

Tightness

Upper Punch :	Average ;	0.12	kN		
	Max ;	0.18	kN	Max Punch ;	1
Lower Punch :	Average ;	0.15	kN		
	Max ;	0.19	kN	Max Punch ;	2
Ejection Force :	Average ;	0.03	kN		
	Max ;	0.05	kN	Max Punch ;	3

Tablet Data (N/A)

Total Counter :	509780	Tablets			
A.W.C Counter :	506899	Tablets			
HEP :	404 (0.1%)	Tablets	LEP :	190 (0.0%)	Tablets
GOOD :	506305 (99.9%)	Tablets			