# ABNAHMEPRÜFZEUGNIS INSPECTION CERTIFICATE

EN 10204-3.1

Cert. No.: 227100 / 2017.11.28

Blatt/Sheet/Page: 1 / 4

ISO 9001:2015 certification EN 9100:2016 certification EN ISO 14001:2015 certification



MARIAZELLERSTRASSE 25 8605 KAPFENBERG/AUSTRIA

Besteller/Purchaser/Acheteur:

BOHLER Pacific Pte. Ltd. 25, Pioneer Crescent SG-628554 Singapore

Singapore

Bestell-Nr./Purchaser order No./No. de commande:

8080000916 / 2017.05.15

Werksauftrags-Nr./Works order-No./No. de la commande de l'usine:

2114723 / 2017.05.15

Prüfgegenstand/Object of test/Object d'examen:

BÖHLER LHX, 2.4665 bar, rolled, solution annealed IBO ECOMAX, ISO 286/2 ITk12 Application: Aviation/Space Ind. Empfänger/Consignee/Destinaire:

BOHLER Pacific Pte. Ltd. 25, Pioneer Crescent SG-628554 Singapore

Singapore

**Empfängerref.-Nr.**/Receiver reference-No./Rèfèrence destinaire:

-

**Lieferschein-Nr.**/Delivery note-No./Avisd'expedition du client:

51471361 / 2017.11.17

Anforderungen/Requirements/Exigence:

AMS 5754M ASTM B572 Issue 06 UNS N06002

GE S400 Issue 03-Jun-16 GE S1000 Issue 23-May-17

Volume of delivery

Pos./Los	Dimensions	Length	No. of Pieces	Weight kgs	MatID	Test No.	Heat No.
10/1	RD 63,5 MM	3.000 - 4.000 MM	15	1510,0	T4T3	1631098-1	C48028

Ingot size = rd. 424 mm (16,7 inch)

Reduction ratio = 41:1

Quality heat treatment

Temperature Soak time Cooling

1170°C 0:45 h M Water

Solution annealed

Pyrometry acc.to AMS 2750E

M...holding time at nominal temperature after center of material has reached the tolerance limit.

# voestalpine Specialty Metals Pte Ltd

The delivery mentioned below was taken out of the material specified in this mill certificate

Quantity/Weight

211-736Kgs

Customer:

Materials One M

PO Number:

M-VSM/081019

Signature / Date:

Jor 17/10/2019

**CERTIFIED TRUE COPY** 

# ABNAHMEPRÜFZEUGNIS INSPECTION CERTIFICATE

EN 10204-3.1

Cert. No.: 227100 / 2017.11.28

Blatt/Sheet/Page:2 / 4

ISO 9001:2015 certification EN 9100:2016 certification EN ISO 14001:2015 certification



MARIAZELLERSTRASSE 25 8605 KAPFENBERG/AUSTRIA

Chemical Steelmaking	Composition Process: VII	n M+ESR								Heat No.
C 0,061	Si 0,09	Mn 0,02	P <0,005	S 0,0004	Cr 21,58	Mo 8,36	Ni 50,8	V 0,03	W 0,50	C48028
Cu <0,02	Co 0,83	Ti 0,02	AI 0,16	B <0,001	Fe 17,53	Zr 0,010				C48028

Si, Mn, P, Cr, Mo, Ni, Cu, Co, Ti, Al, Nb, Fe, Ta, Zr	XRF
C, S	CS Combustion analysis
В	Spark optical emission spectrometer

Country of origin and melt: AUSTRIA

Name of melt source: Böhler Edelstahl GmbH & Co KG

#### Metallographic examination

### Macro etch examination

Testing standard = ASTM A 604/A 604M - 07 Etch media = 1/3 H2O2 (35%) + 2/3 HCI (25-38%)

Class 1 Severity A

Class 2 Severity A

Class 3 Severity A

Class 4 Severity A

## Non metallic inclusions

Non metallic inclusions acc.to ASTM E45-13 method A

	А		В		С		D	
Test no.	thin	heavy	thin	heavy	thin	heavy	thin	heavy
S	-	-	-	-	-	-	1	-
SM	-	-	-	-	-	-	1	-
В	-	-	-	-	-	-	1	-

## **Grain Size Evaluation**

Testing standard = ASTM E112-13, ASTM E960-99 Etch media = H2O 100ml, HCI 300ml, H2O2 15ml

Magnification = 50:1, 100:1, 500:1

Structure type

Direction

Rim

Midradius

Center

Duplex ALA

Iongitudinal

ASTM No. 2.5

ASTM No. 3

ASTM No. 2

ALA ASTM No. >00

ALA ASTM No. 0

ALA ASTM No. >00

# **CERTIFIED TRUE COPY**

# ABNAHMEPRÜFZEUGNIS INSPECTION CERTIFICATE

EN 10204-3.1

Cert. No.: 227100 / 2017.11.28

Blatt/Sheet/Page:3 / 4

ISO 9001:2015 certification EN 9100:2016 certification EN ISO 14001:2015 certification



MARIAZELLERSTRASSE 25 8605 KAPFENBERG/AUSTRIA

# **Mechanical Properties**

The orientation of the tensile test specimen is longitudinal and transverse. L2 = longitudinal, l/2 = longin, l/2 = longitudinal, l/2 = longitudinal, l/2 = longitudin

Tensile test in delivery condition

<b>*Key</b> H = hardest <b>W</b> = softest	M =	= Top = Middle = Bottom			Yield Strength	Ultimate Tensile Strength	Elongation	Reduction of Area
Test no.	*Piece no.	Testing standard	Location	Temp.	YS0.2	UTS	A4	RoA
100(110)	1 1000 1101	rooting ottinuara	Location	grd C	MPa	MPa	%	%
					>=240	>=660	>=35	info.
1631098-1	6B	ASTM E 8/E8M- 16a 01.09.2016	L2	23	273	701	62	58
					>=240	>=660	>=35	info.
1631098-1	6B	ASTM E 8/E8M- 16a 01.09.2016	QZ	23	299	720	58	57

Hardness test in delivery condition

Test no.	Piece no.	Testing standard	Location	HBW 5/750
				<=241

1631098-1

ASTM E10-15a Type A

Stäbe / bars

152-153

The orientation of the stress rupture test specimen is longitudinal. L2 = longitudinal, 1/2 Radius (1/4T)

Stress rupture test in delivery condition

		•			Load	Test duration	Reduction of area after rupture	Elongation after
Test no.	Piece no.	Testing standard	Location	Temp.		Т	Z	A4
100(110.	1 1000 1101	robang bandara	Location	grd C	MD-	h	%	%
					MPa			
					103	>=24	info.	>=10
1631098-1	6B	ASTM E 139-11 01.08.2011	L2	816	103	33,9	59	64

# **ABNAHMEPRÜFZEUGNIS** INSPECTION CERTIFICATE EN 10204-3.1

ISO 9001:2015 certification EN 9100:2016 certification EN ISO 14001:2015 certification



MARIAZELLERSTRASSE 25 8605 KAPFENBERG/AUSTRIA

Cert. No.: 227100 / 2017.11.28

Blatt/Sheet/Page:4 / 4

#### Nondestructive examination

Material identification test (Spectrographic analysis) acc.to internal bohler standard: Positive material identification

100% Ultrasonic test acc. to AMS STD 2154 Rev. A 2012-10 Type I using Phased Array The material fulfils quality class A.

100% Surface Inspection acc.to DIN EN 10277-1:2008 An Eddy Current test was performed. The material fulfils quality class 4.

#### Statements

The material is free of mercury, free of mercury compounts and or radium contamination at time of shipment, material produced without ozone deplating substances.

No weld repair has been performed on this material.

### Radioaktivitätskontrolle/Radioactivity inspection: Co-60<0,1Bq/g;

hiermit kleiner als Grenzwert in der anzuwendenden Spezifikation IAEA RS-G-1.7 für unbedenkliche Stoffe. therefore smaller than upper limit required according to specification IAEA RS-G-1.7 for inoffensive material.

Das Material wurde hergestellt, erprobt, überprüft und geprüft in Übereinstimmung mit der Kundenbestellung und den referenzierten Spezifikationen und erfüllt die Anforderungen, sofern nicht anders in diesem Abnahmezeugnis angegeben. Ohne schriftliche Genehmigung der Böhler Edelstahl GmbH & Co KG darf dieses Zeugnis, außer im Ganzen, nicht vervielfältigt werden. Die Aufzeichnung von falschen, fingierten oder betrügerischen Erklärungen oder Eintragungen auf diesem Dokument, kann gemäß österreichischem Recht (Strafgesetzbuch §223ff) bestraft werden.

Material has been produced, sampled, inspected and tested in accordance with the customer purchase order and referenced specifications and conforms to the requirements unless otherwise noted in this inspection certificate. The certificate shall not be reproduced, except in full, without the written approval of Böhler Edelstahl GmbH & Co KG.The recording of false, fictions or fraudulent statements or entries on the document may be punished by Austrian law(Austrian Penal Code 223ff).

Wir bestätigen hiermit, dass die obengenannten Erzeugnisse den Bestellvorschriften entsprechen. We hereby certify that the above mentioned products are consistent with the order prescriptions. Nous certifions que les produits enumeres ci-dessus sont conformes aux prescriptions de la commande.

Zeichen des Lieferwerks: Brand of Manufacturer: Marques de l'usine:



Besichtigung und Nachmessung: Keine Beanstandung Inspection and Checking of Dimensions: Satisfactory Inspection of Control des dimensions: Satisfaisant

Zeichen des Prüfers: Symbol of Inspector: Symbole de l'inspecteur:



**BOHLER Edelstahl GmbH & Co KG** 

Mariazellerstrasse 25 8605 Kapfenberg, AUSTRIA www.bohler-edelstahl.com alexander.wagner@bohler-edelstahl.at





# Certificate of Conformance voestalpine

ONE STEP AHEAD.

BPAC COC	19/65500000011636	Rev.No.	00
Heat Number	C48028	Customer	REG - VIETNAM ::
Cert No	227100	Customer PO	SM-VSM/081019
Test No.	1631098-1	PO line Item	1
Customer trace nr.	NA		
Material Spec	ALLOY X AMS 5754		
QTY	4.000	Raw Size	DIA 63.50MM X LG 2500MM
Hardness	153.00 HBW		
Heat Treatment:	SOLUTION ANNEALED 117	0°C 0:45 H M WATE	ER
MATL No.	NA	Production Orde	r Number NA
Part No	NA		
This Material meets the sp	ecification of ALLOY X AMS 57	754.	,
	16/:	10/2019	

This certificate shall not reproduced except in full, without the written approval of voestalpine Specialty Metals Pte Ltd.

Name: Title: Martin Jarad

Quality / HSE Manager