



MASTERSCAN ENGINEERING

INSPECTION WITH INTEGRITY

+65 6261 4766 +65 6261 4768 www.masterscan.com.sg sales@masterscan.com.sg
GST/Co. Reg. No.: 200506867D 29 Benoi Road, Pioneer Lot, Singapore 629922



REPORT NO : MSE/SEK/EM/PT/F-031

MSE/REF/NO : D2-26-2919

TESTED DATE : 16.04.2026

PAGE : 1 OF 3

LIQUID PENETRANT TEST REPORT

OWNER : EXXON MOBIL
CLIENT : SIN EE KIANG ENGINEERING & CONSTRUCTION PTE LTD
LOCATION : PDU SITE
PROJECT NAME : PAC TA 2026
JOB NO : PDU PIPING
REQUEST NO : PT-F-56
ITEM TESTED : SURFACE PREPARATION & WELDED JOINTS
TEST PROCEDURE : MSE-TP-PT-006; Rev.8
ACCEPTANCE SPEC : ASME B 31.3 – 2024 Ed./ Clause 344.4.2:

TEST METHOD : VISIBLE COLOUR CONTRAST METHOD/ SOLVENT REMOVABLE
SURFACE CONDITION : AS SMOOTH , WELDED AND CLEANED
SURFACE TEMPERATURE : TEMPERATURE (25 - 35 °C)
MATERIAL : SS316L
TYPE OF PENETRANT : RED DYE PENETRANT / MR 62 (Lot No : 2207026)
METHOD OF APPLICATION : BRUSHING
REMOVER / CLEANER : CLEANER / REMOVER / MR 79 (Lot No : 2411046)
DWELLING TIME : 15 MINUTES
DEVELOPER : DEVELOPER / MR 70I (Lot No : 2407089)
DEVELOPING TIME : 10 MINUTES
LIGHT SOURCE INTENSITY : NATURAL LIGHT > 1080 Lux
LIGHT METER SERIAL NO : P20008686

SCOPE OF EXAMINATION : LIQUID PENETRANT TESTING WAS CARRIED OUT ON SURFACE PREPARATION & WELDED JOINTS
FINDINGS : For more details, pls. refer to the attached data sheets
NO RELEVANT INDICATIONS WERE DETECTED AT THE TIME OF TESTING
ITEM TESTED WERE FOUND COMPLIED TO SPECIFICATION.
RESULT : ACCEPTABLE

Tested By :
A.UDHAYANITHI
NDT LEVEL II



SIGNATURE
DATE : 16.04.2026

Reviewed by :
SURENDRAKUMAR P.V
ASNT NDT LEVEL III



SIGNATURE
DATE : 17.04.2026

Reviewed / Witness by :

SIGNATURE
DATE :

Reviewed / Witness by :

SIGNATURE
DATE :

FORM NO : MSE/NDT/PT/001 Rev.2A

The report is issued under the following terms and conditions:

- The report shall not be reproduced in part or in full unless approved in writing has been given by MASTERSCAN ENGINEERING.
- The report shall not be used in any publicity material without the written consent of MASTERSCAN ENGINEERING.
- MASTERSCAN ENGINEERING agrees to use reasonable diligence in the manner of performing the tests, inspections or services but no warrants are given, and none may be implied directly or indirectly relating to MASTERSCAN ENGINEERING test results, services or facilities
- MASTERSCAN ENGINEERING shall under no circumstances be liable for collateral, special or consequential damage.
- This is a test report and not a MASTERSCAN certificate of quality. The significance of the report is subject to the adequacy and representative character of the sample(s) and to the comprehensiveness of the tests, examinations or survey requested or made.
- The test report is prepared based on the test(s) requested and on the specific items submitted / sampled to MASTERSCAN ENGINEERING for testing. MASTERSCAN ENGINEERING assumes no responsibility for variations in quality or other characteristics of product produced on supplied under conditions over which MASTERSCAN ENGINEERING has no control. MASTERSCAN ENGINEERING'S testing does not constitute a recommendation for, or endorsement of the product or material tested.
- The results reported herein have been performed in accordance with the terms of accreditation under the singapore accreditation council



MASTERSCAN ENGINEERING

INSPECTION WITH INTEGRITY



+65 6261 4766 +65 6261 4768 www.masterscan.com.sg sales@masterscan.com.sg
GST/Co. Reg. No.: 200506867D 29 Benoi Road, Pioneer Lot, Singapore 629922

LIQUID PENETRANT TEST REPORT

REPORT NO : MSE/SEK/EM/PT/F-031

PAGE : 2 OF 3

S/N	TAID NO.	LINE NO.	JOINT No	SIZE	SCH (THK)	WELDER NO.		WELDING PROCESS	WPS NO	WELD TYPE	MAT'L	Distance from Reference Point (mm)	Type of Indication	RESULT	REMARKS
						ROOT	CAPPING								
1	1P0245	3/4"-33-0-0504-AG5	6	3/4	80	-	-	GTAW	WPS-003	SW	SS316L	-	-	ACCEPTABLE	SURFACE & ROOT PT

Tested and Reported By :
A.UDHAYANITHI
MSE NDT Level II

Reviewed by:
SURENDRAKUMAR P.V
ASNT NDT Level III

Reviewed by :

Reviewed by :



SIGNATURE
DATE : 16.04.2026

SIGNATURE
DATE : 17.04.2026

SIGNATURE
DATE :

SIGNATURE
DATE :

The report is issued under the following terms and conditions:

- The report shall not be reproduced in part or in full unless approved in writing has been given by MASTERSCAN ENGINEERING.
- The report shall not be used in any publicity material without the written consent of MASTERSCAN ENGINEERING.
- MASTERSCAN ENGINEERING agrees to use reasonable diligence in the manner of performing the tests, inspections or services but no warrants are given, and none may be implied directly or indirectly relating to MASTERSCAN ENGINEERING test results, services or facilities
- MASTERSCAN ENGINEERING shall under no circumstances be liable for collateral, special or consequential damage.
- This is a test report and not a MASTERSCAN certificate of quality. The significance of the report is subject to the adequacy and representative character of the sample(s) and to the comprehensiveness of the tests, examinations or survey requested or made.
- The test report is prepared based on the test(s) requested and on the specific items submitted / sampled to MASTERSCAN ENGINEERING for testing. MASTERSCAN ENGINEERING assumes no responsibility for variations in quality or other characteristics of product produced on supplied under conditions over which MASTERSCAN ENGINEERING has no control. MASTERSCAN ENGINEERING'S testing does not constitute a recommendation for, or endorsement of the product or material tested.

7 The results reported herein have been performed in accordance with the terms of accreditation under the singapore accreditation council

LIQUID PENETRANT TEST REPORT

REPORT NO : MSE/SEK/EM/PT/F-031

PAGE : 3 OF 3



The report is issued under the following terms and conditions:

1. The report shall not be reproduced in part or in full unless approved in writing has been given by MASTERSCAN ENGINEERING.
2. The report shall not be used in any publicity material without the written consent of MASTERSCAN ENGINEERING.
3. MASTERSCAN ENGINEERING agrees to use reasonable diligence in the manner of performing the tests, inspections or services but no warrants are given, and none may be implied directly or indirectly relating to MASTERSCAN ENGINEERING test results, services or facilities
4. MASTERSCAN ENGINEERING shall under no circumstances be liable for collateral, special or consequential damage.
5. This is a test report and not a MASTERSCAN certificate of quality. The significance of the report is subject to the adequacy and representative character of the sample(s) and to the comprehensiveness of the tests, examinations or survey requested or made.
6. The test report is prepared based on the test(s) requested and on the specific items submitted / sampled to MASTERSCAN ENGINEERING for testing. MASTERSCAN ENGINEERING assumes no responsibility for variations in quality or other characteristics of product produced on supplied under conditions over which MASTERSCAN ENGINEERING has no control. MASTERSCAN ENGINEERING'S testing does not constitute a recommendation for, or endorsement of the product or material tested.