ResearchGate

See discussions, stats, and author profiles for this publication at: https://www.researchgate.net/publication/348759759

Advanced composite in aerospace application: A review on future aspect of fiber-reinforced polymer (frp) in aerospace industry

Conference Paper · January 2021

CITATIONS
4

READS
3,454

4 authors, including:

S. M. Sapuan
Universiti Putra Malaysia
1,175 PUBLICATIONS **51,576** CITATIONS

SEE PROFILE

Ilyas R.A.
University of Technology Malaysia
647 PUBLICATIONS **22,498** CITATIONS

SEE PROFILE

Muhammad Hariz Bin Hassim
Universiti Putra Malaysia
1 PUBLICATION **4** CITATIONS

SEE PROFILE

All content following this page was uploaded by Muhammad Hariz Bin Hassim on 26 January 2021.

The user has requested enhancement of the downloaded file.

ADVANCED COMPOSITE IN AEROSPACE APPLICATION: A REVIEW ON FUTURE ASPECT OF FIBER-REINFORCED POLYMER (FRP) IN AEROSPACE INDUSTRY

H.M. Hariz[1], S.M. Sapuan[1,2]*, R.A. Ilyas[3,4]

[1]*Department of Mechanical and Manufacturing Engineering, Faculty of Engineering, Universiti Putra Malaysia, 43400 UPM Serdang, Selangor, Malaysia*
[2]*Laboratory of Biocomposite Technology, Institute of Tropical Forestry and Forest Products (INTROP), Universiti Putra Malaysia, 43400 UPM Serdang, Selangor, Malaysia*
[3]*Sustainable Waste Management Research Group (SWAM), School of Chemical and Energy Engineering, Faculty of Engineering, Universiti Teknologi Malaysia, 81310 UTM Johor Bahru, Johor, Malaysia*
[4]*Centre for Advanced Composite Materials (CACM), Universiti Teknologi Malaysia, 81310 UTM Johor Bahru, Johor, Malaysia*
*Corresponding's author email: sapuan@upm.edu.my

ABSTRACT

Carbon fiber-reinforced polymers (CFRPs) have attracted attention from the aerospace industry because of their lightweight, excellent mechanical properties and corrosion resistance. Supported these considerations and the experience obtained up to now with Fiber-fortified polymers (FRPs) in primary aircraft structures and also the potential field of further development of fiber composite technology are explained. It is concluded that a composite technology approach, within which Fiber-fortified polymers (FRPs) are to create a tailored structural material, can cause significant weight reduction in future structural applications.

Keywords: fiber-reinforced polymer (FRP), mechanical properties, carbon fiber, aerospace application.

INTRODUCTION

Aircraft makers have several valid reasons for using composites and airline companies would like composites to be utilized in their industry. Several composite materials come through comparatively more significant strength characteristics than old metal [1]–[7]. The composite material can reduce craft weight and also reducing fuel value per rider carried. Composites are more resistant than metal to fatigue from continual take-off or landing cycles, resulting in fewer pricey inspections over the aircraft's life and longer spent inside the air creating cash. To date, several studies have investigated the model of long fiber composites for aeronautical components. A study conducted by Santiuste et al on composites of long fiber reinforced polymer (LFRP) has already been used widely in engineering structures. On the other hand, the nature of the composite, normally thin-walled, distorts the tests' performance regularly led at low cutting velocities achieved after a mind complex machine-device situating procedure, for example, studies based on orthogonal glass and carbon FRP composite cutting. Fiber failure causes each longitudinal and shear modulus degradation, and matrix failure creates transversal and shear modulus degradation [8]. Furthermore, harm initiation corresponds to the start of decay at the fabric point and is employed to anticipate breakdown and the corresponding elimination of the broken section. Considering all of this evidence, it seems that both initiation and complete chip formation were demonstrated by the acquisition of cutting force and subsurface damage. Machining brought subsurface destruction was substantially decreased the fragile composites (CFRPs) than for ductile composites (GFRPs). This is often a vast advantage of CFRPs against GFRPs, considering the high responsibility of CFRP structural elements for aeronautic applications.

FUTURE PERSPECTIVE OF FIBER-REINFORCED POLYMER IN AEROSPACE APPLICATION

Fiber-reinforced polymers (FRPs) are the composite materials most broadly utilized in aviation structures. For example, their particular properties, superior, lightweight, higher firmness and improved corrosion resistance make them an appealing selection for aeronautic applications [9], [10]. It is an incredibly compact and durable fiber-reinforced polymer that incorporates carbon fiber [11], [12]. The reinforcement fibers are typically stiff, tight and strongly distributed in the composite phases of the matrix. The reinforcement is also the critical load-bearing factor since, in the event of single fiber breakage, the load can be transferred to other nearby fibers via the matrix. FRPs

ISBN: 978-983-44426-9-9

contain carbon fiber-reinforced polymers (CFRPs), glass fiber-reinforced polymers (GFRPs) and aramid fibers, as shown in Fig. 1. CFRPs are being used in high-tech applications. GFRP with typical E-glass (electrical) and S-glass (high Strength) also has excellent properties.



Fig. 1 : Components made of FRPs used in airbus [13]

Many studies have begun to examine the future perspective of advanced composite in aerospace applications. Hofstätter et al stated in their research on the current state-of-the-art in fiber-reinforced polymers (FRPs) in additive manufacturing (AM), shows FRP characteristics and their effect on composite materials. Carbon nanotube was tested for UV-curable resin in a mixture of carbon nanotubes with a weight ratio of 0.1 to 5 percent [14]. Having followed the swelling process that requires N, N-dimethylacetamide (DMAc) comprising lithium chloride (LiCl), the whiskers were blended with PLA-melt during the extrusion process, producing an all-biodegradable composite material with greater strength by 20 percent and Young's modulus by 10 percent with a fiber content of 5 percent. The evidence suggests that existing approaches for additively produced FRPs are uncommon. Many ancient applications utilize short and long fibers embedded in a very compound matrix, like part, automobile, wind and medicine engineering.

TABLE 1: Reported work on type of composite in aerospace

Type of composite	Characteristics	Effect of Reinforcement	Reference
Carbon nanotubes	Impact and delamination failure	High specific strength and stiffness	[15]
Fiber reinforced polymers	Shear behaviour	Provide rapid estimates of ply rigidity and toughness	[16]
Carbon fiber	Strength	Significantly improve the ultimate strength of surface bonded	[17]

Researchers attempted to evaluate the future perspective of advanced composite in aerospace applications. In a study experimented by Alderliesten & Benedictus on fiber/metal composite technology for future primary aircraft structures, it was confirmed that the latest developments in the aviation industry indicate a growing need for lower operating and maintenance costs [18]. This transitions into aircraft with longer style life, longer maintenance times, and shorter period maintenance. Despite the attempts being made towards integrated vehicle health management systems, the key to overcoming these strict laws is acknowledging these factors from an initial purpose within the structural style and material choice method. High strength and firmness composite materials, including carbon fiber reinforced polymers (CFRP), demonstrate failure strains below 2 % without ductility. Overall, these studies indicate the production of potential structural materials for region applications remains further research, considering the possibilities for integrating the different metallic and composite engineering materials.

ISBN: 978-983-44426-9-9

CONCLUSIONS

To conclude, the development of future structural materials for aerospace applications still contains a long way to go. Thanks to composite materials' potential, Fiber-reinforced polymers (FRPs) composite technology should be further explored to identify the potential combinations and material characteristics with respect to potential applications. Developing full composite structures because everybody believes the future is black does not testify to a strategic vision on future structures. Engineers and designers should be aware of fiber-reinforced polymers' large potential. Particularly in primary craft structures, wherever the design is determined by fatigue and damage tolerance aspects.

REFERENCES

[1] N. M. Nurazzi, A. Khalina, S. M. Sapuan, R. A. Ilyas, S. A. Rafiqah, and Z. M. Hanafee, "Thermal properties of treated sugar palm yarn/glass fiber reinforced unsaturated polyester hybrid composites," *J. Mater. Res. Technol.*, vol. 9, no. 2, pp. 1606–1618, 2020, doi: 10.1016/j.jmrt.2019.11.086.

[2] M. N. Norizan, K. Abdan, R. A. Ilyas, and S. P. Biofibers, "Effect of fiber orientation and fiber loading on the mechanical and thermal properties of sugar palm yarn fiber reinforced unsaturated polyester resin composites," *Polimery*, vol. 65, no. 2, pp. 34–43, 2020, doi: 10.14314/polimery.2020.2.5.

[3] R. A. Ilyas and S. M. Sapuan, "Biopolymers and Biocomposites: Chemistry and Technology," *Curr. Anal. Chem.*, vol. 16, no. 5, pp. 500–503, Jul. 2020, doi: 10.2174/1573411016052006030953 11.

[4] R. A. Ilyas and S. M. Sapuan, "The Preparation Methods and Processing of Natural Fibre Bio-polymer Composites," *Curr. Org. Synth.*, vol. 16, no. 8, pp. 1068–1070, Jan. 2020, doi: 10.2174/1570179416082001210 5616.

[5] F. A. Sabaruddin *et al.*, "The Effects of Unbleached and Bleached Nanocellulose on the Thermal and Flammability of Polypropylene-Reinforced Kenaf Core Hybrid Polymer Bionanocomposites," *Polymers (Basel).*, vol. 13, no. 1, p. 116, Dec. 2020, doi: 10.3390/polym13010116.

[6] S. M. Sapuan *et al.*, "Mechanical properties of longitudinal basalt/woven-glass-fiber-reinforced unsaturated polyester-resin hybrid composites," *Polymers (Basel).*, vol. 12, no. 10, 2020, doi: 10.3390/polym12102211.

[7] A. A. B. Omran *et al.*, "Micro- and Nanocellulose in Polymer Composite Materials: A Review," *Polymers (Basel).*, vol. 13, no. 2, p. 231, Jan. 2021, doi: 10.3390/polym13020231.

[8] C. Santiuste, X. Soldani, and M. H. Miguélez, "Machining FEM model of long fiber composites for aeronautical components," *Compos. Struct.*, vol. 92, no. 3, pp. 691–698, 2010, doi: 10.1016/j.compstruct.2009.09.021.

[9] M. Aamir, M. Tolouei-Rad, K. Giasin, and A. Nosrati, "Recent advances in drilling of carbon fiber–reinforced polymers for aerospace applications: a review," *Int. J. Adv. Manuf. Technol.*, vol. 105, no. 5–6, pp. 2289–2308, 2019, doi: 10.1007/s00170-019-04348-z.

[10] R. A. Ilyas *et al.*, "Potential of natural fibre composites for transport industry : A review," in *Prosiding Seminar Enau Kebangsaan 2019*, 2019, pp. 2–11.

[11] M. Maria, "Advanced composite materials of the future in aerospace industry," *Incas Bull.*, vol. 5, no. 3, pp. 139–150, 2013, doi: 10.13111/2066-8201.2013.5.3.14.

[12] H. A. Aisyah *et al.*, "Thermal Properties of Woven Kenaf/Carbon Fibre-Reinforced Epoxy Hybrid Composite Panels," *Int. J. Polym. Sci.*, vol. 2019, pp. 1–8, Dec. 2019, doi: 10.1155/2019/5258621.

[13] A. P. Mouritz, *Introduction to aerospace materials*. Woodhead Publishing Limited, 2012.

[14] T. Hofstätter, D. B. Pedersen, G. Tosello, and H. N. Hansen, "State-of-the-art of fiber-reinforced polymers in additive manufacturing technologies," *J. Reinf. Plast. Compos.*, vol. 36, no. 15, pp. 1061–1073, 2017, doi: 10.1177/0731684417695648.

[15] S. U. Khan and J. K. Kim, "Impact and delamination failure of multiscale carbon nanotube-fiber reinforced polymer composites: A review," *Int. J. Aeronaut. Sp. Sci.*, vol. 12, no. 2, pp. 115–133, 2011, doi: 10.5139/IJASS.2011.12.2.115.

[16] F. Naya, C. González, C. S. Lopes, S. Van der Veen, and F. Pons, "Computational micromechanics of the transverse and shear behavior of unidirectional fiber reinforced polymers including environmental effects," *Compos. Part A Appl. Sci. Manuf.*, vol. 92, pp. 146–157, 2017, doi: 10.1016/j.compositesa.2016.06.018.

[17] U. S. Camli and B. Binici, "Strength of carbon fiber reinforced polymers bonded to concrete and masonry," *Constr. Build. Mater.*, vol. 21, no. 7, pp. 1431–1446, 2007, doi: 10.1016/j.conbuildmat.2006.07.003.

[18] R. C. Alderliesten and R. Benedictus, "Fiber/metal composite technology for future primary aircraft structures," *J. Aircr.*, vol. 45, no. 4, pp. 1182–1189, 2008, doi: 10.2514/1.33946.

ISBN: 978-983-44426-9-9

View publication stats