PFAS defluorination using CeO2/Ti-plated Cu electrodes

"I am trying to find a way to defluorinate PFAS in an affordable, efficient and feasible way. As of now CeO2/Ti-plated Cu electrode is the best option as far as %Defluorination, Anodic Voltage vs SHE and Energy Consumption is concerned (73%, -1.37V and <0.62 kWh/m^3/order respectively). The major drawback of this method is that it causes nanoparticletoxicity, lacks scalability and needs mitigation. Explain what causes this toxicity and how can we potentially fix it?" *Generated by LeapSpace*

CeO2/Ti-Plated Cu Electrodes for PFAS Defluorination at a Glance

Key Findings Table

Key finding	What it means for your system	Relevant population/system	Citations
The likely hazard is multi-source: particles, dissolved metals, and residual fluorinated byproducts	"Nanoparticle toxicity" is too narrow; treated water may remain hazardous even if PFAS concentration falls	CeO2/Cu-containing PFAS electrochemical systems and analogous water-treatment contexts	[1] [2] [3] [4] [5] [6] [7]
Fluoride released during defluorination can damage oxide/Ti materials	The treatment process can self-degrade the electrode, increasing shedding and leaching risk over time	Ti- and oxide-based PFAS destruction systems	[8] [9] [10]
CeO2's active chemistry is also a stability risk	Oxygen vacancies and Ce3+/Ce4+ cycling help C-F cleavage, but defect-rich surfaces are chemically labile	CeO2 surfaces and ceria-metal interfaces	[12] [13] [14] [15]
Direct proof for CeO2/Ti-plated Cu-specific shedding + toxicity partitioning is sparse	The mechanism for your exact electrode is still an evidence-based inference, not directly proven in one study	CeO2 PFAS electrode literature	[16] [18] [19]
Water chemistry strongly controls release behavior	pH, ionic strength, Ca2+, NOM, and chloride can change agglomeration, mobility, and dissolved-metal release	Nanoparticles in realistic water matrices	[1] [20] [21] [22] [23]

Key finding	What it means for your system	Relevant population/system	Citations
The most practical mitigation path is immobilization + treatment-train integration	Keep active ceria fixed on a support, treat concentrated PFAS streams, and polish effluent before discharge	PFAS treatment system design	[24] [25] [26] [27] [28]
For scale-up, continuous-flow durability matters more than one-batch performance	A slightly lower-defluorination but stable, low-leaching flow system may be safer and more deployable	Flow PFAS reactors, especially Ti4O7/gas-diffusion systems	[29] [30] [31]

Direct Answer

The most plausible reason your CeO2/Ti-plated Cu electrode appears “toxic” is that the hazard likely comes from **three overlapping sources**, not one: **(1) released CeO2/Cu-containing particles**, **(2) dissolved Ce or Cu ions from corrosion/dissolution**, and **(3) incompletely defluorinated PFAS fragments or short-chain products that remain biologically active** [1] [2] [3] [6] [7].

The likely root cause tying these together is **fluoride-driven degradation**. As PFAS defluorinate, released fluoride can attack oxide and Ti-based surfaces, causing passivation, etching, and even structural collapse; that degradation can then accelerate particle shedding and metal release [8] [9] [10].

Why this happens specifically with ceria is mechanistically consistent with why ceria works so well. **Ce3+/Ce4+ redox cycling, oxygen vacancies, and ceria-metal interfacial sites** help adsorb PFAS and lower the barrier for C-F cleavage at relatively low potential, but those same defect-rich sites are chemically dynamic and may be easier to restructure, fluorinate, or partially dissolve during operation [12] [13] [14] [15].

The best fix is probably **not a single material tweak**, but a **multi-barrier redesign**:

1. **Immobilize ceria more strongly** on a porous, magnetic, or ceramic host rather than relying on weakly bound nanoparticulate coatings [24] [25] [32].
2. **Use continuous-flow architectures with physical retention** rather than open batch-style exposure, and consider polarity reversal to reduce aging/fouling [33] [34] [35].
3. **Treat PFAS concentrates instead of whole water**, using upstream foam fractionation, ion exchange, or NF/RO to reduce volume and simplify containment [26] [28] [36] [37].
4. **Add post-reactor polishing** such as ultrafiltration/adsorption to capture released particles and residual PFAS fragments before discharge [26] [27] [28].

5. If safety and scale matter more than the last increment of batch performance, consider **more mature continuous-flow alternatives**, especially Ti4O7 plus gas-diffusion architectures, which have stronger durability/leaching reporting in the supplied evidence [29] [30] [31].

Confidence level: Medium-High — the overall mechanism is strongly supported across adjacent evidence streams, but direct CeO2/Ti-plated Cu toxicity-partition studies are lacking [16] [18].

Study Scope

This report synthesizes supplied evidence on PFAS electrochemical destruction, CeO2 surface chemistry, nanoparticle fate, reactor engineering, and treatment-train integration, mainly from recent mechanistic, reactor, and review literature spanning roughly 2018-2026 and focused on water-treatment and environmental toxicology contexts [12] [31] [32] [38].

Assumptions & Limitations

- The supplied evidence does **not** include a study that directly quantifies **CeO2/Ti-plated Cu nanoparticle shedding, dissolved Ce/Cu release, and effluent toxicity partitioning in the same experiment**, so parts of the mechanism are inferred from closely related evidence rather than directly demonstrated for your exact configuration [16] [18].
- Performance maturity currently exceeds safety-characterization maturity in this literature base [16] [19].

Suggested Further Research

- Run a **three-fraction toxicity workflow**: whole effluent, dissolved fraction, and retained particulate fraction, paired with ICP-MS/DLS/TEM and bioassays [18] [39] [40].
- Perform **postmortem surface analysis** after PFAS treatment to verify fluorination, vacancy loss, passivation, or collapse using XPS/TEM/Raman/SEM-EDX [19] [41] [42].
- Test **anti-release architectures**: ceramic encapsulation, porous hosts, magnetic recovery, membrane-integrated capture, and stronger binders [24] [25] [26].
- Generate **long-duration continuous-flow data** that report defluorination, fluoride balance, energy, leaching, and lifetime together [29] [43].
- Compare CeO2/Ti-plated Cu against **Ti4O7/gas-diffusion** systems on safety as well as performance [30] [31] [44].

Full Report

Foundational Context

PFAS destruction is harder than PFAS removal because disappearance of the parent compound does not necessarily mean detoxification. In most treatment systems, PFAS transformation proceeds through adsorption or headgroup interaction followed by C-F cleavage and chain shortening, often generating fluoride plus partially defluorinated intermediates rather than complete mineralization [7] [45]. Many PFAS treatment methods therefore leave short-chain products, residual organofluorine, or concentrated residual streams that can still pose risk [3] [4] [46].

For electrochemical systems, the key performance metrics are usually parent-PFAS removal, defluorination, fluoride mass balance, potential/voltage, and energy use. But from a deployment perspective, **stability, leaching, byproducts, and continuous-flow durability** are equally important because they determine whether a high-performing lab material remains safe and affordable at scale [32] [43] [47].

CeO2 is attractive because vacancy-rich ceria can adsorb and activate PFAS at low oxidation potential, lowering the barrier to C-F cleavage [12]. At the same time, oxide electrodes in PFAS systems can be degraded by the very fluoride they generate, producing a basic tradeoff: **high activity may come from chemically dynamic surfaces that are also vulnerable to damage** [8] [9] [10].

Confidence level: High — this section reflects repeated mechanistic patterns across the supplied evidence [12] [45] [47].

Why CeO2/Ti-Plated Cu Can Be Toxic

1) Nanoparticle release and colloidal behavior

A first plausible toxicity source is physical release of CeO2 or Cu-containing particulate matter from the electrode. In water, metal-oxide nanoparticles do not behave as inert solids; their agglomeration, sedimentation, dissolution, and ion release depend strongly on pH, ionic strength, valence composition, and natural organic matter [1]. CeO2 nanoparticles specifically can undergo environmental transformation through reductive dissolution and ligand reactions that alter their transport and toxicity potential [2].

For ceria, colloidal stability is highly matrix-dependent: low levels of humic/fulvic substances can stabilize particles, whereas higher ionic strength and Ca2+ can promote agglomeration [20] [21] [22]. That matters because both stable nanoscale suspensions and unstable agglomerates can create downstream exposure, just through different transport pathways [48] [49].

The direct evidence gap is important: no retrieved paper explicitly reports PFAS-treatment-induced size-resolved CeO2 shedding from a CeO2 PFAS electrode [21] [50] [51]. Still, given what is known about oxide nanoparticle fate in water, particle release is a credible hazard mechanism for CeO2/Ti-plated Cu systems [1] [2].

2) Dissolved metal-ion toxicity

A second plausible source is dissolved cerium or copper released by dissolution or corrosion. Analogous oxide nanoparticle studies show that dissolved metal release can be highly sensitive to pH, ionic strength, and NOM; for CuO, lower pH and higher ionic strength/NOM increased Cu2+ release in the supplied evidence [1]. One CeO2 PFAS reactor study monitored cerium leaching by ICP-AES during operation, showing that such release is technically measurable and relevant to evaluate [52].

However, the supplied set does not contain a direct CeO2/Ti-plated Cu study that cleanly partitions solid-particle loss from dissolved Ce/Cu release and then links either to toxicity [16] [18] [53]. So dissolved-metal toxicity is plausible, but under-characterized for your exact electrode.

3) Residual PFAS fragments and unknown intermediates

A third toxicity source is incomplete mineralization. PFAS treatment often yields short-chain PFCAs, H-PFCAs, FTS compounds, and unknown fluorinated fractions rather than full destruction [5] [6] [7] [54]. Toxicity does not disappear automatically when chain length decreases: long-chain PFAS are often more bioaccumulative and more potent, but short-chain compounds can still trigger oxidative stress, developmental disruption, and endocrine-related effects [55] [56] [57] [58]. In some systems, a short-chain PFCA such as PFBA was even more toxic than PFOA in tested microalgae [59].

So if a CeO2/Ti-plated Cu system reaches meaningful defluorination but not full mineralization, the effluent may remain hazardous for chemical reasons even before considering nanoparticle release [3] [6] [7].

Confidence level: High for multi-source toxicity; **Medium** for assigning relative contribution within CeO2/Ti-plated Cu specifically [1] [2] [6] [18].

Mechanistic Origins of the Toxicity

Surface state, oxygen vacancies, and redox cycling

The same surface chemistry that makes CeO2 active likely contributes to instability. Oxygen vacancies in ceria are tied to Ce(IV)↔Ce(III) cycling, and vacancy-rich surfaces show stronger fluoride adsorption and greater anion reactivity [13] [14]. Mixed Ce(III)/Ce(IV) surfaces stabilize oxygen vacancies and create uncoordinated Lewis-acid sites that enhance adsorption and interfacial chemistry [60] [61].

At ceria-metal interfaces, Cu can intensify this effect. The supplied evidence indicates that a Cu substrate can strongly increase interfacial vacancy density and fully reduce interfacial cerium to Ce3+, changing reducibility and reactivity [15]. Cu-Ce redox exchange can also generate Cu+ and promote adsorption/activation chemistry [62]. Taken together, these findings suggest that CeO2 on Cu is effective partly because it forms a highly reduced, defect-rich interface — but that same interface may be easier to restructure or degrade under electrochemical bias.

This is an inference, but a well-supported one: **the active site and the weak point are probably the same region** [12] [13] [15].

Fluoride-induced degradation and structural collapse

The strongest cross-cutting degradation mechanism in the supplied literature is fluoride attack. PFAS mineralization generates fluoride, and fluoride can attack TiO2 and related titanium oxide structures, causing surface modification, deactivation, and structural etching [9] [63]. One titanium-oxide nanotube PFAS system underwent catastrophic, irreversible collapse after only a few cycles because fluoride etched the oxide framework rather than merely fouling the surface [11].

This matters directly for CeO2/Ti-plated Cu because the system contains both oxide active phases and a Ti-based component. Even if CeO2 itself remains catalytically useful, fluoride-mediated damage at the oxide surface or Ti/Cu interface could weaken adhesion and promote shedding or leaching over time [8] [10].

Water-matrix effects

Release and toxicity risks are also strongly matrix-dependent. Nanoparticle stability shifts with pH, ionic strength, Ca2+, and NOM [1] [20] [21]. Reviews on PFAS electrochemistry also note that real-water constituents such as high TOC, chloride, and competing ions can suppress performance or alter interfacial behavior [23] [64]. NOM can also worsen fluorine accounting by increasing unknown organofluorine fractions during PFAS treatment [54].

So a CeO2/Ti-plated Cu electrode that looks benign in ultrapure water may release particles or leave more problematic byproducts in real groundwater, AFFF-impacted water, or industrial matrices [23] [65].

Confidence level: Medium-High — strong mechanistic consistency, but limited direct postmortem CeO2/Ti-plated Cu evidence [19] [66].

How the Toxicity Can Potentially Be Fixed

1) Immobilize the active phase more strongly

The most credible mitigation is to stop treating ceria as a weakly bound nanoparticulate surface and instead move toward **strong immobilization**. Evidence from related systems shows that ceria can be supported in porous hosts and recovery-oriented frameworks; nano-hydrated ceria supported in porous D201 improved defluorination performance, and Ce(III) was recovered in a magnetic Fe3O4@ZIF-8 framework under mild conditions [24] [25]. Broader reviews also emphasize solid-supported and immobilized active sites as the direction needed for stability and leaching control [32] [67].

Practically, that means:

- porous ceramic or carbon hosts,
- stronger binders/interlayers,
- magnetic or recoverable supports,
- membrane-integrated catalyst retention.

This approach directly targets particle escape without abandoning ceria chemistry [24] [25] [26].

2) Engineer for durability, not just initial activity

Because defect-rich ceria is likely chemically labile, the surface should be engineered to preserve active redox states without allowing progressive collapse. The supplied literature does not provide a validated anti-release coating specifically for PFAS ceria electrodes [68] [69], but it does support the need for post-reaction XPS/XAS-type diagnostics and controlled redox pretreatment to manage Ce3+/Ce4+ state and vacancy density [14] [41].

A reasonable evidence-based design direction is:

- create the minimum vacancy density needed for activity,
- avoid excessively weakly bound nanocrystalline coatings,
- add fluorine-resistant interlayers at Ti/Cu/ceria interfaces,
- design regeneration protocols before catastrophic fluoride damage accumulates.

This part is partly inferred, but consistent with the underlying surface chemistry [10] [13] [14].

3) Redesign the reactor around containment and stable flow

The scale-up lesson from the supplied evidence is that continuous-flow stability is more informative than batch maxima. Flow-through PFAS reactors and gas-diffusion systems show that stable long-duration operation is achievable when mass transfer and interfacial control are well designed [29] [30] [38]. In contrast, some oxide systems fail from fluoride-driven collapse in only a few cycles [11].

Useful reactor tactics include:

- **flow-by/flow-through cells** instead of highly open particle-exposure designs [29] [38],
- **physical particle retention** after the electrochemical zone [26] [27],
- **polarity reversal**, which improved mass transfer, mitigated fouling/aging, and reduced energy use by about 13% in relevant PFAS electrochemical contexts [33],
- avoiding conditions that intensify local fluoride attack or deposit buildup [35] [70].

4) Use a treatment train, not a standalone destructive electrode

The literature repeatedly favors **capture/concentrate first, then destroy**. Adsorption, ion exchange, foam fractionation, and NF/RO can concentrate PFAS into smaller volumes; electrochemical destruction can then treat the concentrate more affordably and with better containment [26] [27] [28] [36]. Pilot NF + UV-sulfite and foam fractionation + electrochemical oxidation systems show that integrated trains can reduce PFAS mass and lower toxicity-related signals more effectively than single-step treatment [28] [37].

For CeO2/Ti-plated Cu, this is especially relevant because a smaller, concentrated stream makes it much easier to:

- contain any released particles,
- monitor Ce/Cu release,
- polish the effluent before discharge,
- manage spent media and residuals [71] [72] [73].

5) Consider switching if durability and safety dominate

If your decision criterion is not just lab defluorination percentage but **safe, scalable, monitorable deployment**, the supplied evidence suggests that more mature continuous-flow systems may currently be preferable. A Cu/Mn-N-C gas-diffusion cathode paired with Ti4O7 achieved about 99% PFAS removal, meaningful defluorination, low energy demand, limited Cu/Mn leaching, and 100 h stability [30]. Ti4O7 reactive electrochemical membranes also showed strong single-pass performance and relatively low energy use [44].

This does not prove those systems are universally better than CeO2/Ti-plated Cu, but it does indicate stronger available evidence on durability and release behavior [30] [31] [44].

Confidence level: High for immobilization/treatment-train logic; **Medium** for specific anti-release fixes on CeO2/Ti-plated Cu because direct validation studies are not in the supplied set [26] [32] [67].

Practical Recommendation

The best near-term strategy is **not** to deploy CeO2/Ti-plated Cu as a bare high-performance destructive electrode for direct discharge polishing. The safer path is a **multi-barrier process**:

1. **Concentrate PFAS first** using foam fractionation, ion exchange, or NF/RO [26] [36] [37].
2. Use CeO2-based electroreduction only in a **contained, continuous-flow reactor** with strong catalyst immobilization and particle retention [24] [26] [33].
3. Add **post-treatment polishing** for both residual PFAS fragments and released particles/metals before discharge [26] [27] [28].
4. Require **full monitoring**, not just PFAS disappearance: fluoride balance, Ce/Cu in dissolved and particulate fractions, and toxicity testing of whole and fractionated effluent [18] [39] [43].
5. If that containment architecture is not feasible, prioritize **more mature immobilized continuous-flow alternatives** with better durability evidence [29] [30] [31].

In short: **the toxicity is probably caused by a coupled process of defect-rich ceria activity, fluoride-driven degradation, particle/ion release, and incomplete mineralization. The fix is to redesign the system around immobilization, containment, concentrate-stream treatment, and polishing rather than trying to solve it with one surface tweak alone** [8] [12] [26] [28].

Overall conclusion confidence: Medium-High — the direction of causation and mitigation is strongly supported across the evidence base, but direct CeO2/Ti-plated Cu toxicity-mechanism studies remain a major gap [16] [18] [19].

References

1. Peng, C., Shen, C., Zheng, S., (...), Shi, J. (2017) Transformation of CuO nanoparticles in the aquatic environment: Influence of pH, electrolytes and natural organic matter. *Nanomaterials*. https://doi.org/10.3390/nano7100326
2. You, G., Hou, J., Xu, Y., (...), Xing, B. (2021) Surface Properties and Environmental Transformations Controlling the Bioaccumulation and Toxicity of Cerium Oxide Nanoparticles: A Critical Review. *Reviews of Environmental Contamination and Toxicology*. https://doi.org/10.1007/398_2020_42
3. Petre, V.-A., Ungureanu, C., Gheorghe, S., Chiriac, F.-L. (2026) PFAS in Aquatic Systems: Bioaccumulation Patterns and Implications of Advanced Water Treatment Limitations. *Environments - MDPI*. https://doi.org/10.3390/environments13060330
4. Mishra, S., Raj, R., Dubey, B.K., (...), Ghangrekar, M.M. (2025) Occurrence, Transformation, and Removal of PFAS in Wastewater Treatment Plants. *PFAS in the Environment: Occurrence, Characterization, Treatment, and Management*. https://doi.org/10.1002/9781394343935.ch6

5. Verma, S., Zimmermann, S., Horn, H. (2026) Advanced oxidation and reduction processes for PFAS treatment: Transformation products, toxicity risks, and detoxification challenge. *Current Opinion in Environmental Science and Health*. https://doi.org/10.1016/j.coesh.2026.100753
6. Khalili, M., Behnami, A., Zoroufchi Benis, K., (...), Dehghanzadeh, R. (2025) Systematic review of various activation methods of sulfate radical precursor for the degradation of PFAS in aquatic environments. *Journal of Environmental Management*. https://doi.org/10.1016/j.jenvman.2025.125409
7. Guo, J., Zhang, P., Sun, H. (2026) Chemical degradation of PFAS in aquatic environments: technological advances and mechanistic insights. *Chinese Science Bulletin*. https://doi.org/10.1360/TB-2025-0205
8. Wang, M., Marriott, P.J., Zhang, J. (2026) Mixed-phase TiOx nanotube array electrodes for PFOA defluorination: Mechanistic insights and fluoride-induced degradation of TiOx. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.179798
9. Gatto, S., Sansotera, M., Persico, F., (...), Bianchi, C.L. (2015) Surface fluorination on TiO2 catalyst induced by photodegradation of perfluorooctanoic acid. *Catalysis Today*. https://doi.org/10.1016/j.cattod.2014.04.031
10. Wang, M., Marriott, P.J., Zhang, J. (2026) Mixed-phase TiOx nanotube array electrodes for PFOA defluorination: Mechanistic insights and fluoride-induced degradation of TiOx. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.179798
11. Wang, M., Marriott, P.J., Zhang, J. (2026) Mixed-phase TiOx nanotube array electrodes for PFOA defluorination: Mechanistic insights and fluoride-induced degradation of TiOx. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.179798
12. Liu, X., Shu, Y., Pan, Y., (...), Wang, Z. (2025) Electrochemical destruction of PFAS at low oxidation potential enabled by CeO2 electrodes utilizing adsorption and activation strategies. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2024.137043
13. Huang, L., Cheng, H., You, X., (...), Shi, B. (2025) Biomimetic cofactor activation of Ce-MOF nanozyme for portable detection of fluoride ions in beverages. *Sensors and Actuators B: Chemical*. https://doi.org/10.1016/j.snb.2025.137485
14. Jeong, H.W., Kang, H.I., Lee, J., Shim, S.E. (2026) Oxygen vacancy–driven redox mechanisms for enhanced thermo-oxidative stability of silicone rubber with Fe2O3, CeO2, and CeZrO2. *Polymer Degradation and Stability*. https://doi.org/10.1016/j.polymdegradstab.2026.111927
15. Luches, Paola, Valeri, Sergio (2015) Structure, Morphology and Reducibility of Epitaxial Cerium Oxide Ultrathin Films and Nanostructures. *Materials*. https://doi.org/10.3390/ma8095278
16. Liu, X., Shu, Y., Pan, Y., (...), Wang, Z. (2025) Electrochemical destruction of PFAS at low oxidation potential enabled by CeO2 electrodes utilizing adsorption and activation strategies. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2024.137043

18. Jiang, C., Liu, B., Wang, H., (...), Liu, W. (2026) Micro-nano bubbles technology enhances PFAS removal in aquatic environments: Technological advancements and mechanisms for enhancing PFAS removal. *Journal of Water Process Engineering*. https://doi.org/10.1016/j.jwpe.2026.110755

19. Fernández-Sotillo, A., Ferreira-Aparicio, P. (2023) Durable corrosion-resistant coating based in graphene oxide for cost-effective fuel cells components. *iScience*. https://doi.org/10.1016/j.isci.2023.106569

20. Oriekhova, O., Stoll, S. (2016) Effects of pH and fulvic acids concentration on the stability of fulvic acids - cerium (IV) oxide nanoparticle complexes. *Chemosphere*. https://doi.org/10.1016/j.chemosphere.2015.08.057

21. Liu, X., Chen, G., Su, C. (2012) Influence of collector surface composition and water chemistry on the deposition of cerium dioxide nanoparticles: QCM-D and column experiment approaches. *Environmental Science and Technology*. https://doi.org/10.1021/es300883q

22. Dippon-Deißler, U., Pabst, S., Klitzke, S. (2018) Colloidal stabilization of CeO2 nanomaterials with polyacrylic acid, polyvinyl alcohol or natural organic matter. *Science of the Total Environment*. https://doi.org/10.1016/j.scitotenv.2018.07.189

23. Veciana, M., Bräunig, J., Farhat, A., (...), Ledezma, P. (2022) Electrochemical oxidation processes for PFAS removal from contaminated water and wastewater: fundamentals, gaps and opportunities towards practical implementation. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2022.128886

24. Zhang, J., Dai, H., Ding, G., Qiu, H. (2024) Preparation of cerium-based composite nanomaterials using for defluorination from water. *Environmental Chemistry*. https://doi.org/10.7524/j.issn.0254-6108.2023051201

25. Huang, J., Wang, L. (2025) Single-step recovery of rare earth cerium on core–shell structured Fe3O4@ZIF-8 under mild conditions: Insights into the formation and evolution of surface ZnO/CeO2 nanocrystals. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2025.164313

26. Wang, Y., Ji, Y., Li, K., Huang, Q. (2023) Foam fractionation and electrochemical oxidation for the treatment of per- and polyfluoroalkyl substances (PFAS) in environmental water samples. *Chemosphere*. https://doi.org/10.1016/j.chemosphere.2023.139615

27. Liang, S., Mora, R., Huang, Q., (...), Anderson, H. (2022) Field demonstration of coupling ion-exchange resin with electrochemical oxidation for enhanced treatment of per- and polyfluoroalkyl substances (PFAS) in groundwater. *Chemical Engineering Journal Advances*. https://doi.org/10.1016/j.ceja.2021.100216

28. Smith, S.J., Lauria, M., Ahrens, L., (...), Wiberg, K. (2023) Electrochemical Oxidation for Treatment of PFAS in Contaminated Water and Fractionated Foam—A Pilot-Scale Study. *ACS ES and T Water*. https://doi.org/10.1021/acsestwater.2c00660

29. Le, P.-C., Bui, D.N., Minh, T.T., (...), Thao, T.T.T. (2026) Cathodically intensified PFAS defluorination in a flow-through electrochemical reactor using a Cu/Mn–N–C lignin-derived gas-diffusion cathode. *Journal of Water Process Engineering*. https://doi.org/10.1016/j.jwpe.2026.110741

30. Le, P.-C., Bui, D.N., Minh, T.T., (...), Thao, T.T.T. (2026) Cathodically intensified PFAS defluorination in a flow-through electrochemical reactor using a Cu/Mn–N–C lignin-derived gas-diffusion cathode. *Journal of Water Process Engineering*. https://doi.org/10.1016/j.jwpe.2026.110741

31. Radjenovic, J., Duinslaeger, N., Avval, S.S., Chaplin, B.P. (2020) Facing the Challenge of Poly- And Perfluoroalkyl Substances in Water: Is Electrochemical Oxidation the Answer?. *Environmental Science and Technology*. https://doi.org/10.1021/acs.est.0c06212

32. Guo, J., Lei, M., Shen, F., (...), Xu, X. (2026) Atomically dispersed p-block sites toward destructive PFAS treatment: Direct evidence, mechanistic analogies for C-F bond activation, and process intensification. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.182061

33. Luo, Y., Awoyemi, O.S., Gopalan, S., (...), Fang, C. (2023) Investigating the effect of polarity reversal of the applied current on electrochemical degradation of per-and polyfluoroalkyl substances. *Journal of Cleaner Production*. https://doi.org/10.1016/j.jclepro.2023.139691

34. Xu, L., Lu, Q., Wang, Y. (2026) Review on the electrochemical oxidation of PFAS using Ti4O7 anodes. *Current Opinion in Electrochemistry*. https://doi.org/10.1016/j.coelec.2026.101861

35. Wang, Y.-F., Li, X., Xu, H., (...), Zhu, Y. (2026) Ti/RuO2-Ir-Ti4O7 composite electrocatalytic membrane for PFOA removal and transformation: Cross-flow vs. dead-end operation, transformation pathways, and toxicogenomic response evolution. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2026.143739

36. Shi, H., Chiang, S.-Y.D., Wang, Y., (...), Huang, Q. (2021) An electrocoagulation and electrooxidation treatment train to remove and degrade per- and polyfluoroalkyl substances in aqueous solution. *Science of the Total Environment*. https://doi.org/10.1016/j.scitotenv.2021.147723

37. Liu, C.J., McKay, G., Jiang, D., (...), Strathmann, T.J. (2021) Pilot-scale field demonstration of a hybrid nanofiltration and UV-sulfite treatment train for groundwater contaminated by per- and polyfluoroalkyl substances (PFASs). *Water Research*. https://doi.org/10.1016/j.watres.2021.117677

38. Fenti, A., Jin, Y., Hanson, A.J.H., (...), Blotevogel, J. (2022) Performance testing of mesh anodes for in situ electrochemical oxidation of PFAS. *Chemical Engineering Journal Advances*. https://doi.org/10.1016/j.ceja.2021.100205

39. Ganzoury, M.A., Ghasemian, S., Zhang, N., (...), de Lannoy, C.-F. (2022) Mixed metal oxide anodes used for the electrochemical degradation of a real mixed industrial wastewater. *Chemosphere*. https://doi.org/10.1016/j.chemosphere.2021.131600

40. Sands, M., Sachdeva, A., Bukavina, L., Irudayaraj, J. (2025) Synergistic toxicity of PFAS and microplastic mixtures across five human cell lines. *Environmental Pollution*. https://doi.org/10.1016/j.envpol.2025.127256

41. Guo, J., Lei, M., Shen, F., (...), Xu, X. (2026) Atomically dispersed p-block sites toward destructive PFAS treatment: Direct evidence, mechanistic analogies for C-F bond activation, and process intensification. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.182061

42. Wang, X., Yan, A., Zhu, L., (...), Wang, Z. (2025) Revealing electric field on low temperature ammonia decomposition activity over ceria-supported catalyst. *Journal of Colloid and Interface Science*. https://doi.org/10.1016/j.jcis.2025.138480

43. Sharma, N., Rasheed, A., Zargar, N., Das, S. (2024) A critical review on mitigation strategies for per- and polyfluoroalkyl substances from water matrices with special emphasis on techno-economic and life cycle assessment: Current status, knowledge gaps, and future perspectives. *Journal of Environmental Chemical Engineering*. https://doi.org/10.1016/j.jece.2024.114863

44. Le, T.X.H., Haflich, H., Shah, A.D., Chaplin, B.P. (2019) Energy-Efficient Electrochemical Oxidation of Perfluoroalkyl Substances Using a Ti4O7 Reactive Electrochemical Membrane Anode. *Environmental Science and Technology Letters*. https://doi.org/10.1021/acs.estlett.9b00397

45. Gar Alalm, M., Boffito, D.C. (2022) Mechanisms and pathways of PFAS degradation by advanced oxidation and reduction processes: A critical review. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2022.138352

46. Zhang, X., Han, T., Yao, X., (...), Duan, P. (2026) Advanced Degradation and Remediation Strategies for Per- and Polyfluoroalkyl Substances (PFASs): Challenges and Future Perspectives. *Toxics*. https://doi.org/10.3390/toxics14060499

47. Zhang, Xiaohui, Han, Tongshun, Yao, Xiaofeng, (...), Duan, Peigao (2026) Advanced Degradation and Remediation Strategies for Per- and Polyfluoroalkyl Substances (PFASs): Challenges and Future Perspectives. *Toxics*. https://doi.org/10.3390/toxics14060499

48. Li, Z., Sahle-Demessie, E., Aly Hassan, A.A., Sorial, G.A. (2011) Transport and deposition of CeO2 nanoparticles in water-saturated porous media. *Water Research*. https://doi.org/10.1016/j.watres.2011.05.025

49. Otero-González, L., Barbero, I., Field, J.A., (...), Sierra-Alvarez, R. (2014) Stability of alumina, ceria, and silica nanoparticles in municipal wastewater. *Water Science and Technology*. https://doi.org/10.2166/wst.2014.408

50. Baalousha, M., Ju-Nam, Y., Cole, P.A., (...), Lead, J.R. (2012) Characterization of cerium oxide nanoparticles-Part 2: Nonsize measurements. *Environmental Toxicology and Chemistry*. https://doi.org/10.1002/etc.1786

51. Batley, G.E., Halliburton, B., Kirby, J.K., (...), Veitch, C. (2013) Characterization and Ecological Risk Assessment Of Nanoparticulate CeO2 as a Diesel Fuel Catalyst. *Environmental Toxicology and Chemistry*. https://doi.org/10.1002/etc.2246

52. Liu, X., Shu, Y., Pan, Y., (...), Wang, Z. (2025) Electrochemical destruction of PFAS at low oxidation potential enabled by CeO2 electrodes utilizing adsorption and activation strategies. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2024.137043

53. Luo, Y., Awoyemi, O.S., Gopalan, S., (...), Fang, C. (2023) Investigating the effect of polarity reversal of the applied current on electrochemical degradation of per-and polyfluoroalkyl substances. *Journal of Cleaner Production*. https://doi.org/10.1016/j.jclepro.2023.139691

54. Barisci, S., Suri, R. (2023) Degradation of emerging per- and polyfluoroalkyl substances (PFAS) using an electrochemical plug flow reactor. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2023.132419

55. Solan, M.E., Koperski, C.P., Senthilkumar, S., Lavado, R. (2023) Short-chain per- and polyfluoralkyl substances (PFAS) effects on oxidative stress biomarkers in human liver, kidney, muscle, and microglia cell lines. *Environmental Research*. https://doi.org/10.1016/j.envres.2023.115424

56. Yeboah, C., Sackey, L.N.A., Asamoah, D.K.O., (...), Mwema, M.F. (2026) Structural drivers of per- and polyfluoroalkyl substances environmental fate, bioaccumulation kinetics, and sub-cellular toxicity: A systematic review of legacy and emerging alternatives. *Science of the Total Environment*. https://doi.org/10.1016/j.scitotenv.2026.182324

57. Zhao, M., Yin, N., Yang, R., (...), Faiola, F. (2024) Assessment and Comparison of Early Developmental Toxicity of Six Per- and Polyfluoroalkyl Substances with Human Embryonic Stem Cell Models. *Environmental Science and Technology*. https://doi.org/10.1021/acs.est.3c10758

58. Menger, F., Pohl, J., Ahrens, L., (...), Örn, S. (2020) Behavioural effects and bioconcentration of per- and polyfluoroalkyl substances (PFASs) in zebrafish (Danio rerio) embryos. *Chemosphere*. https://doi.org/10.1016/j.chemosphere.2019.125573

59. Olorunyomi, G., Ihenyen, E., Niederauer, S., (...), Smith, E.E. (2026) Comparative Toxicity of Perfluorooctanoic Acid (PFOA) and Perfluorobutanoic Acid (PFBA) Exposure in Two Microalgae Species. *Water (Switzerland)*. https://doi.org/10.3390/w18172068

60. Calado, L.M., Taryba, M.G., Carmezim, M.J., Montemor, M.F. (2018) Self-healing ceria-modified coating for corrosion protection of AZ31 magnesium alloy. *Corrosion Science*. https://doi.org/10.1016/j.corsci.2018.06.013

61. Yang, W., Du, Y., Xu, H., (...), Gao, L. (2026) Development of Ce-La bimetal oxyhydroxide nanocomposite with enhanced stability and selectivity for phosphate and fluoride co-removal from phosphogypsum leachate. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.173844

62. Cam, T.S., Omarov, S.O., Chebanenko, M.I., (...), Popkov, V.I. (2021) One step closer to the low-temperature CO oxidation over non-noble CuO/CeO2nanocatalyst: The effect of CuO loading. *Journal of Environmental Chemical Engineering*. https://doi.org/10.1016/j.jece.2021.105373

63. Sansotera, M., Persico, F., Rizzi, V., (...), Navarrini, W. (2015) The effect of oxygen in the photocatalytic oxidation pathways of perfluorooctanoic acid. *Journal of Fluorine Chemistry*. https://doi.org/10.1016/j.jfluchem.2015.06.019

64. Uwayezu, J.N., Carabante, I., Lejon, T., (...), Kumpienė, J. (2021) Electrochemical degradation of per- and poly-fluoroalkyl substances using boron-doped diamond electrodes. *Journal of Environmental Management*. https://doi.org/10.1016/j.jenvman.2021.112573

65. Singh Kalra, S., Cranmer, B., Dooley, G., (...), Mahendra, S. (2021) Sonolytic destruction of Per- and polyfluoroalkyl substances in groundwater, aqueous Film-Forming Foams, and investigation derived waste. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2021.131778

66. Liu, X., Shu, Y., Pan, Y., (...), Wang, Z. (2025) Electrochemical destruction of PFAS at low oxidation potential enabled by CeO2 electrodes utilizing adsorption and activation strategies. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2024.137043

67. Mkilima, T. (2026) Engineering the “Forever Chemicals” Exit: Destructive Technologies for PFAS Mineralization Beyond Adsorption and Containment. *Environmental Quality Management*. https://doi.org/10.1002/tqem.70456

68. Puttamreddy, S., Nippatlapalli, N. (2024) Advanced insights into sustainable electrooxidation technique and futuristic strategies: Multifaceted approach for PFAS degradation. *Journal of Environmental Chemical Engineering*. https://doi.org/10.1016/j.jece.2024.113307

69. Tan, B.T.-W., Abu-Bakar, N.H.H., Lee, H.L. (2025) Electrochemical methods for treatment of per- and polyfluoroalkyl substances (PFAS): A review. *Journal of Environmental Chemical Engineering*. https://doi.org/10.1016/j.jece.2024.114990

70. Luo, Y., Awoyemi, O.S., Gopalan, S., (...), Fang, C. (2023) Investigating the effect of polarity reversal of the applied current on electrochemical degradation of per-and polyfluoroalkyl substances. *Journal of Cleaner Production*. https://doi.org/10.1016/j.jclepro.2023.139691

71. Zaggia, A., Conte, L., Falletti, L., (...), Chiorboli, A. (2016) Use of strong anion exchange resins for the removal of perfluoroalkylated substances from contaminated drinking water in batch and continuous pilot plants. *Water Research*. https://doi.org/10.1016/j.watres.2015.12.039

72. Lin, H., Niu, J., Liang, S., (...), Huang, Q. (2018) Development of macroporous Magnéli phase Ti4O7 ceramic materials: As an efficient anode for mineralization of poly- and perfluoroalkyl substances. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2018.07.210

73. Ren, M., Wang, L. (2026) Recent advances in adsorption and electrosorption for PFASs removal: mechanisms, materials, and practical perspectives. *Separation and Purification Technology*. https://doi.org/10.1016/j.seppur.2026.139900