Design Evolution of Coronary Stent Technology in the Treatment of Coronary Artery Disease

DSTIMD4 Written Assignment | 2026

Introduction

Cardiovascular disease (CVD) accounts for approximately 32% of global mortality, with coronary artery disease (CAD) among its most prevalent forms [1]. CAD is characterised by atherosclerosis: the accumulation of lipid, cholesterol and fibrous elements within the tunica intima, producing inflammatory-mediated plaque that progressively occludes the lumen. Percutaneous coronary intervention (PCI) through stent implantation has become the dominant treatment strategy, with over 1.5 million coronary stents placed annually in the US alone [2]. The evolution of stent technology is an instructive case study in iterative biomechanical optimisation, with each generation engineered as a direct response to the dominant failure mode of its predecessor.

Balloon Angioplasty and the Mechanical Case for Scaffolding

Andreas Grüntzig performed the first successful percutaneous transluminal coronary angioplasty (PTCA) in 1977 [3], demonstrating that mechanical dilation of stenosed coronary vessels was feasible. However, the arterial wall behaves viscoelastically: upon balloon deflation, elastic recovery of the vessel wall drives acute recoil, while smooth muscle cell contraction and neointimal proliferation produce late restenosis in 30–50% of patients [4]. Without a permanent scaffold to counteract the vessel's elastic restoring force, luminal gain was inherently unstable. This mechanical insufficiency defined the engineering requirement for the first generation of coronary stents: a device capable of sustaining sufficient radial force to maintain vessel patency indefinitely.




*Figure 1. Cross-sectional lumen schematic across stent generations. Grey = struts; pink = neointima; purple dots = drug elution; green dashed = re-endothelialisation. *ABSORB pooled analysis [15].*

Bare Metal Stents: Solving Recoil, Creating Restenosis

The Palmaz–Schatz stent, introduced clinically in 1987, was laser-cut from 316L stainless steel (SS) [5]. The yield strength of 316L SS (~205 MPa) dictated strut thicknesses of 130–140 µm to achieve the radial force necessary to resist elastic recoil and prevent acute closure [6]. Whilst BMS effectively eliminated recoil, strut thickness emerged as a critical design variable: the landmark ISAR-STEREO trial (Kastrati et al., 2001) directly compared thick-strut BMS (140 µm) against thin-strut BMS (50 µm) and demonstrated angiographic restenosis rates of 31.4% versus 15.0% respectively [7]. Mechanistically, thicker struts caused greater medial layer injury during deployment, triggering an amplified inflammatory response and neointimal hyperplasia. Additionally, protruding struts disturb coronary haemodynamics: computational fluid dynamics (CFD) models show that strut protrusion creates low time-averaged wall shear stress (TAWSS) recirculation zones downstream, conditions known to promote endothelial dysfunction and thrombus deposition [8] (Figure 2). BMS required repeat intervention in 12–20% of patients due to ISR [9], establishing that material-limited strut thickness was an engineering bottleneck.




Figure 2. Schematic haemodynamic comparison of thick vs. thin struts. Red shading = low TAWSS recirculation zones driving endothelial dysfunction and neointimal proliferation. Based on Beier et al. (2016) [8].

Drug-Eluting Stents: Pharmacological Suppression of Hyperplasia

First-generation drug-eluting stents (DES), introduced in the early 2000s, addressed neointimal hyperplasia by incorporating an antiproliferative drug (sirolimus or paclitaxel) within a durable polymer coating. The Cypher

stent (Cordis) delivered sirolimus from a PVDF-HFP polymer matrix, reducing ISR requiring repeat intervention to approximately 5% [9]. However, the durable polymer provoked chronic localised inflammation and impaired re-endothelialisation, delaying healing and increasing late stent thrombosis (LST) risk beyond 12 months [10]. The engineering challenge became more nuanced: simultaneous suppression of restenosis whilst preserving physiological healing.

Second-generation DES resolved this by adopting cobalt-chromium (CoCr) and platinum-chromium (PtCr) alloys. CoCr alloys exhibit a yield strength of approximately 414 MPa — roughly double that of 316L SS — enabling strut thickness reduction to 80–90 µm whilst maintaining equivalent radial force [6]. This reduction demonstrably improved outcomes through reduced arterial injury and TAWSS perturbation. CFD optimisation studies identify strut angles of ~40° to the flow direction as haemodynamically optimal, minimising recirculation area [8]. Second-generation DES also adopted biodegradable polymer coatings (e.g., polylactic acid), eliminating the persistent inflammatory stimulus of durable polymers and further reducing LST [10].

Bioresorbable Scaffolds: Promise, Failure and Next-Generation Redesign

The ultimate engineering goal was elimination of permanent metallic caging, which constrains vasomotion, precludes adaptive vascular remodelling, and sustains a ~2–3% annual rate of very late adverse events in metallic DES [11]. The Absorb BVS (Abbott Vascular) — a poly-L-lactic acid (PLLA) scaffold with everolimus coating — received CE mark in 2011 [12]. PLLA has an elastic modulus of only ~3.5 GPa, compared to ~200 GPa for CoCr, requiring strut thicknesses of ~157 µm to achieve adequate radial strength [13]. This reintroduced the haemodynamic and thrombogenic penalties that second-generation metallic stents had overcome. Finite element analysis (FEA) modelling of PLLA degradation reveals that resorption is strain-dependent and spatially heterogeneous: high-strain crown regions degrade preferentially, leading to strut discontinuity prior to complete resorption [14]. The ABSORB pooled analysis of 5,988 patients demonstrated device thrombosis of 2.2% with BVS versus 1.0% with CoCr-EES (HR 2.38, 95% CI 1.49–3.79), and target lesion failure of 15.9% versus 13.1% (HR 1.25) [15]. Critically, this excess risk was confined to the first three years — coinciding with resorption — after which event rates were comparable, confirming the failure was scaffold-dependent.

Next-generation BRS target the strut thickness trade-off through polymer engineering. The Firesorb scaffold (MicroPort) achieves 100–125 µm struts via ultra-high molecular weight PLLA; the FUTURE-II trial (n=433) demonstrated a TLF rate of 0.9% at one year with no scaffold thrombosis, comparable to CoCr-EES [16]. The Esprit BVS (Abbott) achieves 99 µm struts through further formulation advances. Magnesium-alloy BRS offer a bioresorbable metal alternative with a higher elastic modulus, though early trials show greater late lumen loss than metallic DES [17] (Table 1, Figure 3).

Generation	Material	Yield Strength	Strut Thickness	Polymer Coating	Clinical Failure Rate	Introduced
PTCA	None (balloon)	—	—	—	30–50% restenosis	1977
BMS 1st-gen	316L Stainless Steel	~205 MPa	130–140 µm	None	12–20% ISR	1987
DES 1st-gen	316L SS / CoCr	~205–414 MPa	130–140 µm	Durable PVDF-HFP	~5% ISR; LST risk	2003
DES 2nd-gen	CoCr / PtCr alloy	~414 MPa	80–90 µm	Biodegradable PLA	~2–3% TLF	2008
BRS (Absorb BVS)	PLLA polymer	~50 MPa*	~157 µm	Biodegradable PLLA	2.2% thrombosis (HR 2.38)	2011
Next-gen BRS (Firesorb)	UHM PLLA	~55 MPa*	100–125 µm	PLLA	0.9% TLF (FUTURE-II)	2020s

*Table 1. Engineering parameters and clinical failure rates across coronary stent generations. *PLLA tensile strength (not yield strength); CoCr and PtCr alloy data from Ormiston & Webster (2007) [6]. BRS data from ABSORB pooled analysis [15] and FUTURE-II [16].*




*Figure 3. Reported restenosis/TLF rates across stent generations. *Endpoint definitions vary. Sources: [4,9,10,15,16].*

Conclusions

The evolution from PTCA to contemporary BRS is characterised by successive engineering responses to clinically identified failure modes: elastic recoil necessitated scaffolding; injury-driven ISR demanded thinner struts and better materials; delayed healing required biodegradable coatings; and permanent metal implantation risks drove the development of bioresorbable platforms. At each stage, quantitative trade-offs between radial force, strut thickness, haemodynamics and biocompatibility constrained design. The central challenge — achieving metallic scaffold radial strength with the resorption kinetics of a degradable polymer — is progressively yielding to advances in high-molecular-weight polymer engineering and FEA-guided geometric optimisation.

References

[1] WHO Global Health Estimates, 2020.

[2] Edelman ER, Rogers C. Circulation. 1998;97(9):842–843.

[3] Grüntzig A. Lancet. 1978;1(8058):263.

[4] Forrester JS et al. J Am Coll Cardiol. 1991;17(3):758–769.

[5] Sigwart U et al. N Engl J Med. 1987;316(12):701–706.

[6] Ormiston JA, Webster MWI. Heart. 2007;93(Suppl 1):i1–i3.

[7] Kastrati A et al. (ISAR-STEREO). Circulation. 2001;103(23):2816–2821.

[8] Beier S et al. Ann Biomed Eng. 2016;44(2):357–368.

[9] Babapulle MN, Eisenberg MJ. Circulation. 2002;106(24):2859–2866.

[10] Ako J et al. Am J Cardiol. 2007;100(8):S3–S9.

[11] Stone GW et al. J Am Coll Cardiol. 2023. doi:10.1016/j.jacc.2023.05.003.

[12] Serruys PW et al. (ABSORB II). Lancet. 2016;388(10059):2479–2491.

[13] McMahon S et al. Prog Polym Sci. 2018;83:79–96.

[14] Yang C et al. Front Bioeng Biotechnol. 2021. PMC8130847.

[15] Stone GW et al. ABSORB Pooled. J Am Coll Cardiol Intv. 2025. doi:10.1016/j.jcin.2024.08.050.

[16] Stone GW et al. FUTURE-II / Firesorb. J Am Coll Cardiol. 2023.

[17] Seguchi M et al. J Cardiol. 2023;81(2):179–188.