

Product Name: POLURGREEN ML 2000 (XP 2100)

Type of Polymer:	Low monomer content aliphatic polyisocyanate	
Range of use:	POLURGREEN ML 2000 is recommended for the formulation of high solid content, low viscosity, lightfast resistant coatings for metal, plastic and concrete.	
Specifications:	POLURGREEN ML 2000 % NCO % of free monomer Viscosity (23°C mPa*s) Max color Hazen	19.0 – 21.0 ≤ 0.1 300 - 900 80
Other data:	POLURGREEN ML 2000 % NV Type of isocyanate Equivalent weight	100 HDI 210
Properties and application:	POLURGREEN ML 2000 can be used in combination with polyaspartic resins, for the formulation of solvent free lightfast resistant coatings. POLURGREEN ML 2000 is a low reactivity polyisocyanate. It may be used alone, or in combination with HDI trimers, to regulate the system reactivity.	
Storage and warranty:	In sealed drums we guarantee a storage life of 12 months, provided the product is stored under dry and cool condition. Once opened the packaging, the product should be used in short time, because it is sensitive to moisture that can cause his curing inside the drum.	

The technical information provided in this sheet or given in oral or written form is general information designed to assist customers in determining the suitability of our Products for their applications. Our Products are intended for sale to professional users. The technical and safety information contained herein are made without guarantee and are only suggestions. Our customers must test our Products to their application and intended use to determine if our Products meet their requirements. There is no implied warranty of merchantability or fitness for a particular purpose of the Products described herein. In no event shall Sun Chemical be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvement might be made without further notice.

