

Product Name: POLURGREEN MT 100

Type of Polymer:	Low monomer content isocyanate	
Range of use:	POLURGREEN MT 100 is recommended for the formulation of lightfast resistant topcoats. Useful for coatings with high solid content and with low viscosity for metal, wood and plastics.	
Specifications:	POLURGREEN MT 100 % NCO % of free monomer Viscosity (23°C mPa*s) Color Hazen	21.5 – 22.5 < 0.1 1800 - 3500 < 40
Other data:	POLURGREEN MT 100 % NV Solvent Type of isocyanate Equivalent weight	100 none HDI 191
Properties and application:	POLURGREEN MT 100, when combined with acrylic or saturated polyester resin, is suitable to obtain lightfast resistant coatings with optimum mechanical and chemical resistance.	
Storage and warranty:	In sealed drums we guarantee a storage life of 12 months, provided the product is stored under dry and cool condition. Once opened the packaging, the product should be used in short time, because it is sensitive to moisture that can cause his curing inside the drum.	

The technical information provided in this sheet or given in oral or written form is general information designed to assist customers in determining the suitability of our Products for their applications. Our Products are intended for sale to professional users. The technical and safety information contained herein are made without guarantee and are only suggestions. Our customers must test our Products to their application and intended use to determine if our Products meet their requirements. There is no implied warranty of merchantability or fitness for a particular purpose of the Products described herein. In no event shall Sun Chemical be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvement might be made without further notice.

