

Product Name: POLURGREEN PRP 4041

Type of Polymer:	Low monomer NCO terminated aliphatic prepolymer	
Range of use:	Adhesives, sealants and topcoats	
Specifications:	POLURGREEN PRP 4041	
	% NCO	9.0 – 11.0
	% of free monomer	≤ 0.1
	Viscosity (23°C mPa*s)	1500 - 3500
	Max Colour (Hz)	100
Other data:	POLURGREEN PRP 4041	
	% NV	100
	Solvent	None
	Type of isocyanate	HDI
	Equivalent weight	420
Properties and application:	POLURGREEN PRP 4041 is a polyether based prepolymer with moderate elongation and high modulus. His chemical nature imparts good hydrolysis resistance. POLURGREEN PRP 4041 may be used in combination with other aliphatic isocyanic resins for the formulation of 1K and 2K polyurethane adhesives, sealants and topcoats, where yellowing resistance is needed. It may be used in combination with polyaspartic resins to control the system reactivity and flexibility.	
Storage and warranty:	In sealed drums we guarantee a storage life of 12 months, provided the product is stored under dry and cool condition. Once opened the packaging, the product should be used in short time, because it is sensitive to moisture that can cause his curing inside the drum.	

The technical information provided in this sheet or given in oral or written form is general information designed to assist customers in determining the suitability of our Products for their applications. Our Products are intended for sale to professional users. The technical and safety information contained herein are made without guarantee and are only suggestions. Our customers must test our Products to their application and intended use to determine if our Products meet their requirements. There is no implied warranty of merchantability or fitness for a particular purpose of the Products described herein. In no event shall Sun Chemical be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvement might be made without further notice.

