deviceID	devicePublishTime	batchNo machineID batchTime			batchDate	aggt10mm	aggt20mm cement01m sand0			Imm cement02m sand02mm			additive1	totalWT	cum
								m		m					
352914090148079	11/06/2022 6:39 PM	354	796	06:32 PM	11/06/2022 12:00 AM	1250	2855	935	800	0	855	576	0.75	8096.75	3.37
352914090148079	11/06/2022 5:48 PM	353	796	05:42 PM	11/06/2022 12:00 AM	1685	4575	1260	1055	0	1310	716	1.18	11747.1 8	4.89
352914090148079	11/06/2022 3:53 PM	351	796	03:46 PM	11/06/2022 12:00 AM	1735	3830	1245	945	0	1280	829	0	10969	4.57
352914090148079	11/06/2022 3:09 PM	350	796	03:02 PM	11/06/2022 12:00 AM	1660	3740	1220	1000	0	1075	862	2.49	10714.4 9	4.46
352914090148079	11/06/2022 1:08 PM	348	796	01:01 PM	11/06/2022 12:00 AM	0	0	2765	0	0	0	160	0.16	2925.16	1.21
352914090148079	11/06/2022 12:43 PM	347	796	12:36 PM	11/06/2022 12:00 AM	1625	3605	1140	1025	0	2305	891	2.05	11693.0 5	4.87
352914090148079	11/06/2022 12:29 AM	344	796	12:23 AM	11/06/2022 12:00 AM	1485	3815	1285	1005	0	1250	823	0.1	10678.1	4.44
352914090148079	11/06/2022 1:10 AM	345	796	01:04 AM	11/06/2022 12:00 AM	1530	3665	1255	1075	0	1115	816	0.04	10531.0 4	4.38
352914090148079	11/06/2022 2:02 AM	346	796	01:55 AM	11/06/2022 12:00 AM	1465	3775	1260	950	0	1245	1463	2.43	11170.4 3	4.65