


PROVISIONAL

COM19SLI

BOPP FILMS

METALLISED NON HEAT SEALABLE BOPP FILM WITH ULTRA HIGH BARRIER GRADE FOR SANDWICH LAMINATION

**DESCRIPTION**

COMSLI is both side treated ultra high barrier metallised BOPP film. It's metallised surface is specialized surface having good treatment retention and chemical resistant, Non-metallised side is treated for sandwich adhesive as well as extrusion lamination (triplex structure) as a replacement of Aluminium foil or metallised polyester.

PRODUCT FEATURES

- Outstanding oxygen barrier
- Outstanding Moisture & light barrier
- Good treatment retention & metal adhesion
- Good chemical Resistance
- Extended shelf life for food products
- Easy convertibility on both sides for adhesive as well as extrusion sandwich lamination
- Excellent runnability on HFFS & VFFS machines

APPLICATIONS

Sandwich lamination in triplex structures as a replacement of Aluminium foil/metallised polyester;

- Hair colorants
- Pouch/Sachet laminates
- Health and beauty care
- Household and detergents

PROVISIONAL

	PROPERTIES	POSITION	COM19SLI	UNIT	METHOD
GENERAL	Nominal Thickness	-	19	μ	Internal Method
	Density	-	0.91	g/cc	Internal Method
	Grammage	-	17.3	g/m ²	Internal Method
	Yield	-	57.8	m ² /kg	Internal Method
OPTICAL	Optical Density	-	2.9	-	Internal Method
SURFACE	Metal Adhesion	-	100	%	Internal Method
MECHANICAL	Tensile Strength (at break)	- MD - TD	1200 2500	kg/cm ²	ASTM D 882
	Elongation (at break)	- MD - TD	190 60	%	ASTM D 882
	Elastic Modulus	- MD - TD	17000 28000	kg/cm ²	ASTM D 882
	Linear Shrinkage	- MD - TD	4 2	%	ASTM D 1204
BARRIER	WVTR 38° C 90% RH	-	0.1	g/m ² /day	ASTM F 1249
	OXTR 23° C 0% RH	-	0.1	cc/m ² /day	ASTM D 3985

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing.
- Reels must not be stacked
(Recommended storage conditions: Temperature < 30 deg C & Humidity 55% (Maximum) in original packed condition)