

PROVISIONAL

T12TTIHR

BOPP FILMS

TRANSPARENT NON HEAT SEALABLE BOTH SIDE CORONA TREATED,
HIGHER TREATMENT INSIDE, HIGH HEAT RESISTANT BOPP FOR CONVERSION



Corona Treated HR Surface (Modified layer)

OPP Modified Core Layer

Corona Treated Glossy Surface

AVAILABLE
CALIPERS

DESCRIPTION

OPP TTIHR is non heat sealable plain high gloss both side corona treated **BOPP** film with good heat resistant characteristics. Its outer corona treated surface is modified to endure heat and shrinking during pack sealing; its core layer is also modified for better rigidity compared to conventional plain BOPP Films. Moreover its inside corona treated surface is specifically designed for printing and lamination during conversion.

PRODUCT FEATURES

- Endurance to heat and shrinking during sealing
- Easy Jaw release
- Good wetting tension for printing and lamination
- Suitable for food contact applications
- Water/oil/grease repellent
- Outstanding clarity and gloss

APPLICATIONS

Can be used as outside web of laminates

- Bakery (Biscuits/cookie/crackers)
- Confectionery(chocolates/gum/sugar)
- Chips/tea/coffee/pasta
- Soaps and detergents
- Miscellaneous industrial and house hold applications

TOPPAN SPECIALITY FILMS

PROVISIONAL

	PROPERTIES	POSITION	T12TTIHR	UNIT	METHOD
GENERAL	Nominal Thickness	-	12	μ	Internal Method
	Density	-	0.91	g/cc	Internal Method
	Grammage	-	10.92	g/m ²	Internal Method
	Yield	-	91.57	m ² /kg	Internal Method
OPTICAL	Haze	-	2.5	%	ASTM D 1003
	Gloss	-	95	GU	ASTM D 2457
SURFACE	COF	Film/Film	0.25	-	ASTM D 1894
		Film/Metal	0.20	-	ASTM D 1894
	Wetting tension	-	38*	dyne/cm	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	- MD	1300	kg/cm ²	ASTM D 882
		- TD	2600		
	Elongation (at break)	- MD	180	%	ASTM D 882
		- TD	60		
THERMAL	Elastic Modulus	- MD	20000	kg/cm ²	ASTM D 882
		- TD	36000		
	Linear Shrinkage	- MD	3	%	ASTM D 1204
		- TD	1		

* 38 dyne/cm guaranteed for 3 months from the invoice date in controlled ambient condition as per below storage guidelines.

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing except for wetting tension