

COTPSLO-U

BOPP FILMS

TRANSPARENT TOP COATED PRESSURE SENSITIVE BOPP FACESTOCK FILM



Coated print receptive layer

OPP core

Corona treated OPP layer

1.85,
1.97
mils

AVAILABLE
CALIPERS

DESCRIPTION

Transparent **BOPP** Film is with one Side Print Receptive Coated & Other Side Treated for Pressure Sensitive Labels

PRODUCT FEATURES

- Excellent ink adhesion with a broad range of ink systems, including UV curing inks on print receptive coated surface.
- Corona treated surface suitable for adhesive anchorage
- High speed press performance
- Superior performance of print surface in humid environment
- Excellent gloss
- Outstanding Clarity
- Excellent stiffness and mechanical properties
- Good dimensional stability
- Good die cutting performance

APPLICATIONS

- Labels

COATING SIDE

COT PSLO-U : Outside Print receptive coated surface

	PROPERTIES	POSITION	COT47PSLO-U	COT50PSLO-U	UNIT	METHOD
GENERAL	Nominal Thickness	-	1.85	1.97	mils	Internal Method
	Grammage	-	8.76	9.34	lb/1000ft ²	Internal Method
	Yield	-	16438	15453	in ² /lb	Internal Method
OPTICAL	Haze	-	2.5		%	ASTM D 1003
	Gloss	-	90		GU	ASTM D 2457
SURFACE	Wetting tension (Uncoated Surface)		38			ASTM D 2578
MECHANICAL	Tensile Strength (at break)	- MD - TD	18490 39825		psi	ASTM D 882
	Elongation (at break)	- MD - TD	200 60		%	ASTM D 882
	Elastic Modulus	- MD - TD	227573 469369		psi	ASTM D 882
THERMAL	Linear Shrinkage	- MD - TD	4 2		% %	ASTM D 1204

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of manufacturing
- Coated reels must not be stacked