

PROVISIONAL

T10TIC

TRANSPARENT NON SEALABLE CORONA TREATED ONE SIDE BOPP FILM FOR EASY COLD SEAL RELEASE APPLICATION



Corona Treated Surface

OPP Core

Modified Surface for Easy Cold seal release



AVAILABLE
CALIPERS

DESCRIPTION

T10TIC is transparent high gloss one side corona treated non heat sealable **BOPP** film, specifically designed for easy cold seal release as outer web of laminates.

PRODUCT FEATURES

- Excellent ink adhesion on the treated side
- Excellent release from cold seal adhesive
- Outstanding Clarity & Gloss
- Printable/glueable
- Robust Machinability
- Suitable for food contact application
- Water/ Oil/ Grease repellent

APPLICATIONS

- Confectionery (chocolate/gum/sugar)
- Bakery (biscuits/cookie/crackers)
- Chips/tea/coffee/pasta
- Miscellaneous industrial & house hold application

NOMENCLATURE

TIC... Corona treated surface is Inside & Outside surface is Cold Seal Release

TOC... Corona treated surface is Outside & Inside surface is Cold Seal Release

PROVISIONAL

	PROPERTIES	POSITION	T10TIC	UNITS	TEST METHOD
GENERAL	Nominal Thickness	-	10	μ	Internal Method
	Density	-	0.91	g/cc	Internal Method
	GSM	-	9.1	g/m ²	Internal Method
	Yield	-	109.9	m ² /kg	Internal Method
OPTICAL	Haze	-	1.8	%	ASTM D 1003
	Gloss	-	95	GU	ASTM D 2457
SURFACE	Dynamic COF	Film/Film	0.25	-	ASTM D 1894
	Wetting Tension	-	38*	-	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	-MD -TD	1300 2700	kg/cm ²	ASTM D 882
	Elongation (at break)	-MD -TD	150 50	%	ASTM D 882
	Elastic Modulus	-MD -TD	18000 32000	kg/cm ²	ASTM D 882
THERMAL	Linear Shrinkage (max)	-MD	5	%	Internal Method
		-TD	2		

* 38 dyne/cm guaranteed for 3 months & 36 dyne/cm guaranteed for 6 months from the invoice date in controlled ambient condition as mentioned in storage guidelines.

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed with three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use. Film characteristics are maintained for six months from the date of manufacturing.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing except for corona treated layer surface tension.
- Coated reels must not be stacked.