


MDS225-M

BOPP FILMS

METALLISED LOW SEAL INITIATION TEMPERATURE, HIGH HOT-TACK & HIGH SEAL STRENGTH BARRIER GRADE BOPP FILM FOR HIGH SPEED PACKAGING APPLICATIONS



Metallised Layer
OPP Core
Low SIT / High Hot Track Layer



AVAILABLE
CALIPERS

DESCRIPTION

MDS225-M is a metallised Barrier Grade multipurpose **BOPP** film with low seal initiation temperature and broad seal range. Especially designed for high speed packaging where its wide seal operating window can be used on high speed machines. In addition to this, its improved barrier properties make it an ideal choice for sensitive product demanding great protection.

PRODUCT FEATURES

- Wide sealing range with low seal initiation temperature(SIT ~ 95°C)
- Excellent sealing properties in term of strength, hot-tack
- Remarkable performance on HFFS & VFFS machines
- Excellent seal integrity in presence of contaminants and humidity
- Excellent metal adhesion, bond strength and treatment retention
- Excellent barrier properties

APPLICATIONS

To be used as inner sealable web in laminated structure where high barrier protection and seal integrity are required

- Confectionary (chocolate/gum/sugar)
- Bakery (Biscuits/cookie/crackers)
- Potato chips/snacks/crisp
- Household and detergents

	PROPERTIES	POSITION	MDS18I225-M	MDS20I225-M	MDS25I225-M	UNIT	METHOD
GENERAL	Nominal Thickness	-	18	20	25	μ	Internal Method
	Density	-	0.91	0.91	0.91	g/cc	Internal Method
	Grammage	-	16.38	18.2	22.8	g/m ²	Internal Method
	Yield	-	61.1	54.9	44.0	m ² /kg	Internal Method
OPTICAL	Optical Density	-		2.2		-	Internal Method
SURFACE	Metal Adhesion	-		100		%	Internal Method
MECHANICAL	Tensile Strength (at break)	- MD - TD		1300 2700		kg/cm ²	ASTM D 882
	Elongation (at break)	- MD - TD		200 70		%	ASTM D 882
	Elastic Modulus	- MD - TD		18000 28000		kg/cm ²	ASTM D 882
	Linear Shrinkage (max)	- MD		4 2		%	ASTM D 1204
THERMAL	Heat Seal Range	-		95-145		°C	Internal Method
	Seal Strength	-		425		g/25mm	Internal Method (130°C/1sec/30psi)
BARRIER	WVTR 38° C 90% rh	-		0.8		g/m ² /day	ASTM F 1249
	OXTR 23° C 0% rh	-		100		cc/m ² /day	ASTM D 3985

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing except for metallized layer surface tension
- Strongly recommend online corona treatment in metallised films during lamination as treatment level decay with time is a natural phenomenon which depends on ambient conditions (Recommended storage conditions: Temperature < 30 deg C & Humidity 55% (Maximum) in original packed condition).

TOPPAN SPECIALITY FILMS