


PROVISIONAL

COCXHPSLM

COATED FILMS

WHITE CAVITATED TOP COATED PRESSURE SENSITIVE BOPP FACESTOCK FILM



DESCRIPTION

White Cavitated **BOPP** Film with one side Print Receptive Coated **Matte** Surface and other side Treated **Glossy** surface for Pressure sensitive Labels

PRODUCT FEATURES

- Excellent ink adhesion with a broad range of ink systems, including UV curing inks on Print receptive coated **matte** surface.
- Corona treated **glossy** surface suitable for adhesive anchorage
- High speed press performance.
- Coating adhesion is maintained in hot and cold water immersion without clouding
- Superior performance of print surface in humid environment
- Outstanding opacity and whiteness
- Excellent stiffness and mechanical properties
- Good dimensional stability
- Good die cutting performance

APPLICATIONS

- Labels

COATING SIDE

COCX HPSLM: Outside Print Receptive Coated Matte surface

TOPPAN SPECIALITY FILMS

PROVISIONAL

	PROPERTIES	POSITION	COCX60HPSL-M	UNIT	METHOD
GENERAL	Nominal Thickness	-	2.34	mils	Internal Method
	Grammage	-	9.16	lb/1000ft ²	Internal Method
	Yield	-	15749	in ² /lb	Internal Method
OPTICAL	Transmittance	-	18	%	ASTM D 1003
	Gloss (45°C) (Print receptive Matt side)	-	15	GU	ASTM D 2457
SURFACE	Wetting tension (Uncoated side)	-	38	dy/cm	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	- MD - TD	12798 25596	psi	ASTM D 882
	Elongation (at break)	- MD - TD	200 60	%	ASTM D 882
	Elastic Modulus	- MD	227520	psi	ASTM D 882
		- TD	398160		
THERMAL	Linear Shrinkage	- MD	4	%	ASTM D 1204
		- TD	2	%	

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. Coated films should be allowed to reach operating room temperature 24 hours before use.

SAFETY

Compliance with industrial health and safety standards. Coated films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing
- Coated reels must not be stacked